

	Material ID	Formula	Spacegroup	ϵ_{exp}	ϵ_{us}	$\epsilon_{Petousis}$	ϵ_{MP}	n_{sites}	n_{elems}
1	mp-5986	BaTiO3	99	907.3	223.1	11.5	11.5	5	3
2	mp-19717	TePb	225	414.0	85.8	335.4	379.8	2	2
3	mp-5246	KNbO3	38	342.7	67.5	15.5	11.9	5	3
4	mp-5229	SrTiO3	221	300.0	195.7	8.6	nan	5	3
5	mp-2201	PbSe	225	210.0	132.0	364.8	356.3	2	2
6	mp-21276	PbS	62	169.0	78.6	284.2	323.8	8	2
7	mp-691	SnSe	62	49.7	29.7	40.8	60.7	8	2
8	mp-3666	LiTaO3	161	44.8	37.0	39.2	38.1	10	3
9	mp-3834	BaZrO3	221	43.0	57.5	73.0	55.2	5	3
10	mp-19	Te	152	39.7	196.6	57.9	164.3	3	1
11	mp-3731	LiNbO3	1	39.0	26.9	29.5	40.0	40	3
12	mp-2231	SnS	62	37.3	19.5	30.8	48.1	8	2
13	mp-558134	TlF	39	35.0	7.2	39.5	39.5	4	2
14	mp-23167	TlCl	221	32.7	9.3	356.5	34.6	2	2
15	mp-22875	TlBr	221	30.6	8.1	180.2	40.8	2	2
16	mp-23197	TlI	221	29.6	10.2	154.7	44.5	2	2
17	mp-315	PbF2	225	28.4	19.8	33.0	23.0	3	2
18	mp-2242	GeS	62	28.2	17.4	19.6	34.3	8	2
19	mp-700	GeSe	62	26.0	20.4	22.5	39.5	8	2
20	mp-20194	CeO2	225	26.0	28.8	31.5	26.9	3	2
21	mp-226	FeS2	205	24.1	26.6	28.2	28.2	12	2
22	mp-557	TeO2	92	23.5	33.4	24.4	27.0	12	2
23	mp-4515	Ag3SbS3	161	22.7	10.8	13.2	17.2	14	3
24	mp-408	Mg2Ge	225	21.7	24.0	25.7	23.4	3	2
25	mp-4431	Ag3AsS3	161	20.9	10.5	13.5	14.2	14	3
26	mp-571102	TlI	225	20.8	7.9	21.5	17.6	2	2
27	mp-1367	Mg2Si	225	19.4	24.8	23.7	23.0	3	2
28	mp-9252	HgS	154	18.2	8.6	12.3	12.2	6	2
29	mp-634	HgS	152	18.2	8.7	12.1	12.0	6	2
30	mp-1634	MoSe2	194	18.0	11.0	11.7	11.7	6	2
31	mp-3163	BaSnO3	221	18.0	24.3	22.5	22.5	5	3
32	mp-3792	YAlO3	62	18.0	17.9	18.0	15.9	20	3
33	mp-22965	BiTeI	156	14.5	18.7	23.7	23.9	3	3
34	mp-2472	SrO	225	14.5	20.5	20.5	18.0	2	2
35	mp-9984	SnS2	186	13.9	11.1	12.5	12.5	6	2
36	mp-665	SnSe2	164	13.8	15.4	10.6	23.9	3	2
37	mp-909	As2Se3	14	13.4	nan	10.4	10.4	20	2
38	mp-23259	LiBr	225	13.2	5.9	15.6	11.4	2	2
39	mp-470	GeO2	136	13.0	15.2	13.5	13.2	6	2
40	mp-23703	LiH	225	12.9	9.1	14.2	14.3	2	2
41	mp-19399	Cr2O3	167	12.8	10.1	11.1	11.0	10	2
42	mp-2815	MoS2	194	12.7	9.6	9.8	9.8	6	2
43	mp-23231	AgBr	225	12.5	8.9	16.3	12.7	2	2
44	mp-2605	CaO	225	12.1	14.3	16.4	16.5	2	2
45	mp-2624	AlSb	216	12.0	13.5	13.4	13.3	2	2
46	mp-22905	LiCl	225	11.9	7.7	13.3	10.3	2	2
47	mp-4763	ZnSiP2	122	11.5	12.5	12.4	12.4	8	3
48	mp-149	Si	227	11.5	12.9	13.1	13.0	2	1
49	mp-4452	Cd(GaS2)2	82	11.4	9.2	9.5	9.5	7	3
50	mp-5342	GaAgS2	9	11.3	10.3	10.4	10.2	8	3
51	mp-22922	AgCl	225	11.2	13.1	14.8	11.4	2	2
52	mp-2490	GaP	216	11.1	12.6	12.9	12.8	2	2
53	mp-1479	BP	216	11.0	9.3	9.3	9.3	2	2
54	mp-406	CdTe	216	11.0	13.4	13.0	12.8	2	2
55	mp-1340	Ga2Se3	9	11.0	10.8	12.0	12.1	10	2
56	mp-856	SnO2	136	10.9	11.6	11.5	11.7	6	2
57	mp-4820	ZrSiO4	141	10.9	13.1	12.8	13.0	12	3
58	mp-1253	BaSe	225	10.7	18.8	14.1	14.1	2	2
59	mp-2251	Li3N	191	10.5	9.5	10.7	10.7	4	2
60	mp-14568	BaMgF4	36	10.3	9.0	12.1	9.6	12	3
61	mp-8884	ZnTe	186	10.1	nan	11.5	11.5	4	2
62	mp-2176	ZnTe	216	10.1	13.3	12.0	12.0	6	2
63	mp-1143	Al2O3	167	10.1	10.8	10.8	9.7	10	2
64	mp-2172	AlAs	216	10.1	11.8	11.6	11.5	2	2
65	mp-886	Ga2O3	12	10.1	10.7	12.1	11.2	10	2
66	mp-1170	SnS2	164	10.0	10.6	7.6	16.0	3	2
67	mp-4175	ZnSnP2	122	10.0	14.8	15.6	15.6	8	3
68	mp-1070	CdSe	186	9.9	12.6	12.2	12.6	4	2