

	Material ID	Formula	Spacegroup	ϵ_{exp}	ϵ_{us}	$\epsilon_{Petousis}$	ϵ_{MP}	n_{sites}	n_{elems}
69	mp-568662	BaCl2	225	9.8	7.8	8.1	6.9	3	2
70	mp-830	GaN	216	9.8	10.6	11.0	11.0	2	2
71	mp-804	GaN	186	9.8	10.5	10.8	10.9	4	2
72	mp-1550	AlP	216	9.8	10.4	10.4	10.4	2	2
73	mp-7140	SiC	186	9.8	10.7	10.6	10.6	4	2
74	mp-7631	SiC	186	9.8	10.6	10.5	10.4	12	2
75	mp-555359	KMnF3	140	9.8	9.1	10.0	10.0	10	3
76	mp-555123	KMnF3	221	9.8	12.0	13.4	13.4	5	3
77	mp-11714	SiC	186	9.7	10.6	10.5	10.5	8	2
78	mp-5238	GaCuS2	122	9.5	10.8	11.5	11.0	8	3
79	mp-3772	Cd(GaSe2)2	82	9.2	35.8	11.1	11.1	7	3
80	mp-1265	MgO	225	9.2	10.5	10.7	10.8	2	2
81	mp-661	AlN	186	9.1	8.8	8.7	8.7	4	2
82	mp-1190	ZnSe	216	9.1	12.2	10.7	10.7	2	2
83	mp-1138	LiF	225	9.1	6.4	8.6	8.7	2	2
84	mp-1986	ZnO	216	9.1	11.1	11.3	11.3	2	2
85	mp-672	CdS	186	8.9	9.8	10.0	10.0	4	2
86	mp-22914	CuCl	160	8.8	8.0	8.9	7.5	2	2
87	mp-2507	GaS	194	8.6	7.2	7.6	7.6	8	2
88	mp-10695	ZnS	216	8.6	9.2	9.3	9.4	2	2
89	mp-22896	LaCl3	176	8.6	10.6	10.2	10.2	8	2
90	mp-2758	SrSe	225	8.5	14.1	11.9	11.9	2	2
91	mp-560588	ZnS	186	8.3	9.2	9.1	9.1	4	2
92	mp-560902	MnF2	136	8.2	5.9	7.1	7.1	6	2
93	mp-2133	ZnO	186	8.1	10.8	10.8	10.8	4	2
94	mp-3953	CaCO3	167	8.0	7.5	7.9	9.2	10	3
95	mp-1572	GaSe	187	7.9	8.6	6.6	10.3	8	2
96	mp-22913	CuBr	119	7.9	8.4	9.2	9.1	2	2
97	mp-1415	CaSe	225	7.8	14.1	12.5	12.5	2	2
98	mp-4979	AlCuS2	122	7.8	8.6	8.7	8.7	8	3
99	mp-981	SrF2	225	7.7	7.9	7.6	6.5	3	2
100	mp-22691	InSe	160	7.5	10.9	9.7	9.7	4	2
101	mp-1873	ZnF2	136	7.4	8.6	8.1	8.1	6	2
102	mp-2741	CaF2	225	7.4	8.3	8.4	7.1	3	2
103	mp-1029	BaF2	225	7.3	8.0	8.3	7.1	3	2
104	mp-22958	KBrO3	160	7.3	7.5	7.1	7.0	5	3
105	mp-361	Cu2O	224	7.3	9.6	9.6	11.5	6	2
106	mp-5854	LiGaO2	33	7.2	6.5	7.0	7.1	16	3
107	mp-8016	AlCuSe2	122	7.2	10.5	10.4	10.1	8	3
108	mp-573697	CsCl	225	7.2	5.2	6.4	5.4	2	2
109	mp-1639	BN	216	7.1	7.0	7.0	7.0	2	2
110	mp-2542	BeO	186	7.1	7.1	7.3	7.3	4	2
111	mp-22925	AgI	216	7.0	8.5	7.3	7.2	2	2
112	mp-22894	AgI	186	7.0	8.7	7.2	7.2	4	2
113	mp-2895	Mg2SiO4	62	7.0	7.3	7.4	6.8	28	3
114	mp-684580	AgI	119	7.0	8.3	7.3	7.4	2	2
115	mp-3448	KMgF3	221	7.0	7.8	6.9	6.9	5	3
116	mp-827	KN3	140	6.9	7.4	6.2	6.2	8	2
117	mp-22895	CuI	7	6.5	8.5	7.8	7.7	8	2
118	mp-984	BN	194	6.4	4.7	4.7	4.7	4	2
119	mp-7848	AlPO4	82	6.1	3.7	3.8	3.8	6	3
120	mp-682	NaF	225	6.0	5.0	5.5	5.5	2	2
121	mp-22862	NaCl	225	5.9	5.4	6.3	6.5	2	2
122	mp-23193	KCl	225	5.9	5.1	5.6	4.7	2	2
123	mp-2964	NaNO2	44	5.9	5.0	5.3	nan	8	3
124	mp-28027	AsF3	33	5.7	3.4	5.2	5.2	16	2
125	mp-22898	KI	225	5.6	5.7	5.9	5.0	2	2
126	mp-66	C	227	5.5	5.8	5.8	5.8	2	1
127	mp-463	KF	225	5.5	6.2	6.4	5.3	2	2
128	mp-559798	NiF2	136	5.2	5.0	5.2	5.2	6	2
129	mp-1249	MgF2	136	5.2	5.2	3.3	5.1	6	2
130	mp-22903	RbI	225	4.9	4.2	5.7	5.7	2	2
131	mp-23295	RbCl	225	4.9	4.5	5.7	5.7	2	2
132	mp-22867	RbBr	225	4.9	3.6	5.7	5.7	2	2
133	mp-23251	KBr	225	4.9	3.7	5.6	4.8	2	2
134	mp-3955	AlPO4	154	4.7	nan	4.6	4.8	18	3
135	mp-632326	HCl	36	4.0	2.4	2.8	2.7	4	2
136	mp-27529	PI3	173	3.7	7.7	4.1	4.1	8	2