

	Material ID	Formula	Spacegroup	ϵ_{elec}	ϵ_{ionic}	ϵ_{total}	E_{gap} (eV)	Φ_{M} (eV)	n_{sites}	n_{elems}
1	mp-14550	TiCdO3	62	7.51	709	716	2.12	1,520	20	3
2	mp-997585:La->Y	Y8Al7GaO24	221	4.69	490	495	2.83	1,402	40	4
3	mp-32244:W->Mo	LiNbMoO6	113	5.76	528	534	2.19	1,172	18	4
4	mp-1097026	LaGaO3	221	5.23	305	311	3.42	1,062	5	3
5	mp-754225	YbTiO3	62	6.37	422	428	2.30	986	20	3
6	mp-3335	Sm2Ti2O7	227	6.13	331	337	2.82	951	22	3
7	wbm-1-40021	YbTiO3	62	6.36	387	393	2.33	916	20	3
8	mp-1226157	Cs2Ti(WO4)3	166	5.36	315	321	2.83	908	18	4
9	wbm-3-54931	Sr2LuTaO6	225	4.34	247	252	3.49	878	10	4
10	mvc-3783	MgTiO3	62	6.34	370	376	2.33	877	20	3
11	mp-556003	CaTiO3	74	6.39	384	390	2.16	843	10	3
12	mp-1202153	Na2Nb4O11	9	6.20	301	307	2.74	842	34	3
13	wbm-1-42539	La2MgZrO6	148	4.74	199	204	4.09	832	10	4
14	mp-1217978	SrPrScO4	107	4.64	224	228	3.52	804	7	4
15	mp-556925	TiMnO3	62	7.29	515	523	1.54	803	20	3
16	mp-979932:Sr->Pb	SiPb3O5	140	6.55	387	393	1.93	757	18	3
17	mp-1225952	CsNbWO6	74	5.43	248	254	2.92	741	18	4
18	wbm-1-25816	LiTaO3	167	5.41	223	228	3.21	733	10	3
19	mp-9890	TaAgO3	167	6.71	364	371	1.95	724	10	3
20	mp-754128:Ba->Ca	Ca3Hf2O7	139	4.24	199	203	3.47	704	12	3
21	mp-1219587	RbNbWO6	74	5.26	231	236	2.93	691	18	4
22	mp-1222804	LaY3Ti4O14	166	6.09	233	240	2.81	674	22	4
23	mp-1222933	LaTiNbO6	33	6.06	226	232	2.80	649	36	4
24	mp-755367:Cu->Rb	RbLiTa2O6	155	5.51	265	271	2.36	639	10	4
25	mp-4019	CaTiO3	62	6.39	257	263	2.31	606	20	3
26	wbm-1-38346	CaTiO3	62	6.39	254	261	2.32	605	20	3
27	mp-1218162	SrNd2Ti4O12	123	6.68	333	340	1.73	588	19	4
28	mp-756175	Zr2Bi2O7	227	6.53	200	206	2.80	578	22	3
29	mp-3858	NaTaO3	62	5.26	203	208	2.59	539	20	3
30	mp-755367:Cu->Ag	LiTa2AgO6	155	6.11	260	266	2.02	538	10	4
31	wbm-1-40022	YbTiO3	74	6.34	230	236	2.23	527	10	3
32	mp-1222976	LaTaBi2O7	74	6.39	262	268	1.96	526	22	4
33	mp-39511	LiCaTa2O6F	74	4.49	138	143	3.66	524	22	5
34	wbm-1-38356	CaZrO3	127	4.65	163	168	3.09	519	10	3
35	wbm-1-39241	NaTaO3	62	5.26	193	198	2.59	513	20	3
36	mp-6440	CaTiSiO5	15	4.51	171	175	2.91	509	16	4
37	wbm-3-51397	NdScO3	140	5.14	166	171	2.95	504	10	3
38	mp-1173711	Na3ErTi2Nb2O12	26	6.08	235	241	2.09	502	40	5
39	mp-559482	Ti2Bi2O7	227	8.42	180	189	2.62	495	22	3
40	mp-675778:Na->Li	LiY2F7	12	2.32	68	70	6.99	489	10	3
41	mp-1218781	Sr2La2MgTi3O12	1	5.67	233	239	1.97	471	20	5
42	mp-1220301	NbTiWO6	74	5.86	152	158	2.93	462	18	4
43	mp-755367:Cu->Na	NaLiTa2O6	155	5.32	150	155	2.96	460	10	4
44	mp-754936	DyAlO3	167	4.25	83	87	5.19	453	10	3
45	mp-1199037	NaNbO3	52	5.76	245	251	1.76	441	40	3
46	wbm-3-55347	Ba2ZrTiO6	225	5.68	192	198	2.23	441	10	4
47	wbm-2-35353	Ca2DyTaO6	87	4.46	111	116	3.79	439	10	4
48	mp-1218358	SrCaTi2O6	26	6.40	202	209	2.09	435	20	4
49	mp-38125	Sm2CdSe4	122	10.72	298	309	1.40	433	14	3
50	mp-1227686	Ca3Ta4(O6F)2	166	4.50	113	118	3.57	420	21	4
51	wbm-3-51131	Na2ZrO3	65	3.76	128	131	3.15	414	6	3
52	mp-1223520	KCa2Ta3O10	38	4.09	184	189	2.18	411	16	4
53	mp-5986	BaTiO3	99	5.63	218	223	1.78	397	5	3
54	mp-977360	AcF3	225	3.01	51	54	7.30	395	4	2
55	mp-759812	Li4Ti11O24	12	5.14	166	172	2.30	394	39	3
56	mp-769280	Ca5Ta4O15	164	4.67	127	131	2.98	391	24	3
57	mp-545665	WO3	191	6.14	313	319	1.19	381	12	2
58	mp-1518526	Sr2ZrTiO6	225	5.33	156	161	2.35	378	10	4
59	mp-1227336	BaSrTi2O6	123	6.65	206	212	1.75	371	10	4
60	mp-1227473	Ca2La2MgTi3O12	1	5.66	172	178	2.08	369	20	5
61	mp-1078457	Ba2ZrTiO6	225	5.68	157	162	2.22	359	10	4
62	wbm-1-40008	SrTiO3	99	5.96	190	196	1.80	354	5	3
63	wbm-1-38267	CaHfO3	127	4.39	91	96	3.67	352	10	3
64	mp-756214	YAlO3	167	4.25	66	70	5.00	351	10	3