Alloy 1060

1000 series | Reference sheet | Data checked 14 October 2026

A commercially pure aluminium designation with 99.6% minimum aluminium in the cited reference. Product-specific condition is essential when interpreting its properties.

Scope: Selected reference facts; incomplete alloy coverage

This reference sheet is not a material certificate, procurement specification or source of design allowables. Values apply only to their listed form, temper and condition. Confirm current requirements with the supplier and governing standard.

Forms and tempers

Forms: Extruded profiles; Rod and bar; Tube

Tempers in record: H112

Selected physical properties

Density: 0.0975 lb/in³

Temper: Not specified | Form: Extrusion | Condition: Temperature not specified

Basis: typical | Verification: single-source | Source: hydro1xxx | Checked: 2026-10-14

Selected mechanical properties

H112 | Extrusion

Tensile strength	Yield / proof strength	Thickness / specimen scope
60 MPa	15 MPa	All thicknesses in cited supplier table

Condition: Supplier reference; not a design allowable or certificate.

Basis: source-minimum | Verification: single-source | Source: hydro1xxx | Checked: 2026-10-14

Alloy 1060 / Composition and sources

Selected chemistry

Element	Published limit / value	Provenance
Al	Minimum 99.6 wt %	Basis: composition-minimum | Verification: single-source | Source: hydro1xxx | Checked: 2026-10-14

This is selected chemistry, not a complete composition specification. Unlisted elements must not be assumed to be zero.

Applications and selection guidance

Applications:

High-purity material is referenced for handling equipment and containers. Suitability for food or pharmaceutical use still requires assessment of the complete product and its surface condition.

Source register

hydro1xxx | Hydro 1xxx extrusion data

Revision / access scope: 2019/01 (February 2019) | Checked: 2026-10-14

https://www.hydro.com/globalassets/01-products--services/extruded-profiles/americas/ena-resources/alloy-data-sheets/hydro_2019_data_sheet_1xxx.pdf

Source facts are presented in an original editorial layout. Source publications may change; full source tables and imagery are not reproduced. This partial sheet does not imply interchangeability between alloy designations or certification of any supplied product.