Alloy 5083

5000 series | Reference sheet | Data checked 14 October 2026

A non-heat-treatable magnesium alloy referenced for marine sheet and plate. Exact temper, section and service requirements govern acceptance.

Scope: Selected indicative supplier facts; critical specification values require independent confirmation

This reference sheet is not a material certificate, procurement specification or source of design allowables. Values apply only to their listed form, temper and condition. Confirm current requirements with the supplier and governing standard.

Forms and tempers

Forms: Sheet

Tempers in record: O, H111

Selected physical properties

No physical property values published in this partial record.

Selected mechanical properties

O / H111 | Sheet

Tensile strength	Yield / proof strength	Thickness / specimen scope
275-350 MPa	125 MPa	0.2-6.3 mm; BS EN 485-2:2008 cited by supplier

Condition: Supplier cites historic EN edition; not an authorized standard table or certification

Basis: indicative-range | Verification: single-source | Source: aalco5083 | Checked: 2026-10-14

Alloy 5083 / Composition and sources

Selected chemistry

No chemistry values published in this partial record.

Applications and selection guidance

Applications:

The supplier density field is malformed and remains withheld. Marine selection must consider the approved material specification and fabricated condition; the alloy name alone does not establish vessel qualification.

Source register

aalco5083 | Aalco 5083 sheet reference

Revision / access scope: Public indicative sheet; cites historical EN revisions; currency not guaranteed | Checked: 2026-10-14

https://www.aalco.co.uk/datasheets/Aluminium-Alloy-5083-0-H111-Sheet-and-Plate_149.ashx

Source facts are presented in an original editorial layout. Source publications may change; full source tables and imagery are not reproduced. This partial sheet does not imply interchangeability between alloy designations or certification of any supplied product.