Alloy 5454

5000 series | Reference sheet | Data checked 14 October 2026

An aluminium sheet alloy referenced for transport and process-plant fabrication. The supplied condition must be matched to its dimensional range.

Scope: Selected indicative supplier facts; critical specification values require independent confirmation

This reference sheet is not a material certificate, procurement specification or source of design allowables. Values apply only to their listed form, temper and condition. Confirm current requirements with the supplier and governing standard.

Forms and tempers

Forms: Sheet

Tempers in record: O, H111

Selected physical properties

Density: 2690 kg/m³

Temper: Not specified | Form: Sheet | Condition: Temperature not specified; supplier indicative reference

Basis: typical | Verification: single-source | Source: aalco5454 | Checked: 2026-10-14

Selected mechanical properties

O / H111 | Sheet

Tensile strength	Yield / proof strength	Thickness / specimen scope
215-275 MPa	85 MPa	0.2-6.0 mm; BS EN 485-2:2008 cited by supplier

Condition: Supplier cites historic EN edition; not an authorized standard table or certification

Basis: indicative-range | Verification: single-source | Source: aalco5454 | Checked: 2026-10-14

Alloy 5454 / Composition and sources

Selected chemistry

No chemistry values published in this partial record.

Applications and selection guidance

Applications:

Electrical data is withheld because the source labels a conductivity unit as resistivity. End-use performance, weld condition and the governing purchase specification require separate confirmation.

Source register

aalco5454 | Aalco 5454 sheet reference

Revision / access scope: Public indicative sheet; cites historical EN revisions; currency not guaranteed | Checked: 2026-10-14

https://www.aalco.co.uk/datasheets/Aluminium-Alloy-5454-O-and-H111-Sheet_238.ashx

Source facts are presented in an original editorial layout. Source publications may change; full source tables and imagery are not reproduced. This partial sheet does not imply interchangeability between alloy designations or certification of any supplied product.