

High Strength Steel

Weldox 900 is a general structural steel with a minimum yield strength of 900 MPa (131 ksi). Weldox 900 meets the requirements on the corresponding steel grades and qualities according to EN 10025. Values in brackets are in imperial units for information only.

Applications	Load carrying structures having very high demands on low weight.
Designation	Weldox 900D with guaranteed impact toughness at -20° C (-4°F). Corresponds to S890Q Weldox 900E with guaranteed impact toughness at -40° C (-40°F). Corresponds to S890QL Weldox 900F with guaranteed impact toughness at -60° C (-76°F). Corresponds to S890QL1

Chemical composition

(ladle analysis)

C*	Si*	Mn*	P	S	B*	Nb*	Cr*	V*	Cu	Ti*	Al* total	Mo*	Ni	N
max %	max %	max %	max %	max %	max %	max %	max %	max %	max %	max %	min %	max %	max %	max %
0.20	0.50	1.60	0.020	0.010	0.005	0.04	0.70	0.06	0.10	0.04	0.018	0.70	0.10	0.010

*Intentional alloying elements. The steel is grain-refined

Plate thickness	CEV	CET
	Typical values	
	%	%
8 mm (0.314")	0.55	0.36
20 mm (0.786")	0.55	0.36
60 mm (2.358")	0.55	0.36

$$CEV = C + \frac{Mn}{6} + \frac{Cr+Mo+V}{5} + \frac{Ni+Cu}{15}$$

$$CET = C + \frac{Mn+Mo}{10} + \frac{Cr+Cu}{20} + \frac{Ni}{40}$$

Mechanical properties	Plate thickness mm (inch)	Yield strength ¹⁾ R _{p0.2} min MPa ²⁾ (ksi)	Tensile strength ¹⁾ R _m MPa ²⁾ (ksi)	Elongation ¹⁾ A ₅ min %	A ₅₀ min ³⁾ %
	4.0 - 53.0 (0.157-2.083)	900 (131)	940-1100 (136-160)	12	16
	53.1- 80.0 (2.083-3.144)	830 (120)	880-1100 (128-160)	12	16

¹⁾ For transverse test pieces

²⁾ 1 MPa = 1 N/mm²

³⁾ Only after special agreement

Weldox 900

Page. 2 (2)

Impact properties

Steel grade and quality	Impact energy for (J) (ft-lbf) tests on transverse ¹⁾ Charpy V 10 x 10 tests specimens ²⁾ Test temperatures in °C (°F)			
	0 (32)	-20 (-4)	-40 (-40)	-60 (-76)
	30 (22)	27 (20)	—	—
Weldox 900 D	30 (22)	27 (20)	—	—
Weldox 900 E	35 (26)	30 (22)	27 (27)	—
Weldox 900 F	40 (30)	35 (26)	30 (22)	27 (20)

¹⁾ Unless otherwise agreed, transverse impact testing according to EN 10025-6 option 30 will apply.

²⁾ For plate thicknesses less than 12 mm, subsize Charpy V-specimens are used. The specified minimum value is then proportional to the cross section of the specimen.

Testing	Testing according to EN 10025.	
Delivery condition	Q	Quenched and tempered as per EN 10025-6
Dimensions	<p>Weldox 900 is supplied in plate thicknesses of 4-80 mm ¹⁾ (0.157-3.144").</p> <p>More detailed information on dimensions is provided in our brochure 41-General Product Information Weldox, Hardox, Armax and Toolox-UK.</p> <p>¹⁾ Other thicknesses after special agreement.</p>	
Tolerances	<p>- All plates are produced with AccuRollTech™ thickness precision guarantee.</p> <p>AccuRollTech™ meets the requirements of EN 10 029, but offers more narrow tolerances.</p> <p>- Tolerances on flatness according to Class N (Normal tolerances).</p> <p>More detailed information is given in our brochure 41-General Product Information Weldox, Hardox, Armax and Toolox-UK as well as at www.weldox.com.</p>	
Surface condition	According to EN 10163-2, Class A, Subclass 1 (repair by welding is allowed).	
General technical delivery requirements	According to our brochure 41-General Product Information Weldox, Hardox, Armax and Toolox-UK.	
Heat treatment and fabrication	<p>Weldox 900 has obtained its mechanical properties by a quenching and tempering process.</p> <p>Weldox 900 is not suited for applications requiring hot working at temperatures above 550°C (1020°F) since the material may then lose its guaranteed properties.</p> <p>For information concerning welding and fabrication, see our brochures on www.weldox.com or consult our Technical Customer Service.</p> <p>Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration.</p>	

108-US, Weldox is a registered trademark of SSAB Oxelösund AB, Sweden.
The UK English version of this document shall prevail in case of discrepancy.
Download the latest version of this document on internet: www.ssab.com

SSAB Oxelösund AB, 613 80 Oxelösund, Sweden, +46 155 25 40 00, www.ssab.com