

# Domex 550 MC

## Hot rolled, extra high strength, cold forming steel

### Product

Domex cold forming steels are thermo-mechanically rolled in modern plants where the heating, rolling and cooling processes are carefully controlled.

The chemical analysis, consisting of low levels of carbon and manganese has precise addition of grain refiners such as niobium, titanium or vanadium. This together with a clean structure, makes Domex Steels the most competitive alternative for cold formed and welded products.

Domex 550 MC with designation D and E meet and exceed the demands for steel S550 MC in EN-10149-2.

### Applications

The extra high strength steel grades are used in applications such as truck chassis, cranes and earthmoving machines. In these applications, the high strength of the steels is used to save weight and/or to increase the payload.

As a result of this and the good formability of the steels, the total costs can be reduced.

### Dimension range

Domex 550 MC is available in the range of sizes tabulated below in as rolled or pickled condition with mill edge.

For material with trimmed edges, the width is reduced by 35 mm.

Some exceptions may occur.

Thickness (mm)	Width (mm)	Length (mm)
2,00 - (3,00)	1000 - 1035	1500 - 13000
3,00 - (4,00)	885 - 1300	1500 - 13000
4,00 - (5,00)	885 - 1450	1500 - 13000
5,00 - (10,00)	885 - 1600	1500 - 13000
10,00 - (11,00)	885 - 1300	1500 - 13000
11,00 - 12,00	885 - 1050	1500 - 13000

### Chemical composition

C	Si	Mn	P	S	Al	Nb	V	Ti
%	%	%	%	%	%	%	%	%
max	max	max	max	max	min	max	max	max
0,12	0,10 <sup>1)</sup>	1,80	0,025	0,010	0,015	0,09 <sup>2)</sup>	0,20 <sup>2)</sup>	0,15 <sup>2)</sup>

1) If the material is to be hot-dip galvanized, this must be specified in the order.

2) Sum of Nb, V and Ti = 0.22% max.

### Mechanical properties

Yield strength	Tensile strength	Elongation on failure	
R <sub>eh</sub> N/mm <sup>2</sup>	R <sub>m</sub> N/mm <sup>2</sup>	< 3 mm	≥ 3 mm
min	min - max	A <sub>80</sub> %	A <sub>5</sub> %
550	600 - 760	14	17

### Bendability

	Nominal sheet thickness, t		
	≤ 3 mm	3 mm < t ≤ 6 mm	> 6 mm
Min. recommended bending radius (≤ 90°)	0,6 x t	1,0 x t	1,2 x t

### Impact strength

The Charpy V-notch test is carried out according to EN 10045-1.

Designation	Test temperature	Energy level
B	Not impact tested	
D	-20°C	40J
E	-40°C	27J

1) Other test temperatures and impact strengths are available subject to special agreement.

## Welding

The low contents of carbon, phosphorus and sulphur enable all conventional welding methods to be readily used for Domex 550 MC. No preheating is necessary. A narrow heat affected zone with a somewhat lower hardness is formed immediately adjacent to the weld. However, if normal welding parameters and methods are used, the heat affected zone is of no practical significance.

Tensile test pieces taken across the weld can meet the same minimum tensile strength requirements as the base metal.

If the stresses acting on the weld are low also under-matching filler metals can be used.

There are a large number of matching or over matching filler metals that can be used for welding of Domex 550 MC, which gives a weld that can meet the same minimum tensile strength requirements as the base metal. Some examples of different filler metals that can be used are tabulated below.

## Heat treatment

Stress relief annealing should be carried out within the temperature range of 530 - 580°C. Heat treatment above this range, e.g. normalizing and hot forming, reduces the strength and should be avoided.

## Technical service and information

Knowledge Service Center will be pleased to assist with additional information concerning this product and other products from SSAB Tunnpått.

## Examples of different matching and over matching filler metals

Manual metal arc welding Coated electrode	Gas shielded metal arc welding		Manufacturer
	Cored electrode	Wire electrode	
OK 75.75 Filarc 108 Maxeta 110 Tenacito 75	OK Tubrod 15.27 Filarc PZ6147 - Fluxofil 42	OK Autrod 13.13 PZ6047; PZ6048 Elgamatic 135 Carbofil NiMo-1	ESAB Filarc ELGA Oerlikon

The particulars in this data sheet are correct at the time of going to print and are intended to give general guidance for the use of the product. Subject to changes arising from continual product development. The information and data must not be regarded as guaranteed values, unless specially confirmed in writing.



SSAB Tunnpått AB  
SE-781 84 Borlänge  
Sweden  
Tel +46 243 700 00  
Fax +46 243 720 00  
office@ssabtunnplat.com  
ssabtunnplat.com  
ssabdirect.com

Denmark  
SSAB Svensk Stål A/S  
Tel +45 4320 5000  
ssab.dk

Finland  
OY SSAB Svenskt Stål Ab  
Tel +358-9-686 6030  
ssab.fi

France  
SSAB Swedish Steel SA  
Tel +33 1 55 61 91 00  
ssab.fr

Germany  
SSAB Swedish Steel GmbH  
Tel +49 211 91 25-0  
Tel +49 711 6 8784-0  
ssab.de

Great Britain  
SSAB Swedish Steel Ltd  
Tel +44 1905 795794  
swedishsteel.co.uk

Italy  
SSAB Swedish Steel S.p.A  
Tel +39 030 905 881 1  
ssab.it

The Netherlands  
SSAB Swedish Steel BV  
Tel +31 24 67 90 550  
ssab.nl

Norway  
SSAB Svensk Stål A/S  
Tel +47 23 11 85 80  
ssab.no

Poland  
SSAB Swedish Steel Sp z o.o.  
Tel +48 22 723 04 80

Portugal  
SSAB Swedish Steel  
Tel +351 256 371 610  
ssab.pt

Spain  
SSAB Swedish Steel S.L.  
Tel +34 91 300 5422  
ssab.es

USA  
SSAB Swedish Steel Inc.  
Tel +1 412-269 21 20  
swedishsteel.us

Brazil  
SSAB Swedish Steel Ltda.  
Tel + 55 41 3014 9070  
ssab.com.br

South Africa  
SSAB Swedish Steel Pty Ltd  
Tel +27 11 822 2570  
swedishsteel.co.za

China  
SSAB Swedish Steel  
Tel +86 10 6466 3441  
swedishsteel.cn

Korea  
SSAB Swedish Steel Ltd  
Tel +82 31 906 2770