



Domex 550 W

The weather resistant extra high strength steel

Product

A weather resistant steel in the Domex range characterized by:

- Corrosion resistance
- Extra high strength
- Good formability
- Good impact toughness
- Good weldability

The unique combination of these properties is achieved by fine grain size, precipitation hardening and closely controlled hot rolling practice. Moreover, this steel is weather resistant, i.e. during outdoor usage within a couple of years, a smooth compact oxide layer is formed that inhibits further corrosion.

Applications

Typical applications are vehicle underbodies, container frame structures, steel bridges and building constructions, chimney cases, rail wagons, snow sheds, different kinds of masts i.e. applications where a corrosions resistant steel is needed together with high strength.

Dimension range

Domex 550 W can be delivered in dimensions according to table below.

Thickness (mm)	Width (mill edge) (mm)	Length (mm)
3	1280	1500 - 13000
4	1280	1500 - 13000
5	1280	1500 - 13000
6	1280	1500 - 13000

For special requirements other thicknesses (within the range 3-6mm) and widths can be delivered.

Chemical composition

C	Si	Mn	P	Cu	Cr	Micro
%	%	%	%	%	%	alloying
max	max	max	max	max	max	elements
0,10	0,45	0,80	0,12	0,35	0,95	

Mechanical properties

Yield strength R _{eH} N/mm²	Tensile strength R _m N/mm²	Elongation A ₅ %
min 550	min 600	min 18

Bending

For sheet thickness 3-6mm the minimum inner bending radius for 90° bend is 1xt, using a die opening of 10xt.

Impact toughness

Charpy-V test is carried out with longitudinal test specimens. Domex 550 W can be delivered with impact toughness guarantee at -40°C and 27J.

Welding

The weldability of Domex 550 W is good. No preheating is required. All conventional welding methods can be used.

To obtain the same corrosion resistance in the weldment as in the base metal special filler metals should be used. The producers of filler metals have given the following recommendations for welding of this type of weather resistant steels:.

Producer	MMA (Manual metal arc)	MAG (Gas metal arc	FCAW (Flux cored arc)
ESAB	OK 73.08	OK Autrod 13.26	OKTubrod 14.01
Filarc	85CP	PZ 6012	PZ 6112
Oerlikon	Tenconrd Kb	Spoolcord TD-COR	Fluxofil 18

OK Autrod 13.26 is a matching wire while the other filler metals are slightly undermatching in relation to the base metal strength of Domex 550 W.

Heat treatment

Normally stress relieving is not needed. If however needed, stress relieving should be carried out below 580°C. Heating above this temperature, such as normalising or hot forming, reduces the strength and should be avoided.

Technical service and information

Knowledge Service Center will be pleased to assist with additional information concerning this product from SSAB Tunnplåt.

The particulars in this data sheet are correct at the time of going to print and are intended to give general guidance for the use of the product. Subject to changes arising from continual product development. The information and data must not be regarded as guaranteed values, unless specially confirmed in writing.

SSAB Tunnplåt AB

781 84 Borlänge Sweden Tel +46 243 700 00 Fax +46 243 720 00 office@ssabtunnplat.com www.ssabtunnplat.com www.ssabdirect.com Australia

SSAB Swedish Steel Pty. Ltd Tel +61 3 9548 8455

Benelux SSAB Swedish Steel BV Tel +31 24 679 05 50 ssab.nl

BrazilSSAB Swedish Steel Ltda.
Tel + 55 41 3014 9070

ssab.com.br

Czech Republic SSAB Swedish Steel s.r.o.

55AB Swedish Steel s.r.o. Tel +420 545 42 2550

China SSAB Swedish Steel Tel +86 10 6440 3550 swedishsteel.cn Denmark

SSAB Svensk Stål A/S Tel +45 4320 5000 ssab.dk

FinlandOY SSAB Svenskt Stål AB
Tel +358 9 686 6030
ssab.fi

France SSAB Swedish Steel SA Tel +33 1 55 61 91 00 ssab.frt

GermanySSAB Swedish Steel GmbH
Tel +49 211 912 50
Tel +49 711 687 840
ssab.de

Great BritainSSAB Swedish Steel Ltd
Tel +44 1905 795794
swedishsteel.co.uk

Italy
SSAB Swedish Steel S.p.A
Tel +39 030 905 881 1
ssab.it

Norway SSAB Svensk Stål A/S Tel +47 23 11 85 80 ssab.not

Poland SSAB Swedish Steel Sp. z o.o. Tel +48 22 723 00 49

Portugal SSAB Swedish Steel Tel +351 252 291 000 ssab.pt

Russia SSAB Swedish Steel Tel + 791 690 84 767 **Spain**SSAB Swedish Steel S.L.
Tel +34 91 300 54 22
ssab.es

South Africa SSAB Swedish Steel Pty Ltd Tel +27 11 822 2570 swedishsteel.co.za

South Korea SSAB Swedish Steel Ltd Tel +82 2 369 7272

Turkey SSAB Swedish Steel Celik Dis Tic.Ltd.Sti. Tel +90 216 372 63 70 ssab.com.tr

USASSAB Swedish Steel Inc
Tel +1 412-269 21 20
swedishsteel.us

