



# Dogal 500 DP

# **Extra High Strength Steels**

#### General

Dogal 500 DP is an extra high strength steel that is hot-dip galvanized for corrosion protection.

Dogal DP steels are easy to coldform and excellent for stretch forming and roll forming. The steel grade is supplied in accordance with prEN 10336

Dogal DP grades show less spring-back after cold forming campared to HSLA steels with the same tensile strength due to a large gap between the yield strength and the tensile strength, i.e a high work hardening exponent.

#### **Dimensions**

Dogal 500 DP steels are available in thicknesses between 0,7 and 2,0 mm and in widths up to 1500 mm. Limitations may occur depending on combination of width and thickness.

# **Applications**

Extra high strength steels can be used for example in the automotive and transport industry. Dogal 500 DP is very suitable for any application with stretch-forming. The improved bendability properties makes more complicated design solutions possible. Strength can be increased and weight can be saved by replacing mild steels with extra high strength grades.

#### Tolerances

Dogal DP are supplied to tolerances in accordance with EN 10143.

# Zinc coating

The various coating thicknesses are classified into weight classes which specify the minimum zinc weight in g/m<sup>2</sup> on both sides, as determined by means of the triple-spot test in accordance with EN 10327.

| Weight class | Coating thickness<br>per side *<br>µm | Weight determination g/m² on two side<br>  Triple-spot-test   Singel test<br>  min   min |     |  |  |
|--------------|---------------------------------------|--|-----|--|--|
| Z100         | 7                                     | 100  | 85  |  |  |
| Z120         | 8                                     | 120  | 100 |  |  |
| Z140         | 10                                    | 140  | 120 |  |  |
| Z200         | 14                                    | 200  | 170 |  |  |
| Z275         | 20                                    | 275  | 235 |  |  |

<sup>\*</sup> The values are calculated on the basis of the minimum values for the triple-spot test  $(1 \mu m = 7.14 \text{ g/m}^2)$ .

# **Surface apperance**


The surface is skin-passed.

#### **Surface treatment**

DP steels are provided with chemical and/or oiling passivation as surface protection. The chemical passivation are chromate free and fulfil the demands in the End-of-life Vehicles Directive (2000/53/EC) and the Directive on the restriction of the use of ceratin hazardous substances in electrical and electronic equipment (2002/95/EC).

# **Forming limit curves**

(typical values)



# **Mechanical properties**

(transverse to rolling direction)

| Steel grade  | Yield strength   | Tensile strength                  | Elongation                  | Bake Hardening index BH <sub>2</sub> |  |
|--------------|--|-----------------------------------|-----------------------------|--------------------------------------|--|
|              | R <sub>p02</sub> or R <sub>eL</sub><br>N/mm<br>min - max | R <sub>m</sub><br>N/mm<br>min-max | A <sub>so</sub><br>%<br>min | MPa<br>min                           |  |
| Dogal 500 DP | 300 - 380  | 500 - 600                         | 23                          | 30                                   |  |

# **Chemical composition**

|              | % by mass |           |           |          |        |                          |              |              |          |          |
|--------------|-----------|-----------|-----------|----------|--------|--------------------------|--------------|--------------|----------|----------|
| Steel grade  | C<br>max  | Si<br>max | Mn<br>max | P<br>max | S      | Al <sub>tot</sub><br>min | Cr+Mo<br>max | Nb+Ti<br>max | V<br>max | B<br>max |
| Dogal 500 DP | 0,080     | 0,30      | 1,56      | 0,020    | 0,0040 | 0,020                    | 0,74         | 0,015        | 0,020    | 0,001    |

# Welding

Dogal 500 DP can be welded with all conventional fusion welding methods. The steel can be spot welded to itself and also to other steels (soft steels and high strength steels). When spot welding is used it is recommended that increased electrode forces and longer weld times are used.

# **Technical service and information**

Knowledge Service Center will be pleased to assist with additional information concerning this product from SSAB Tunnplåt.

Specifications herein are for general reference only. They are valid at date of publication and are subjects to change without notice due to ongoing product development.

Specifications are binding only if confirmed in writing.

SSAB Tunnplåt AB
781 84 Borlänge
Tel +46 243 700 00
Fax +46 243 720 00
office@ssabtunnplat.com
www.ssabtunnplat.com
www.ssabdirect.com

**Denmark** SSAB Svensk Stål A/S Tel +45 4320 5000 ssab.dk

Finland OY SSAB Svenskt Stål AB Tel +358 9 686 6030 ssah fi

**Czech Republic** SSAB Swedish Steel s.r.o. Tel +420 545 422 550

France
SSAB Swedish Steel SA
Tel +33 155 61 91 00
ssab.fr

**Germany**SSAB Swedish Steel GmbH
Tel +49 211 91 25-0
Tel +49 711 6 87 84-0
ssab.de

**Great Britain**SSAB Swedish Steel Ltd
Tel +44 1905 795794
swedishsteel.co.uk

Italy SSAB Swedish Steel S.p.A Tel +39 030 90 58 811 ssab.it

The Netherlands
SSAB Swedish Steel BV
Tel +31 24 679 05 50
ssab.nl

Norway SSAB Svensk Stål A/S Tel +47 23 11 85 80 ssab.no

**Poland**SSAB Swedish Steel Sp. z o.o.
Tel +48 22 723 03 80
Tel +48 22 723 00 49

**Portugal**SSAB Swedish Steel
Tel +351 256 371 610
ssab.pt

**Spain**SSAB Swedish Steel SL
Tel +34 91 300 5422
ssab.es

SSAB Swedish Steel Inc Tel +1 412-269 21 20 swedishsteel.us

**Brazil**SSAB Swedish Steel Ltda.
Tel + 55 41 3014 9070
ssab.com.br

South Africa SSAB Swedish Steel Pty Ltd Tel +27 11 822 2570 swedishsteel.co.za China

SSAB Swedish Steel Tel +86 10 6466 3441 swedishsteel.cn

**Korea**SSAB Swedish Steel Ltd
Tel +82 2 369 7272

Japan SSAB Swedish Steel Ltd Tel +81 3 3456 3447

