

Prelaq Nova

Prepainted sheet steel for buildings

Applications

Prelaq Nova is suitable for external building products, such as profiled sheet for roofing and wall cladding, prefabricated wall panels, wall and roof fittings, and sheet steel roofing tiles. In addition to being suitable for normal environments, Prelaq Nova can also be used in industrial and marine environments.

Product description

Prelaq Nova with dual finishes

Prelaq Nova is produced with dual types of surface finishes. The normal type (Prelaq Nova) and a matt type (Prelaq Nova Matt). Aesthetical requirements indicate what is best suited for a specific building.

Prelaq Nova has a coating with a total thickness of 50 µm. The thickness of the paint is optimized for wear resistance, weathering resistance and consumption of resources. It has greater durability than standard polyester when exposed to people walking on the roof and other stresses occurring on roofs. The coating has excellent gloss retention and colour fastness, and also provides good protection against corrosion.

The reverse side of the sheet is painted as standard with grey epoxy-type paint, and the reverse side is marked with particulars of product name and production date.

Paint Coat

	Thickness	
	Prelaq Nova	Prelaq Nova Matt
Front side	50 µm	50 µm
Reverse side (grey)	10 µm	10 µm

Properties

	Test method	Data	
		Prelaq Nova	Prelaq Nova Matt
Paint thickness, nominal	ISO 2808	50 µm	50 µm
Gloss	EN 13523-2	40	10
Minimum inner bending radius	EN13523-7	1 T ¹⁾ (dark colours) 2 T ¹⁾ (light colours)	1 T ¹⁾ (dark colours) 2 T ¹⁾ (light colours)
Adhesion	EN 13523-6	Satisfactory	Satisfactory
Scratch resistance	EN 13523-12	Min 35 N	Min 35 N
Maximum service temperature		100 °C	100 °C

1) T is the sheet thickness

Substrate material

Prelaq Nova is supplied on hot-dip galvanized sheet to EN 10326 or EN 10327, with zinc weight class Z 275 or Z 350.

Colours

The standard colours are shown in a special colour chart.

Inspection and maintenance

Regular maintenance extends the useful life of the paint coat and thus also the intervals between repainting, see the brochure entitled "Inspection and maintenance of prepainted steel sheet", E 838. Take care to avoid damage to the coating during production and installation. To repair scratches and handling damage, clean and touch up with Abratex Lackstift (touch-up crayon) or equivalent product. Several makes and systems of repainting paints are available on the market.

Intervals between repainting

A suitable time for repainting can be determined by regular inspection of the paint coat.

An assessment of when it is appropriate to repaint the sheet should be made by an expert. The normal time before repainting Prelaq Nova is considered to be at least 20 years, provided that regular maintenance is done.

Resistance to corrosion

The corrosion resistance of Prelaq Nova is continuously tested by exposure of test pieces outdoors in corrosive marine and industrial environments.

Prelaq Nova belongs to corrosion protection category RC4 as per ENV 10169-2.

For indoor use, Prelaq Nova conforms to moisture category CPI5 and environmental category A4 as per EN 10169-3:2003.

The material should not be stored or installed close to damp and corrosive materials or in areas in which the sheet is subjected to strong cleaning agents or in premises in which animals are kept.

Resistance to UV light

Prelaq Nova can be used in UV resistance category not exceeding R_{uv}3 as per ENV 10169-2. This means that Prelaq Nova can be used north of latitude 37°N (southern Europe). Between latitude 37° N and 45° N the altitude must not exceed 900 m.

Resistance to chemicals

The coating generally has good resistance to chemicals. However, there are exceptions, e.g. certain organic solvents such as aromatics, ketones and chlorinated hydrocarbons.

Fire classification

Prelaq Nova fulfills the following requirements:

Classification	Standard
Class A2 - s2,d0	EN 13501-1
Klasse B2	Din 4102 Teil 1
Class 1	BS476 Part 7

Industrial safety

Special measures should be taken to prevent personnel being exposed to the air pollutants formed during grinding, welding and cutting of the sheet material. For further information, refer to your national industrial safety regulations concerning paints and thermosetting plastics.

Prelaq Nova has non-slip properties that are equivalent to those of other roofing sheet materials.

Working

If the material is used for producing pressed or bent parts with tight radii, check that no cracking has occurred in the paint coat. See the minimum bending radius in the table of properties.

Working should be avoided at sheet temperatures below +15°C. Cracking of the paint coat may occur at lower temperatures.

Cut edges

Edge corrosion may occur if the sheet is used in corrosive environments and if the cut edges of the sheet are exposed. Protective painting can be applied to avoid edge corrosion

Environment

Environmental work has long been an established part of the operations at SSAB Tunnplåt. Developments are reported in an annual environmental report to the authorities. SSAB Tunnplåt devotes active work to the development of its processes, and develops products that are beneficial from the environmental aspect and from a life cycle perspective. SSAB Tunnplåt has gained environmental certification in accordance with ISO 14001.

Steel is 100% recyclable. The environmental properties of Prelaq Nova are given in a special environmental specification that can be ordered from SSAB Tunnplåt or obtained from our web site.

Miscellaneous

Storage of the material outdoors should be avoided. If this is unavoidable, the material should be satisfactorily covered and should be stored so that good air circulation will be obtained, in order to avoid moisture.

For particulars of tolerances and properties in general, refer to European Standard EN 10169-1.

Technical service and information

The Organic Coated Products Marketing Department will be pleased to provide additional information on this product and other prepainted products from SSAB Tunnplåt.

The information in this document is valid at the date of publication and is intended to serve as general guidance for the use of the product. The latest version of this document is published on our web site. We reserve the right to introduce changes resulting from our continual product development work. The information and data given must not be regarded as binding, unless specially confirmed in writing.



SSAB Tunnplåt AB

SE-781 84 Borlänge
Sweden
Tel: 0243-700 00
Fax: 0243-720 00
office@ssabtunnplat.com
ssabtunnplat.com
prelaq.com

Denmark

SSAB Svensk Stål A/S
Tel +45 43 20 5000
ssab.dk

Finland

OY SSAB Svenskt Stål AB
Tel +358 9 686 6030
ssab.fi

France

SSAB Swedish Steel SA
Tel +33 1 55 61 91 00
ssab.fr

Great Britain

SSAB Swedish Steel Ltd.
Tel +44 1384 746 60
dobel.co.uk

Italy

SSAB Swedish S.p.A
Tel +39 030 90 58 811
ssab.it

The Netherlands

SSAB Prelaq BV
Tel +31 24 679 07 00
ssab.prelaq.nl

Norway

SSAB Svensk Stål A/S
Tel +47 23 11 85 80
ssab.no

Poland

SSAB Swedish Steel
Sp. z o.o.
Tel +48 22 353 15 00
prelaq.pl