



Contents lists available at ScienceDirect

Chemical Engineering Journal

journal homepage: www.elsevier.com/locate/cej

Syngas production for Fischer-Tropsch process via co-electrolytic processes of CO₂ reduction and NH₃ oxidation

Minjun Choi^{a,b,1}, Jin Won Kim^{a,b,c,1}, Sunki Chung^{a,b,c}, Youjin Lee^{a,b}, Sungyool Bong^{a,b,c}, Jaeyoung Lee^{a,b,c,*}

^a School of Earth Sciences and Environmental Engineering, Gwangju Institute of Science and Technology (GIST), Gwangju 61005, Republic of Korea

^b International Future Research Center of Chemical Energy Storage and Conversion Processes (ifRC-CHESS), Gwangju Institute of Science and Technology (GIST), Gwangju 61005, Republic of Korea

^c Ertl Center for Electrochemical and Catalysis, Gwangju Institute of Science and Technology (GIST), Gwangju 61005, Republic of Korea

ARTICLE INFO

Keywords:

Co-electrolytic processes
Carbon dioxide reduction
Ammonia oxidation
Fischer-Tropsch process
Syngas production
Low energy consumption

ABSTRACT

As a solution for simultaneously reducing harmful air pollutants containing ammonia and CO₂, with respect to ameliorating the effects of global warming, we report a co-electrolytic process involving ammonia oxidation reaction (AOR) and an electrochemical CO₂ reduction reaction (ECR) for syngas production that uses less energy compared to the conventional process. The conventional process is based on ECR and an oxygen evolution reaction (OER), and it requires a high amount of energy because of its higher thermodynamic and practical operation voltage. By contrast, the new co-electrolytic process employs an AOR instead of an OER, and a decreased energy consumption (maximum 34.04%) is observed with the addition of ammonia. The new process provides advantages with respect to its lower energy consumption and controllable hydrogen and carbon monoxide ratio. We also found that this syngas production method, in which the NH₃ concentration and applied current can be controlled, produces syngas with different H₂ and CO ratios, it is comparable to that used in the conventional Fischer-Tropsch process.

1. Introduction

Developing sustainable technologies is necessary to reduce environmental pollutants and mitigate climate change caused by high carbon dioxide (CO₂) concentrations owing to industrialization [1]. Of the various methods used, the electrolytic process provides several advantages that complement the conventional technique. For example, it employs mild operating conditions and atom-efficient strategies for selective conversion using electrons as reactants, which are known as oxidation and reduction steps [2]. Further, as no harmful or toxic chemical agents are used, it efficiently minimizes social and environmental damage [3–5].

Electrochemical CO₂ reduction (ECR) employs a mild operating temperature and pressure and is thus a promising electrolytic process

for producing value-added chemicals from waste CO₂ [6–8]. Energy-dense molecules are converted by the ECR process, and these can be selectively controlled by controlling the electrochemical conditions and developing the electrocatalyst materials. In addition, the ECR process can be easily scaled up [9]. It has thus become an important technology for reducing the accumulation of CO₂. It has no carbon footprint, and it can be used in combination with renewable energy, such as that obtained by solar, wind, and hydroelectric power systems [6,9,10].

The development of electrocatalysts has been the primary focus of many ECR process studies [11–13] because the final product can be controlled depending on the type of electrocatalyst applied. For example, Au- and Ag-based materials are the most well-known electrocatalysts for producing carbon monoxide (CO) from CO₂ [14,15], and Cu-based electrocatalysts produce multiple carbons such as ethylene,

Abbreviations: AOR, Ammonia oxidation reaction; FE, Faradaic efficiency; GC, Gas chromatography; GDE, Gas diffusion electrode; GIST, Gwangju Institute of Science and Technology; HER, Hydrogen evolution reaction; LSV, Linear sweep voltammetry; OER, Oxygen evolution reaction; TCD, Thermal conductivity detector; UV, UV-Vis; BK, blank anolyte; ECR, electrochemical CO₂ reduction reaction.

* Corresponding author at: School of Earth Sciences and Environmental Engineering, Gwangju Institute of Science and Technology (GIST), Gwangju 61005, Republic of Korea.

E-mail address: jaeyoung@gist.ac.kr (J. Lee).

¹ These authors contributed equally to this work.

<https://doi.org/10.1016/j.cej.2021.132563>