



Short communication

Multifunctional non-Pt ternary catalyst for the hydrogen oxidation and oxygen evolution reactions in reversal-tolerant anode

Seung Woo Lee^a, Bong Ho Lee^a, Tae-Yang Kim^a, Chaekyung Baik^a, Mi So Kim^b, Geun Seok Chai^b, Chanho Pak^{a,*}^a Graduate Program of Energy Technology, School of Integrated Technology, Institute of Integrated Technology, Gwangju Institute of Science and Technology, Gwangju 61005, Republic of Korea^b Radiation Technology eXcellence (RTX), Daejeon 34025, Republic of Korea

ARTICLE INFO

Keywords:

Non-Pt ternary alloy catalyst
Reversal-tolerant anode
Hydrogen oxidation reaction
Oxygen evolution reaction
Polymer electrolyte membrane fuel cell


ABSTRACT

The reversal-tolerant anode (RTA) has been introduced to mitigate the fatal anode degradation by cell voltage reversal under hydrogen fuel starvation in fuel cell electric vehicles (FCEVs). The RTA employs an oxygen evolution reaction (OER) catalyst in the anode to boost water electrolysis rather than carbon corrosion under fuel starvation. Graphitic carbon-supported IrRu₄Y_{0.5} exhibits outstanding performances for hydrogen oxidation reaction and OER. In single cell test, the IrRu₄Y_{0.5} delivers ~ 21% better performance and longer RTA durability (~ 64 min) than Pt/C catalyst. It is anticipated that IrRuY-based alloy catalysts could replace high-priced Pt-based catalysts as multifunctional RTA for FCEVs.

1. Introduction

Polymer electrolyte membrane fuel cells (PEMFCs) are ideal for maximizing hydrogen utilization, because they quickly and efficiently convert the chemical energy stored in hydrogen (H₂) to electrical energy without emitting greenhouse gases [1–3]. Despite the improvements in fuel cell technology accomplished through much efforts spanning several decades, an increase in the fuel cell market share still faces challenges. These include cost, performance and durability. In the case of fuel cell electric vehicles (FCEVs) that employ PEMFC systems as a power train, there are many transient operational conditions. Several of these conditions can cause fuel starvation, which results in reversal of the cell potential and oxidation of carbon in the anode.

The carbon oxidation reaction (COR, Eq. (1)) in the anode occurs easily to provide protons and electrons required for system operation under fuel starvation conditions by competing the oxygen evolution reaction (OER, Eq. (2)), which is the alternative reaction for the generation of protons and electrons [4].



If the carbon corrosion persists at a high potential during fuel starvation, the electrochemically active surface area of the catalyst decreases drastically, leading to serious deterioration of the membrane

electrode assembly (MEA). To mitigate the fatal anode degradation, some OER catalysts were added into the anode to realize the reversal-tolerant anode (RTA), facilitating water oxidation for the protons and electrons delivered to the cathode, even under fuel starvation [5–11].

Recently, IrRu-based alloy catalyst as the RTA has been proposed owing to its activities for both HOR and OER. Total replacement of the Pt catalyst in the automotive PEMFC with an IrRu-based catalyst was suggested [5,6]. It has been reported that a third element, such as Co, Ce, Ti or Na can be introduced to the IrRu alloy to improve its OER activity [12–14]. However, these elements can readily dissolve under the PEMFC conditions, resulting in the reduction of electrocatalyst's HOR activity.

In this study, yttrium (Y) was selected as the third element for the synthesis of ternary alloy catalysts, because metallic Y was known to increase electrochemical activity in the PEMFC [15–17]. However, it has been known that Y³⁺ ions can hardly be reduced to metallic Y through conventional solution and/or gas reduction methods due to its low reduction potential (2.37 V vs. NHE). In this study, a novel approach such as an electron beam (EB) method was employed for the first time to reduce the metal ions to metallic species by using high energy electrons. The enhanced HOR and OER activities were achieved by incorporating Y into the IrRu₄ alloy, and its catalytic performance was compared with those of bimetallic IrRu₄ alloy catalyst prepared by the EB method, and ternary IrRuY catalysts prepared by the conventional

* Corresponding author.

E-mail address: chanho.pak@gist.ac.kr (C. Pak).<https://doi.org/10.1016/j.catcom.2019.105758>

Received 3 March 2019; Received in revised form 13 July 2019; Accepted 13 July 2019

Available online 13 July 2019

1566-7367/ © 2019 Elsevier B.V. All rights reserved.