



Contents lists available at ScienceDirect

Chemical Engineering Journal

journal homepage: www.elsevier.com/locate/cejTransparent SiN_x thin-film anode for thin-film batteries by reactive sputtering at room temperatureHyunSeok Lee^{a,b}, Kwang-Bum Kim^b, Ji-Won Choi^{a,c,*}^a Center for Electronic Materials, Korea Institute of Science and Technology (KIST), 5 Hwarang-ro 14 gil, Seongbuk-Gu, Seoul 02792, Republic of Korea^b Energy Conversion and Storage Materials Laboratory, Department of Material Science and Engineering, Yonsei University, 262 Seongsanno, Seodaemun-Gu, Seoul 120-749, Republic of Korea^c Division of Nano & Information Technology, KIST School, Korea University of Science and Technology (KUST), 5 Hwarang-ro 14 gil, Seongbuk-Gu, Seoul 02792, Republic of Korea

HIGHLIGHTS

- Exploration of transparent SiN_x thin films by reactive sputtering at RT.
- The capacity of SiN_{0.85} thin films is 1018 mAh/g.
- The capacity retention of SiN_{0.85} thin films is 95.4% after 100 cycles.
- Transmittance of SiN_{0.85} thin film exhibits 88%.

ARTICLE INFO

Keywords:

Lithium thin-film battery
SiN_x
Anode
Reactive sputtering

ABSTRACT

Silicon is extensively researched as a substitute for carbon as the anode material in Li-ion batteries. However, the cycle life of Si is very short because of its high volume expansion. Herein, we propose SiN_x deposited by radio frequency reactive sputtering at room temperature as an anode material. Sputtering presents the advantage of being easily applicable to fabricate all-solid-state thin film batteries. In this study, we use a Si target and explore the deposition conditions, and the compositions of the SiN_x thin film are confirmed by X-ray photoelectron spectroscopy analysis. The SiN_{0.85} thin film shows an initial discharge capacity of 1018 mAh g⁻¹ and capacity retention of 95.4% after 100 cycles, thus exhibiting stable performance. In addition, the transmittance of the SiN_{0.85} thin film on the glass substrate is 88% in the visible region (400–800 nm). Meanwhile, on the transparent conducting electrode, the transmittance before and after lithiation is 80% and 55% in the visible region, respectively. These results demonstrate that the SiN_{0.85} thin film, which can be used as the anode of transparent thin-film batteries, can be fabricated using reactive RF magnetron sputtering at room temperature.

1. Introduction

Over the last decade, there has been significant research on transparent devices, including transparent batteries [1–3]. For example, researchers have fabricated transparent batteries using grid-shaped electrodes [2–4]. The transparency of the battery can be increased by decreasing the grid-line width to be lower than the resolution of the human eye. However, because some components of a battery are not transparent, researchers have been attempting to develop a larger variety of transparent materials for batteries. Most studies that focused

on attaining a cathode with high transmittance have used olivine-based materials [5,6]. These materials have a wide band gap, which makes them excellent candidates for cathode materials in a transparent battery.

For anode materials, Li₄Ti₇O₁₂ (LTO) has been investigated because it has a wide band gap [7,8]. However, the transmittance of LTO-based batteries is known to change because the color of LTO changes during the discharge process. For example, Roeder et al. reported a battery with a high transmittance before charge–discharge, but its transmittance decreased owing to Li intercalation during discharge [7].

Abbreviations: RF, radio frequency; LTO, Li₄Ti₇O₁₂; XPS, X-ray photoelectron spectroscopy; UV–Vis, ultraviolet–visible; SEI, solid-electrolyte interphase; XRR, X-ray reflectivity

* Corresponding author at: Center for Electronic Materials, Korea Institute of Science and Technology (KIST), 5 Hwarang-ro 14 gil, Seongbuk-Gu, Seoul 02792, Republic of Korea.

E-mail address: jwchoi@kist.re.kr (J.-W. Choi).

<https://doi.org/10.1016/j.cej.2020.126086>

Received 5 March 2020; Received in revised form 19 June 2020; Accepted 24 June 2020

Available online 01 July 2020

1385-8947/ © 2020 Elsevier B.V. All rights reserved.