



## Full Length Article

Synthesis of rod-type  $\text{Co}_{2.4}\text{Mn}_{0.6}\text{O}_4$  via oxalate precipitation for water splitting catalysts

Kyoung Ryeol Park<sup>a,c</sup>, Jae Eun Jeon<sup>a,c</sup>, Kangmin Kim<sup>b</sup>, Nuri Oh<sup>a</sup>, Yong Ho Ko<sup>c</sup>, Jaewoong Lee<sup>c</sup>, Seung Hwan Lee<sup>d</sup>, Jeong Ho Ryu<sup>e</sup>, HyukSu Han<sup>f,\*</sup>, Sungwook Mhin<sup>c,\*</sup>

<sup>a</sup> Department of Materials Science and Engineering, Hanyang University, Seoul 04763, Republic of Korea

<sup>b</sup> Korea Institute of Industrial Technology, 137-41 Gwahakdanji-ro, Gangneung-si, Gangwon-do 25440, Republic of Korea

<sup>c</sup> Korea Institute of Industrial Technology, Gaetbeol-ro 156, Yeosu-gu, Incheon 21999, Republic of Korea

<sup>d</sup> School of Aerospace and Mechanical Engineering, Korea Aerospace University, Goyang-si, Gyeonggi-do, Republic of Korea

<sup>e</sup> Department of Materials Science and Engineering, Korea National University of Transportation, Chungju 380-702, Republic of Korea

<sup>f</sup> Department of Materials Science and Engineering, Hongik University, Sejong-ro 2639, Republic of Korea

## ARTICLE INFO

## Keywords:

Cobalt-manganese oxide

Electrocatalyst

Oxygen evolution reaction


Water splitting

## ABSTRACT

Development of a cost-effective oxygen evolution reaction (OER) catalyst for hydrogen production from water has attracted the attention of scientists due to its potential to solve current environmental and energy issues, such as  $\text{CO}_2$  emissions and depletion of fossil fuels. In this paper, we report a facile synthesis to develop cobalt-manganese-oxide ( $\text{Mn}_x\text{Co}_{3-x}\text{O}_4$ , CMO) nanorods via an oxalate precipitation method followed by annealing at different temperatures. Importantly, morphology and surface area of the CMO nanorods, which are directly related to the OER activity, can be precisely controlled by changing annealing temperatures. The CMO nanorods engineered by oxalate precipitation and subsequent heat treatment show promising OER catalytic performance, such as a small overpotential of 365 mV for generating a current density of  $10 \text{ mA cm}^{-2}$ , a low Tafel slope of  $50.6 \text{ mV dec}^{-1}$ , and excellent long-term stability in alkaline media. Electrochemical properties combined with materials characterization provide insightful information on the OER mechanism of the CMO nanorods.

## 1. Introduction

Hydrogen energy is a promising solution to the urgent problems associated with future energy and environment crises [1,2]. Hydrogen can be produced in a carbon-free way using electrolyzers via water splitting [3]. In a water-splitting electrolyzer, electrocatalysts for the oxygen ( $\text{O}_2$ ) evolution reaction (OER), which is an anodic catalytic reaction, play a crucial role in reducing the overpotential and, thus, enhancing the overall electrolysis efficiency [4]. Generally, a proposed possible mechanism for oxygen evolution reaction under alkaline condition has been popularly reported as follows [5]:



The OER is a thermodynamically sluggish reaction because multiple electrons and protons are involved in the anodic reaction [6,7]. Extensive research has focused on developing highly efficient OER electrocatalysts to lower the activation energy and accelerate the reaction kinetics [3,8].

Besides the high catalytic activity, long-term stability under alkaline conditions is a critical requirement for practical use of OER electrocatalysts in electrolyzers [9]. Highly active OER electrocatalysts, such as transition metal-based hydroxide [10], sulfides [11], nitrides [12,13] and phosphides [14], often exhibit poor long-term stability in alkaline solution under OER conditions. The poor long-term stability has been attributed to partial oxidation of electrocatalysts, which occurs spontaneously from a thermodynamic perspective under the OER conditions [15,16]. To eliminate the detrimental effects of partial oxidation of electrocatalysts on OER performance, oxide-based OER electrocatalysts are of particular interest as they are robust and highly efficient electrocatalysts [15–23].

Among numerous oxide-based OER catalysts, ruthenium oxide ( $\text{RuO}_2$ ) is regarded as the most active OER catalyst. However, its

\* Corresponding authors.

E-mail address: [hyeleci@kitech.re.kr](mailto:hyeleci@kitech.re.kr) (S. Mhin).

<https://doi.org/10.1016/j.apsusc.2020.145390>

Received 23 September 2019; Received in revised form 4 January 2020; Accepted 12 January 2020

Available online 21 January 2020

0169-4332/ © 2020 Elsevier B.V. All rights reserved.