



Contents lists available at ScienceDirect

## Chemical Engineering Journal

journal homepage: [www.elsevier.com/locate/cej](http://www.elsevier.com/locate/cej)

# Synthetic multiscale design of nanostructured Ni single atom catalyst for superior CO<sub>2</sub> electroreduction

Gyoung Hwa Jeong<sup>a,b,1</sup>, Ying Chuan Tan<sup>c,1</sup>, Jun Tae Song<sup>d</sup>, Gil-Yong Lee<sup>a,b</sup>, Ho Jin Lee<sup>a,b</sup>, Jaewoong Lim<sup>e</sup>, Hu Young Jeong<sup>f</sup>, Somi Won<sup>e</sup>, Jihun Oh<sup>b,\*</sup>, Sang Ouk Kim<sup>a,b,\*</sup>

<sup>a</sup> National Creative Research Initiative (CRI) Center for Multi-Dimensional Directed Nanoscale, KAIST, 291 Daehak-ro, Yuseong-gu, Daejeon 34141, Republic of Korea

<sup>b</sup> Department of Materials Science and Engineering, KAIST, 291 Daehak-ro, Yuseong-gu, Daejeon 34141, Republic of Korea

<sup>c</sup> Institute of Materials Research and Engineering (IMRE), A\*STAR, 2 Fusionopolis Way, #08-03 Innova 138634, Singapore

<sup>d</sup> Department of Applied Chemistry, Faculty of Engineering, Kyushu University, Fukuoka 819-0395, Japan

<sup>e</sup> Department of Chemistry, UNIST, 50 UNIST-gil, Ulsan 44919, Republic of Korea

<sup>f</sup> UNIST Central Research Facilities, UNIST, 50 UNIST-gil, Ulsan 44919, Republic of Korea

## ARTICLE INFO

## Keywords:

Single atom catalyst  
CO<sub>2</sub> reduction  
Carbon nanostructure  
Electrochemistry

## ABSTRACT

Rational design of nanoscale structures can greatly strengthen heterogeneous catalysis with the maximal utilization of active sites. Single atom catalysts (SACs) are recently emerging but a systematic design of nanostructured SAC has rarely been demonstrated yet. Here, distinct architectural structure-dependence of electrochemical CO<sub>2</sub> reduction (CO<sub>2</sub>RR) on Ni-based SACs is presented. Starting from Ni-imidazolate coordination polymers (Ni-Im) and their supported counterparts with a carbon nanotube (CNT) and a zeolite imidazolate framework (ZIF-8), the respective derivatives, i.e. Ni-SAC, Ni-SAC-CNT, and Ni-SAC-ZIF8, are obtained after pyrolysis. The presence of substrates ultimately results in large surface porous N-doped carbon nanostructures, which facilitate the diffusion of etchants to remove undesired Ni nanoparticles effectively. The dense Ni single atomic sites contained within the nanostructure are easily accessible to CO<sub>2</sub> reactants during CO<sub>2</sub>RR, thus promoting high utilization of active sites even at large current densities. Electro-conductive CNT substrates mediate fluent charge transfer and stimulates the intrinsic activity of catalytic sites. Consequently, operating at 400 mA cm<sup>-2</sup>, Ni-SAC-CNT attains a high faradaic efficiency of 99% toward CO at a low overpotential of 0.24 V, equivalent to a record cathodic energetic efficiency and turnover frequency of 83.4% and 439,000 h<sup>-1</sup>, respectively.

## 1. Introduction

Rapid advent of environmental issues arising from fossil fuel based current industrial system have triggered intensive research interest in the electrochemical CO<sub>2</sub> reduction reaction (CO<sub>2</sub>RR) [1–8]. Among several different electrochemical CO<sub>2</sub>RR products, CO is the basic chemical resource for methanol production, Fischer-Tropsch synthetic oils, and various carbonylation reactions [9]. The electrochemical conversion of CO<sub>2</sub> into CO is a typical two-electron process favored at the surface of Au, Ag, and Zn [10,11]. Nanostructured Au and Ag catalysts with relatively low energy barriers toward CO show excellent electrochemical reduction catalyst activity with CO Faradaic efficiency (FE) above 90% at overpotentials lower than 300 mV [12–14]. Nonetheless,

most prior studies have been unable to reach the economical viable activity of 200 mA cm<sup>-2</sup> particularly due to the limited CO<sub>2</sub> mass transport in a conventional H-type electrochemical cell. Recently, an increasing number of studies have employed flow electrolyzers based on gas-diffusion electrodes (GDEs) to achieve industrially relevant CO production rates [15–17]. Unfortunately, these results still rely on noble metals, which inevitably suffer from a high economic burden for scaling up. Alternatively, efforts have been spent on identifying cheaper alternatives, such as AgZn alloy and Cu/In hybrid [18,19], though they still suffer from high overpotentials and thus large power consumption for electrochemical CO<sub>2</sub>RR.

Lately, single atom catalysts (SACs) are emerging as a novel class of catalysts that can be rationally designed for numerous applications,

\* Corresponding authors.

E-mail addresses: [jihun.oh@kaist.ac.kr](mailto:jihun.oh@kaist.ac.kr) (J. Oh), [sangouk.kim@kaist.ac.kr](mailto:sangouk.kim@kaist.ac.kr) (S. Ouk Kim).

<sup>1</sup> G.H.J. and Y.C.T. contributed equally to this work.