



Contents lists available at ScienceDirect

Journal of Power Sources

journal homepage: www.elsevier.com/locate/jpowsour

Organometallic redox flow batteries using iron triethanolamine and cobalt triethanolamine complexes

Chanho Noh^a, Yongjin Chung^{b,*}, Yongchai Kwon^{a,c,*}

^a Graduate School of Energy and Environment, Seoul National University of Science and Technology, 232 Gongneung-ro, Nowon-gu, Seoul, 01811, Republic of Korea


^b Department of Chemical and Biological Engineering, Korea National University of Transportation, 50 Daehak-ro, Chungju, Chungbuk, 27469, Republic of Korea

^c Department of Chemical and Biomolecular Engineering, Seoul National University of Science and Technology, 232 Gongneung-ro, Nowon-gu, Seoul, 01811, Republic of Korea

HIGHLIGHTS

- Fe (TEA) and Co(TEA) are proposed as redox couple of ARFB.
- Optimal ratio of Co ion and TEA ligand is determined for optimal Co(TEA).
- 4 M NaOH is required for optimizing 1:2.5 Fe (TEA) and 1:1 Co(TEA).
- ARFB using this redox couple shows excellent CE (99%) and power density (35 mW cm^{-2}).
- Electrolyte cost per capacity of ARFB is 43% lower than VRFB.

GRAPHICAL ABSTRACT



ARTICLE INFO

Keywords:

Organometallic complex
Triethanolamine chelate
Cobalt and iron
Aqueous redox flow battery
Energy storage system

ABSTRACT

Organometallic complexes consisting of iron- and cobalt-triethanolamine ligand (Fe (TEA) and Co(TEA)) are proposed as redox couple of aqueous redox flow battery (ARFB). Fe (TEA) and Co(TEA) are dissolved in sodium hydroxide (NaOH) electrolyte, while their chemical stability and electrochemical reactivity are quantitatively characterized. As a result, the chemical stability of Co(TEA) is degraded for multiple charge/discharge cycle test due to the deformation of unchelated TEAs by the chemical reaction with hydroxyl ion (OH^-) and the catalytic effect of Co(TEA). To address the issue, the ratio of Co to TEA and the concentration of NaOH are manipulated. When the ratio is 1:1, the redox reactivity of Co(TEA) is improved because the amount of unchelated TEAs that is a reason for lowering its redox reactivity is minimized, while 4 M NaOH is proper to supply enough amount of OH^- , preserving its chemical structure and reducing mass transfer retardation. Regarding Fe (TEA), with 1:2.5 ratio of Fe to TEA in 4 M NaOH, the stability and performance of Fe (TEA) are best. Performance of ARFB using 1:2.5 Fe (TEA) and 1:1 Co(TEA) shows excellent results of high charge and energy efficiencies of 99% and 62% at 40 mA cm^{-2} , and high power density of 35 mW cm^{-2} .

* Corresponding author. Graduate School of Energy and Environment, Seoul National University of Science and Technology, 232 Gongneung-ro, Nowon-gu, Seoul, 01811, Republic of Korea.

** Corresponding author.

E-mail addresses: ychung@ut.ac.kr (Y. Chung), kwon@seoultech.ac.kr (Y. Kwon).

<https://doi.org/10.1016/j.jpowsour.2020.228333>

Received 25 December 2019; Received in revised form 22 April 2020; Accepted 8 May 2020

Available online 15 May 2020

0378-7753/© 2020 Elsevier B.V. All rights reserved.