



Contents lists available at ScienceDirect

Journal of Power Sources

journal homepage: www.elsevier.com/locate/jpowsour

n-Dodecane steam reforming over Ni catalysts supported on ZrO₂-KNbO₃

Taewook Kim^{a,*}, Yong Sik Chung^b, Jae Gi Sung^b, Hwan Kim^b, Seongmin Park^b,
Han Kyu Jung^b, Sungtae Park^{b,c}, Won Bae Kim^b, Jong Shik Chung^{b,c}

^a Green Materials & Processes R&D Group, Ulsan Division, Korea Institute of Industrial Technology (KITECH), 55, Jongga-Ro, Jung-Gu, Ulsan, 44413, Republic of Korea


^b Department of Chemical Engineering, Pohang University of Science and Technology (POSTECH), 77, Cheongam-Ro, Nam-Gu, Pohang, 37673, Republic of Korea

^c Institute for New and Renewable Energy, Pohang University of Science and Technology (POSTECH), 77, Cheongam-Ro, Nam-Gu, Pohang, 37673, Republic of Korea

HIGHLIGHTS

- High thermal stability and coke-resistance of the KNbO₃ material.
- Moderate and strong acidic sites required for high hydrocarbon cracking.
- Impregnated zirconia increases moderate and strong acidity.
- High and stable catalytic activity towards *n*-C₁₂H₂₆ SR over Ni/ZrO₂-KNbO₃.
- Good stability and coke-resistance of Ni/ZrO₂-KNbO₃ towards *n*-C₁₂H₂₆ SR.

GRAPHICAL ABSTRACT



ARTICLE INFO

Keywords:

Hydrogen production
Diesel
Hydrocarbon cracking
Coke resistance

ABSTRACT

Coke-resistant Ni catalyst supports are evaluated for steam reforming (SR) *n*-dodecane, the alkane used as a surrogate for diesel fuel in this study. Reactions are conducted at 800 °C for 5 h, with a molar steam-to-carbon ratio of 3.0 and a gas hourly space velocity of 20000 h⁻¹. Thermally stable, coke-resistant supports loaded with 15 wt% Ni are prepared using the following potassium oxides: K₂Ti₂O₅ (KTI), K₄Zr₅O₁₂ (KZR), KNbO₃ (KNB), KTaO₃ (KTA), and K₂WO₄ (KW). Ni/KZR and Ni/KW show the best catalytic performance in the SR reaction due to their moderate-to-strong acidities and lack of porosity, which are necessary features for hydrocarbon cracking. Unfortunately, these catalysts are poorly stable under the defined operating conditions. KNB is the most suitable support due to its excellent thermal stability and coke-resistance; however, it lacks acidity. The acidity of KNB is enhanced by impregnation with ZrO₂, which transforms it into an acidic oxide (ZR-KNB). ZR-KNB features high thermal stability and high coke-resistance during the SR of *n*-dodecane under the applied test conditions. The Ni/ZR-KNB catalyst delivers excellent SR performance with respect to both *n*-dodecane conversion and hydrogen selectivity.

1. Introduction

Steam reforming (SR) of diesel yields an effluent gas that provides an alternative economical source of H₂ [1–6]. For example, hydrogen

produced from the SR of diesel fuel can be used to provide the auxiliary or main power for fuel cells of road and marine vehicles. By applying SR to large-scale fuel cells, the produced hydrogen can also be used to supply stationary power to buildings and distributed power generation

* Corresponding author.

E-mail address: taewook@kitech.re.kr (T. Kim).

<https://doi.org/10.1016/j.jpowsour.2020.228834>

Received 18 June 2020; Received in revised form 19 August 2020; Accepted 21 August 2020

Available online 7 September 2020

0378-7753/© 2020 Elsevier B.V. All rights reserved.