



Contents lists available at ScienceDirect

Journal of Power Sources

journal homepage: [www.elsevier.com/locate/jpowsour](http://www.elsevier.com/locate/jpowsour)

# Efficient semi-transparent perovskite solar cells with a novel indium zinc tin oxide top electrode grown by linear facing target sputtering

Yong-Jin Noh<sup>a</sup>, Jae-Gyeong Kim<sup>b</sup>, Seok-Soon Kim<sup>c</sup>, Han-Ki Kim<sup>b, \*\*</sup>, Seok-In Na<sup>a, \*</sup>

<sup>a</sup> Professional Graduate School of Flexible and Printable Electronics, LANL-CBNU Engineering Institute Korea, Chonbuk National University, 664-14, Deokjin-dong, Deokjin-gu, Jeonju-si, Jeollabuk-do, 561-756, Republic of Korea

<sup>b</sup> School of Advanced Materials Science and Engineering, Sungkyunkwan University, 2066, Seobu-ro, Jangsan-gu, Suwon, Republic of Korea

<sup>c</sup> Department of Nano and Chemical Engineering, Kunsan National University, Kunsan, Jeollabuk-do, 753-701, Republic of Korea

## HIGHLIGHTS

- High-quality IZTO film is deposited by linear facing target sputtering.
- The effect of thickness of the IZTO film on PeSCs performance was investigated.
- The IZTO-based semi-transparent PeSCs showed high efficiency of 12.85%.

## ARTICLE INFO

### Keywords:

Perovskite solar cell  
Semi-transparent top electrode  
Indium zinc tin oxide  
Linear facing target sputtering  
Transparent electrode

## ABSTRACT

We propose that an indium zinc tin oxide electrode grown by linear facing target sputtering without additional thermal treatment can effectively act as an efficient semi-transparent top electrode for high-performance semi-transparent hybrid perovskite solar cells. The semi-transparent perovskite solar cells using an indium zinc tin oxide electrode as a novel top electrode achieves a power conversion efficiency of 12.85%, similar to that of an opaque electrode-based device of 13.48%. More importantly, by adjusting the perovskite thickness, a power conversion efficiency of 8.306% is obtained at an average visible transmittance of 33.9%, thus well supporting that the indium zinc tin oxide electrode can be considered to be an advanced and efficient semi-transparent top electrode for the fabrication of building integrated photovoltaics with high efficiency and good transparency.

## 1. Introduction

Organic-inorganic hybrid perovskites have emerged as the promising next-generation materials for the fabrication of highly efficient solar cells because of their excellent properties such as large absorption coefficients, large charge-carrier mobility, bipolar transport properties, and long carrier-recombination lifetime [1–9]. Recently, the power conversion efficiency (PCE) of perovskite solar cells (PeSCs) has achieved performance similar to that of the conventional photovoltaics based on silicon and thin-films [8]. Due to these perovskite's merits and value, the perovskite applications have been extended into the building-integrated photovoltaics (BIPVs), wearable electronics, and tandem solar cells [10–14]. In particular, the BIPV application has been highly attracted because the BIPV can be a major part of solar cell market and thus a transparent electrode essentially required for the top

electrode has been increasingly important as a core material for the semi-transparent PeSCs. However, such semi-transparent electrode researches have not been relatively much studied, compared with the opaque or bottom electrodes. Therefore, development of an efficient semi-transparent electrode for fabricating semi-transparent PeSCs is of great importance for the BIPV application.

Various transparent electrodes, such as thin metal films, metal nanowires, conductive polymers, oxide/metal/oxide electrodes, and transparent conductive oxides (TCOs), have been so far reported and employed as the top electrode for semi-transparent PeSCs [14–27]. Among the various transparent electrodes, the silver-based materials including silver nanowires and silver thin films with metal oxides have been considered to be promising electrode alternatives for fabricating efficient semi-transparent PeSCs because of their advantages such as the solution processability, high conductivity, and high transmittance

\* Corresponding author.

\*\* Corresponding author.

E-mail addresses: [hankikim@skku.edu](mailto:hankikim@skku.edu) (H.-K. Kim), [nsi12@jbnu.ac.kr](mailto:nsi12@jbnu.ac.kr) (S.-I. Na).

<https://doi.org/10.1016/j.jpowsour.2019.226894>

Received 7 December 2018; Received in revised form 3 July 2019; Accepted 15 July 2019

Available online 24 July 2019

0378-7753/© 2019 Elsevier B.V. All rights reserved.