



Contents lists available at ScienceDirect

Journal of Alloys and Compounds

journal homepage: <http://www.elsevier.com/locate/jalcom>

Synergistic effects of dual nano-type electrode of NiCo-nanowire/NiMn-nanosheet for high-energy supercapacitors

Damin Lee^a, Kyung Su Kim^a, Je Moon Yun^b, Seog-Young Yoon^a, Sanjay Mathur^c, Heon-Cheol Shin^{a,*}, Kwang Ho Kim^{a,b,**}^a School of Materials Science and Engineering, Pusan National University, San 30 Jangjeon-dong, Geumjeong-gu, Busan, 609-735, Republic of Korea^b Global Frontier R&D Center for Hybrid Interface Materials, Pusan National University, San 30 Jangjeon-dong, Geumjeong-gu, Busan, 609-735, Republic of Korea^c Department of Chemistry, Chair of Inorganic and Materials Chemistry, Cologne University, Cologne, 50939, Germany

ARTICLE INFO

Article history:

Received 4 December 2018

Received in revised form

21 February 2019

Accepted 23 February 2019

Available online 27 February 2019

Keywords:

Ni-Co-Mn

Nanostructure

Dual nano-type electrode

Hydrothermal method

Supercapacitors

ABSTRACT

A unique three-dimensional hybrid NiCo(CO₃)(OH)₂ nanowire/NiMn(CO₃)(OH)₂ nanosheet composite was fabricated using a facile hydrothermal method as a binder-free electrode directly grown on Ni foam for supercapacitors. We examined the synergistic effect by fabricating Ni-Co-Mn ternary electrodes that used Ni-Co with a large specific surface area and Mn with a very high theoretical capacity. The new hybrid electrode had good electrochemical characteristics, exhibiting remarkably high specific capacitances of 1673.3 and 453.0 F g⁻¹ at 3 and 15 A g⁻¹, respectively. Compared with other samples, the capacitance showed less reduction as the current density increased. This result indicates stable electrode properties with increasing voltage. The cycling stability of the hybrid NiCo(CO₃)(OH)₂/NiMn(CO₃)(OH)₂ composite was measured as 82.1% after 5000 cycles. Additionally, we fabricated an asymmetric supercapacitor employing the NiCo(CO₃)(OH)₂/NiMn(CO₃)(OH)₂ composite as the positive electrode and graphene as the negative electrode, which exhibited a high energy density of 27.2 W h kg⁻¹ at a power density of 702.7 W kg⁻¹ and a remarkable cycling stability, with 89.4% capacitance retention after 5000 cycles. Thus, for the first time, we investigated the dual nano-type structure of an NiCo(CO₃)(OH)₂ nanowire/NiMn(CO₃)(OH)₂ nanosheet electrode for supercapacitors and obtained satisfactory results.

© 2019 Elsevier B.V. All rights reserved.

1. Introduction

The 21st century is a period of change, characterized by the fourth industrial revolution and 5G. Therefore, all human life will be related to digital equipment that will require a small and high-capacity storage device. Additionally, high-energy storage devices are required owing to the emergence of renewable energy and hybrid industry [1,2]. Among the various power source devices, supercapacitors are attractive because they are eco-friendly and provide a high-capacity energy-storage system. Recently, two interesting types of supercapacitors have been studied, with different charge-storage mechanisms: electrical double-layer

capacitors using C-based active materials and faradaic capacitors using redox-based faradic reactions [3–5]. Among them, the faradaic capacitors we studied have the high specific energy of a capacitor as well as the redox characteristic of a battery [6]. Regarding the electrode material, good electrochemical characteristics are required, including an excellent electrical conductivity, a large specific surface area, and no reactivity with the electrolyte. To satisfy this requirement, cathode materials based on RuO₂ have been actively studied, which theoretically have a high capacity exceeding 1000 F g⁻¹ [7,8]. However, these materials are rare and expensive and require the use of electrolytes that are environmentally harmful, making commercialization difficult. Therefore, to replace them, studies on metal oxides having a relatively low cost and high capacity have been continuously performed. In this respect, transition metals have been widely used as cathode materials. Currently, transition-metal oxides/hydroxides such as NiO [9], MnO₂ [10], CuO [11], Co₃O₄ [12], and Ni(OH)₂ [13] and their binary arrays are widely studied as the positive electrode material for faradaic capacitors owing to their eco-friendly nature, low cost,

* Corresponding author.

** Corresponding author. School of Materials Science and Engineering, Pusan National University, San 30 Jangjeon-dong, Geumjeong-gu, Busan, 609-735, Republic of Korea.

E-mail addresses: hcshin@pusan.ac.kr (H.-C. Shin), kwhokim@pusan.ac.kr (K.H. Kim).