



Plasma-induced alloying as a green technology for synthesizing ternary nanoparticles with an early transition metal



Injoon Jang^{a,1}, Sehyun Lee^{a,1}, Eoyoon Lee^b, Dong-Wook Lee^a, Hee-Young Park^a, Baek B. Choi^c, Hyung Chul Ham^b, Sung Jong Yoo^{a,d,e,*}

^a Center for Hydrogen-Fuel Cell Research, Korea Institute of Science and Technology (KIST), 02792 Seoul, Republic of Korea

^b Department of Chemistry and Chemical Engineering, Inha University, 22212 Incheon, Republic of Korea

^c Energy and Environment Laboratory, Korea Electric Power Corp, Research Institute, Daejeon 34056, Republic of Korea

^d KHU-KIST Department of Converging Science and Technology, Kyung Hee University, Seoul 02447, Republic of Korea

^e Division of Energy & Environment Technology, KIST School, University of Science and Technology (UST), Seoul 02792, Republic of Korea

ARTICLE INFO

Article history:

Received 4 June 2021

Received in revised form 14 September 2021

Accepted 8 October 2021

Available online 29 October 2021

Keywords:

plasma-induced alloying

ternary nanoparticles

transition metal

Pt alloy

electrocatalyst

vanadium

ABSTRACT

The strategy of employing Pt alloys with other transition metals (TMs) is advantageous owing to the enhancement of the oxygen reduction reaction (ORR) activity and the reduction of Pt usage. The ternary alloy system with early TMs can overcome stability issues and even enhance the intrinsic activity of the catalysts owing to rearrangement of electronic structures between three metal elements. Herein, efficient catalysts with V—an early TM—were successfully obtained via a plasma-induced alloying strategy. The effect of V in the PtCoV/C catalyst, which exhibits the highest ORR activity among the synthesized Pt–TM–V (TM = Co, Ni, Cu) catalysts, was determined. The addition of V induces electron rearrangement in PtCoV, inhibiting the oxidation of Co and V and optimizing the oxygen-binding energy of Pt. Thus, incorporation of V into PtCoV nanoparticles enhances the electrochemical ORR activity and stability. The catalytic performance of PtCoV achieved 966 mV of half-wave potential, 3.05 A/mg_{PGM} of mass activity, and 8.58 mA/cm₂ of specific activity. This systemic strategy not only proposes a novel and facile approach for the synthesis of ternary alloy catalysts but also reveals the intricacies of the catalytic activity, allowing the application of ternary alloy electrocatalysts.

© 2021 Elsevier Ltd. All rights reserved.

Introduction

Hydrogen is regarded as the most promising energy source to meet the growing demand for eco-friendly energy, in which electricity is generated via a pollutant-free reaction. Proton exchange membrane fuel cells (PEMFCs), a type of hydrogen fuel cell, have

been successfully commercialized for applications in the automotive market owing to their high-power density and potential [1,2]. However, the oxygen reduction reaction (ORR) activity, which is indicative of PEMFC performance, remains insufficient. Furthermore, an improvement in the long-term stability, a major challenge facing PEMFCs, is needed [3–6].

Pt is widely used as a cathode electrocatalyst for oxygen reduction owing to its excellent intrinsic properties [7,8]. Although its use in commercial fuel cells is increasing, some of the issues encountered include limited natural Pt resources and high cost. To overcome these problems, the alloying of Pt with other metals has been explored to decrease the usage of Pt and improve its catalytic activity [9–11]. Alloying with TMs not only decreases the amount of Pt used but also increases its intrinsic catalytic activity [12–15]. If the electronegativity of the TM is lower than that of Pt, the electronic structure of Pt can be modified, which can transfer some electrons from TM to Pt, leading to a downshift of the d-band center [11,16–18]. According to the d-band theory, the binding between Pt

Abbreviations: ADT, Accelerated degradation test; CV, Cyclic voltammograms; DFT, Density functional theory; ECSA, Electrochemical surface area; EDS, Energy dispersive spectroscopy; FCC, Face-centered cubic; KIST, Korea Institute of Science and Technology; ORR, Oxygen reduction reaction; PEMFC, Proton exchange membrane fuel cells; PVD, Physical vapor deposition; STEM, Scanning transmission electron microscope; TEM, Transmission electron microscopy; TGA, Thermogravimetric analysis; TM, Transition metals; UST, University of Science and Technology; XANES, X-ray absorption near edge structure; XPS, X-ray photoelectron spectroscopy; XRD, X-ray diffraction

* Corresponding author at: Center for Hydrogen-Fuel Cell Research, Korea Institute of Science and Technology (KIST), 02792 Seoul, Republic of Korea.

E-mail address: ysj@kist.re.kr (S.J. Yoo).

¹ These authors contributed equally to this work.