



Contents lists available at ScienceDirect

Chemical Engineering Journal

journal homepage: www.elsevier.com/locate/cej


Optimizing the performance of meta-polybenzimidazole membranes in vanadium redox flow batteries by adding an alkaline pre-swelling step

Chanho Noh^{a,1}, Dmytro Serhiichuk^{b,c,d,1}, Najibah Malikah^{b,d}, Yongchai Kwon^{a,e,*}, Dirk Henkensmeier^{b,d,f,*}^a Graduate School of Energy and Environment, Seoul National University of Science and Technology, Nowon-gu, Seoul 01811, Republic of Korea^b Center for Hydrogen and Fuel Cell Research, Korea Institute of Science and Technology, Seongbuk-gu, Seoul 02792, Republic of Korea^c Chemical Technology Faculty, NTUU Igor Sykorsky Kyiv Polytechnic Institute, Kyiv 03056, Ukraine^d Division of Energy & Environment Technology, KIST School, University of Science and Technology, Seongbuk-gu, Seoul 02792, Republic of Korea^e Department of Chemical and Biomolecular Engineering, Seoul National University of Science and Technology, Nowon-gu, Seoul 01811, Republic of Korea^f Green School, Korea University, Seongbuk-gu, Seoul 02841, Republic of Korea

HIGHLIGHTS

- Alkaline pre-swelling increases conductivity of sulfuric acid doped PBI 3–10 times.
- Pre-swelling in 4 M NaOH reduces VO_2^+ permeability from 4×10^{-15} to $1.6 \times 10^{-15} \text{ m}^2 \text{ s}^{-1}$.
- Selectivity (conductivity/permeability) was increased 7 times.
- Energy efficiencies of 91.3% at 80 mA cm^{-2} and 95.4% at 40 mA cm^{-2} were achieved.

GRAPHICAL ABSTRACT



ARTICLE INFO

Keywords:

PBI
Alkaline pre-treatment
Conductivity
Vanadium permeability
VRFB

ABSTRACT

Polybenzimidazole (PBI) is a promising material for vanadium redox flow battery (VRFB) membranes. It shows a low permeability for vanadium ions, a conductivity in the range of 5 mS cm^{-1} in contact with 2 M sulfuric acid, and resists degradation by VO_2^+ . Recent literature showed that the conductivity of PBI can be increased to 18 mS cm^{-1} by pre-swelling the membrane with phosphoric acid (PA), and up to 590 mS cm^{-1} by casting a sulfonated *para*-PBI membrane from polyphosphoric acid before immersion in sulfuric acid. However, these membranes show an increased permeability towards VO_2^+ ions, and thus reduced coulomb efficiency in the VRFB. Here we investigate pre-swelling in 4 M alkaline solution. It increases the conductivity in 2 M sulfuric acid to 56 (potassium hydroxide) and 12 mS cm^{-1} (sodium hydroxide). In 3 M sulfuric acid, the NaOH swollen membrane (4N3S) shows 14 mS cm^{-1} , corresponding to an area resistance of $69 \text{ m}\Omega \text{ cm}^2$ for a $10 \mu\text{m}$ thick membrane, lower than that of Nafion 115 ($192 \text{ m}\Omega \text{ cm}^2$) and even Nafion 212 ($89 \text{ m}\Omega \text{ cm}^2$). The selectivity (conductivity/permeability) is $9 \times 10^{14} \text{ S s m}^{-3}$, 7, 30 and 1000 times higher than for standard PBI, PA and polyphosphoric acid pre-swollen membranes, respectively. A VRFB with a $5 \mu\text{m}$ thick 4N3S membrane showed energy efficiencies of 91.3% at 80 mA cm^{-2} and 95.4% at 40 mA cm^{-2} .

* Corresponding authors at: Graduate School of Energy and Environment, Seoul National University of Science and Technology, Nowon-gu, Seoul 01811, Republic of Korea (Y. Kwon). Center for Hydrogen and Fuel Cell Research, Korea Institute of Science and Technology, Seongbuk-gu, Seoul 02792, Republic of Korea (D. Henkensmeier).

E-mail addresses: kwonyc@seoultech.ac.kr (Y. Kwon), henkensmeier@kist.re.kr (D. Henkensmeier).

¹ Both authors contributed equally.