



High-performance Fe₅C₂@CMK-3 nanocatalyst for selective and high-yield production of gasoline-range hydrocarbons

Shin Wook Kang^a, Kyeounghak Kim^b, Dong Hyun Chun^a, Jung-Il Yang^a, Ho-Tae Lee^a, Heon Jung^a, Jung Tae Lim^c, Sanha Jang^a, Chul Sung Kim^c, Chan-Woo Lee^d, Sang Hoon Joo^{e,*}, Jeong Woo Han^{b,*}, Ji Chan Park^{a,*}

^a Clean Fuel Laboratory, Korea Institute of Energy Research, 152 Gajeong-Ro, Yuseong-Gu, Daejeon 34129, South Korea

^b Department of Chemical Engineering, University of Seoul, 163 Siripdae-Ro, Dongdaemun-Gu, Seoul 02504, South Korea

^c Department of Physics, Kookmin University, 77 Jeongneung-Ro, Seongbuk-Gu, Seoul 02707, South Korea

^d R&D Platform Center, Korea Institute of Energy Research, 152 Gajeong-Ro, Yuseong-Gu, Daejeon 34129, South Korea

^e School of Energy & Chemical Engineering, Ulsan National Institute of Science & Technology, Ulsan 44919, South Korea

ARTICLE INFO

Article history:

Received 26 December 2016

Revised 3 March 2017

Accepted 3 March 2017

Available online 27 March 2017

Keywords:

Selective Fischer-Tropsch synthesis

Amorphous carbon

Ordered mesoporous carbon

Density functional theory

Iron-carbide

ABSTRACT

Highly-loaded and well-dispersed Fe₅C₂ nanoparticles within ordered mesoporous carbon CMK-3 (Fe₅C₂@CMK-3) were prepared via a simple melt infiltration method. They were successfully applied to high-temperature Fischer-Tropsch synthesis, and showed high CO conversion (91%) and activity ($5.1 \times 10^{-4} \text{ mol}_{\text{CO}} \text{ g}_{\text{Fe}}^{-1} \text{ s}^{-1}$) as well as good selectivity (38 wt%) for gasoline-range hydrocarbons (C₅–C₁₂). The catalytic property of Fe₅C₂@CMK-3 was newly interpreted, based on theoretical data obtained by computational simulations.

© 2017 Elsevier Inc. All rights reserved.

1. Introduction

Fischer–Tropsch synthesis (FTS) has been a key technology that can produce a high quality petroleum substitute by coupling CO and H₂ gases derived from fossil resources such as coal, natural gas, and biomass [1,2]. Using this reaction for selective, high-yield production of synthetic fuel has been a significant challenge [3]. Typically, gasoline and lower-olefin products are effectively obtained by high-temperature FTS (HT-FTS) operated at temperatures of 300–350 °C using an iron-based catalyst [4]. Recently, some research has been reported for ways to provide more selective production of lower-olefins (C₂–C₄) [5–7]. However, profound studies and efficient new ways to produce gasoline-range hydrocarbons (C₅–C₁₂), without additional use of zeolite materials as a cracking catalyst, are rare [8].

Until now, iron-based nanocatalysts with carbon support (e.g. activated carbon, charcoal, carbon nanotubes, carbon nanofibers,

and graphene) have been used for HT-FTS due to their high specific surface areas and good thermal stability [9–14]. The recent use of ordered mesoporous carbon materials with high surface area, large pore volume and uniform mesopores enabled the uniform dispersion of tiny nanoparticles and efficient mass transfer [15–17].

Generally, alkali metals serving as a base promoter (e.g. Na, K, Cs) have been exploited in order to improve the catalytic activity of the catalysts [18–21]. However, when using a large amount of base promoter, the selectivity and productivity for gasoline-range hydrocarbons tend to decrease, because of the high basicity of the active surfaces formed by the promoters [22]. In the present work, we report Fe₅C₂ nanoparticles (4.6 nm) encapsulated within amorphous carbon CMK-3 (Fe₅C₂@CMK-3) as an efficient catalyst for selective production of gasoline-range hydrocarbons. The catalyst, which was prepared via melt infiltration of hydrated iron nitrate salt and a subsequent thermal activation process pre-optimized by screening various temperatures and gas conditions, showed higher activity and better selectivity for C₅–C₁₂ hydrocarbons than those in graphene. Furthermore, the catalytic property of Fe₅C₂@CMK-3 was newly interpreted, based on theoretical data obtained by computational simulations.

* Corresponding authors.

E-mail addresses: shjoo@unist.ac.kr (S.H. Joo), jwhan@uos.ac.kr (J.W. Han), jcpark@kier.re.kr (J.C. Park).