

Available online at www.sciencedirect.com

ScienceDirect

journal homepage: www.elsevier.com/locate/he

Highly dispersed and CO_{ad}-tolerant Pt_{shell}-Pd_{core} catalyst for ethanol oxidation reaction: Catalytic activity and long-term durability

Insoo Choi ^{a,*}, Dong-Hee Lim ^{b,1}, Dong Yun Shin ^b^a Division of Energy Engineering, Kangwon National University, 346 Jungang-ro, Samcheok, Gangwon-do 25913, Republic of Korea^b Department of Environmental Engineering, Chungbuk National University, 1 Chungdae-ro, Cheongju, Chungbuk 28644, Republic of Korea

ARTICLE INFO

Article history:

Received 5 December 2017

Received in revised form

28 February 2018

Accepted 4 March 2018

Available online 24 March 2018

Keywords:

Platinum

Palladium

Catalyst

Ethanol oxidation

CO_{ad}-tolerant

Stability

ABSTRACT

Highly dispersed Pt_{shell}-Pd_{core} catalyst is synthesized via an electroless deposition and a galvanic displacement. From electrochemical analysis, the catalyst is confirmed to be active toward an ethanol oxidation reaction for a prolonged time, and is more resistive against CO_{ad}-poisoning than a conventional Pt/C catalyst. The stable activity of Pt_{shell}-Pd_{core}/C is ascribed to the modified electronic property of Pt over-layer, which leads to a weak CO-adsorption strength with a high affinity for OH. The weakened binding property of surface Pt with CO_{ad} was experimentally confirmed by conducting a CO_{ad}-stripping and by measuring an electrochemically active surface area of the catalyst over multiple cycles. The CO_{ad} oxidation ability of as-synthesized catalyst is further proved by a computational method via density functional theory (DFT) calculation. The result presents a potential application of the catalyst for the efficient ethanol oxidation in a direct ethanol fuel cell.

© 2018 Hydrogen Energy Publications LLC. Published by Elsevier Ltd. All rights reserved.

Introduction

Much attention has been made to proton exchange membrane fuel cells (PEMFCs) due to its versatility as a power source for portable electronics and electric vehicles [1–5]. PEMFCs are classified into H₂-PEMFC (gaseous hydrogen) and direct alcohol-PEMFC (methanol, ethanol), based on which type of fuel is oxidized to generate electrons. Of those, direct alcohol-PEMFC is more advantageous than H₂-PEMFC, in terms of easy

storage, transportation, and high volumetric-/gravimetric energy density [6–8].

For the last two decades, direct methanol fuel cell (DMFC), one of the direct alcohol-PEMFCs, has been widely investigated as a future power source. However, methanol is toxic as well as volatile, and therefore it is not an ultimate replacement for H₂. As an alternative fuel, ethanol provides more advantages; safer, more energy density compared to methanol (8.01 kWh kg⁻¹ vs. 6.09 kWh kg⁻¹) [9,10]. Therefore,

* Corresponding author. Bldg. 4, Room #228, Division of Energy Engineering, Kangwon National University, 346 Jungang-ro, Samcheok 25913, Republic of Korea.

E-mail address: ischoi@kangwon.ac.kr (I. Choi).

¹ Equally Contributed.

<https://doi.org/10.1016/j.ijhydene.2018.03.022>

0360-3199/© 2018 Hydrogen Energy Publications LLC. Published by Elsevier Ltd. All rights reserved.