



Contents lists available at ScienceDirect

Electrochimica Acta

journal homepage: www.elsevier.com/locate/electacta

Understanding morphological degradation of Ag nanoparticle during electrochemical CO₂ reduction reaction by identical location observation



Hyewon Yun^{a,b}, Jiwon Kim^{a,c}, Woong Choi^a, Man Ho Han^{a,d}, Jong Hyeok Park^c,
Hyung-suk Oh^{a,e}, Da Hye Won^{a,e}, Kyungwon Kwak^{b,f}, Yun Jeong Hwang^{a,g,*}

^a Clean Energy Research Center, Korea Institute of Science and Technology (KIST), Hwarang-ro 14-gil 5, Seongbuk-gu, Seoul 02792, Republic of Korea

^b Department of Chemistry, College of Science, Korea University, Anamdong-5-Ga, Seoul 02841, Republic of Korea

^c Department of Chemical and Biomolecular Engineering and Yonsei-KIST Convergence Research Institute, Yonsei University, Seoul 03722, Republic of Korea

^d Department of Chemical and Biological Engineering, Korea University, Anamdong-5-Ga, Seoul 02841, Republic of Korea

^e Division of Energy and Environmental Technology, KIST School, Korea University of Science and Technology (UST), Seoul 02792, Republic of Korea

^f Center for Molecular Spectroscopy and Dynamics, Institute for Basic Science (IBS) and Department of Chemistry, Korea University, Seoul 02841, Korea

^g Department of Chemistry, Seoul National University, Seoul, 08826, Republic of Korea

ARTICLE INFO

Article history:

Received 18 December 2020

Accepted 9 January 2021

Available online 13 January 2021

Keywords:

CO₂ reduction

IL-TEM

Ag nanoparticle

Stability

Degradation

ABSTRACT

Electrocatalytic systems affording stable performance beyond the initial catalytic activity and selectivity have been actively discussed. Understanding the long-term stability of nanoparticle catalysts requires careful monitoring of the morphological changes. Herein, we demonstrate the relationship between the degradation of the catalytic activity and morphological changes in Ag nanoparticles during the electrochemical CO₂ reduction reaction (CO₂RR) for CO production by identical location transmission electron microscopy (IL-TEM) measurements. The synthesized Ag/C catalyst with 95.1% CO Faradaic efficiency (FE_{CO}) at -0.82 V vs. RHE showed a gradual decrease in the CO production current density and FE_{CO} , whereas the H₂ production increased during 12 h of CO₂RR. IL-TEM images showed that small Ag particles with dimensions of less than 5 nm were newly formed from the original particles within 1 h of reaction, accounting for 80% of the total number of particles, and slowly grew to around 10 nm with multiple domains when the CO₂RR was prolonged. These morphological changes were explained in connection with the CO current density gradient, where it was proposed that the formation of small particles causes a sharp decrease in the CO production during the first hour, and subsequent growth of the Ag nanoparticles did not restore the CO₂RR activity of the particles. It was confirmed that degradation of the nanoparticles was more severe at a higher cathodic potential, and occurred during the CO₂RR, but not in the hydrogen evolution reaction (HER) in N₂-purged KHCO₃ electrolyte. In this study, we introduce analytical methods for observing morphological changes of nanoparticles in the identical location during CO₂RR electrolysis.

© 2021 Published by Elsevier Ltd.

1. Introduction

The electrochemical CO₂ reduction reaction (CO₂RR) has been intensively studied as a promising CO₂ utilization technique that can be combined with renewable energy sources. It targets the conversion of CO₂, a greenhouse gas, to value-added useful chemicals such as CO, formate, and C₂H₄ [1–4]. CO is a particularly promising target chemical as it can be produced with high selec-

tivity and energy conversion efficiency via the CO₂RR due to the recent progress in the development of electrocatalysts, membranes, and electrolyzers [5–7]. A mixture of CO and H₂ is industrially used to produce hydrocarbons via the Fischer-Tropsch process [8].

High selectivity for CO with a Faradaic efficiency of over 95% has been achieved with various catalysts such as Au [7], Ag [9], Zn [10], Cu-based bimetallic catalysts [11], and single-atom catalysts [12], with the assistance of nanostructuring. Ag has been used as a model catalyst for understanding the fundamentals of CO production and device applications [13–15]. Defects or edge sites of Ag-based nanocatalysts show high intrinsic activity for selective CO production, but their stability has yet not been systematically

* Corresponding authors.

E-mail addresses: kkwak@korea.ac.kr (K. Kwak), yjhwang@kist.re.kr, yunjeong.hwang@gmail.com (Y.J. Hwang).