

# Mill Test Certificate

## 검 사 증 명 서

Order No. : 26-AB-0412  
계약번호

Supplier :  
주문자

Customer :  
고객사

Date of Production : 2026-09-28  
제조일자

PO No. :  
주문번호

Commodity : HOT ROLLED STEEL PLATE  
품명

Spec & Type : EN 10025-2 S355J2+N  
규격

Surface Condition : AS ROLLED  
표면상태

| Size<br>/치수             | Product No.<br>/제품번호 | Quantity<br>/수량 | Weight<br>/중량(kg) | Heat No.<br>/제강번호 | Country of Melt & Pour | Position | Tensile Test<br>/인장시험 |             |           | Impact Test<br>/충격시험 -20℃ | Division | Chemical Composition<br>/화합성분 |           |           |          |          |           |           |           |           |          |            |
|-------------------------|----------------------|-----------------|-------------------|-------------------|------------------------|----------|-----------------------|-------------|-----------|---------------------------|----------|-------------------------------|-----------|-----------|----------|----------|-----------|-----------|-----------|-----------|----------|------------|
|                         |                      |                 |                   |                   |                        |          | YP<br>(MPa)           | TS<br>(MPa) | EL<br>(%) |                           |          | C<br>(%)                      | Si<br>(%) | Mn<br>(%) | P<br>(%) | S<br>(%) | Cu<br>(%) | Cr<br>(%) | Ni<br>(%) | Mo<br>(%) | N<br>(%) | Ceq<br>(%) |
| MIN                     | SPEC. 하한             |                 |                   |                   |                        |          | 345                   | 470         | 22        | 27                        |          |                               |           |           |          |          |           |           |           |           |          |            |
| MAX                     | SPEC. 상한             |                 |                   |                   |                        |          |                       | 630         |           |                           |          | 0.200                         | 0.55      | 1.60      | 0.0250   | 0.0250   | 0.55      |           |           |           | 0.0120   | 0.45       |
| 20.0x2,438x12,000       | PL26A0412            | 1               | 4,594             | SH60218           | KOR                    | T        | 382                   | 528         | 27        | 96                        | L        | 0.162                         | 0.21      | 1.42      | 0.0142   | 0.0041   | 0.02      | 0.03      | 0.02      | 0.004     | 0.0046   | 0.41       |
| 20.0x2,438x12,000       | PL26A0413            | 1               | 4,594             | SH60218           | KOR                    | B        | 376                   | 521         | 28        | 88                        | L        | 0.162                         | 0.21      | 1.42      | 0.0142   | 0.0041   | 0.02      | 0.03      | 0.02      | 0.004     | 0.0046   | 0.41       |
| 20.0x2,438x12,000       | PL26A0414            | 1               | 4,594             | SH60219           | KOR                    | T        | 389                   | 535         | 26        | 102                       | L        | 0.158                         | 0.24      | 1.38      | 0.0128   | 0.0036   | 0.03      | 0.04      | 0.02      | 0.005     | 0.0051   | 0.40       |
| 20.0x2,438x12,000       | PL26A0415            | 1               | 4,594             | SH60219           | KOR                    | B        | 371                   | 517         | 29        | 91                        | L        | 0.158                         | 0.24      | 1.38      | 0.0128   | 0.0036   | 0.03      | 0.04      | 0.02      | 0.005     | 0.0051   | 0.40       |
| *** Sub Total (010) *** |                      | 4               | 18,376(kg)        |                   |                        |          |                       |             |           |                           |          |                               |           |           |          |          |           |           |           |           |          |            |
| *** Grand Total ***     |                      | 4               | 18,376(kg)        |                   |                        |          |                       |             |           |                           |          |                               |           |           |          |          |           |           |           |           |          |            |

=== Last Item ===

Residual Elements (Product Analysis, %) /잔류원소

|       |       |       |       |       |       |
|-------|-------|-------|-------|-------|-------|
| Co    | Sb    | W     | Zn    | Zr    | Ce    |
| 0.007 | 0.003 | 0.004 | 0.005 | 0.002 | 0.001 |

\* Position - T : Top, M : Middle, B : Bottom

\* Tensile Test. Direction : Transversal, Gauge Length : 200 mm(Rectangular)  
Test Method : ISO 6892-1:2019 Method B, YP Method : Upper Yield Point (ReH)

\* Impact Test - ISO 148-1, Charpy V-notch 10x10 mm, -20 ℃, Average of 3

\* Division - L : Ladle Analysis, Chemical Analysis : ASTM E415-21 (Spark OES)  
Ceq = C + Mn/6 + (Cr+Mo+V)/5 + (Ni+Cu)/15

We certify that the material has been made in accordance with the order and is in compliance.  
This material has been fully killed and made by basic oxygen process.  
Test Certificate is issued according to ISO 10474/EN 10204 3.1.  
We, STRUCTA STEEL WORKS, hereby certify that the products specified in the present MTC  
have been fully processed in South Korea.  
Legal sanction can be imposed on forging. Improper use of product can cause safety issues.

Surveyor To:

e-Certificate : <https://docs.structasteel.example.kr/mtc/MTC-STRUCTA-261007-01.pdf>