Provecta[™] Aliphatic

FTA3290+5.5

Provecta[™] Aliphatic technical film has non-yellowing characteristic which can remain its great physical properties under UV light exposure. It is great for automotive stone chip protection film.

Features:

- Ether base
- · Aliphatic / Non-yellowing
- Optical grade transparency

Applications:

- Automotive stone chip protection film
- Medical devices

Hardness	Specific Gravity	Tensile Strength	Tear Strength	300% Modulus	Elongation	Melting Point	UV Discoloration
(Shore A/D) D2240	D792	(kg/cm²) D412	(kg/cm) D624 (Die C)	(kg/cm²) D412	(%) D412	(°C)	G154
92A	1.09	warp: 681 weft: 610	warp: 77 weft: 68	warp: 419 weft: 415	warp: 370 weft: 351	92	4

The data and information provided are for reference only and are not guaranteed.

