Provecta™ Hot Melt

FS3233X1+DZ03P

Provecta[™] Hot Melt technical films are solvent-free, high elastic, and perfect for microfiber fabrics, PU leather, and genuine leather, among other materials.

Features:

- Heat pressing with microfiber, PU leather, non-woven fabric
- Low processing temperature
- Eco-friendly

Hardness	Specific Gravity	Tensile Strength	Tear Strength	300% Modulus	Elongation	Melting Point
(Shore A/D) D2240	D792	(kg/cm²) D412	(kg/cm) D624 (Die C)	(kg/cm²) D412	(%) D412	(°C)
45D	1.16	warp: 445 weft: 435	warp: 88 weft: 91	warp: 70 weft: 58	warp: 892 weft: 902	90

The data and information provided are for reference only and are not guaranteed.

