Provecta™ Aromatic

FT1H29

FT1H29 tubular film has excellent hydrolysis resistance with different thicknesses and diameters such as 0.05mm thickness and 50mm diameter (78.5mm width), etc. DingZing tubular film has ester and ether types with different choices of hardness.

Applications:

- Food grade conveying pipe
- Fire hose pipe
- Inflatable camping tent frame
- Medical products (air mattress
 & fluid bag)



Color	Thickness	Hardness	Specific Gravity	Tensile Strength	Tear Strength	300% Modulus	Elongation	Melting Point
	mm	(Shore A/D) D2240	D792	(kg/cm²) D412	(kg/cm) D624(Die C)	(kg/cm²) D412	(%) D412	(°C)
102H	0.25X160 (Flat width)	85A	1.12	warp:533 weft:496	warp:80 weft:86	warp:131 weft:124	warp:517 weft:527	149

The data and information provided are for reference only and are not guaranteed.