








# Provecta™ Tape

## DINDEX 091X3.3

Provecta™ Tape has rubber-like characteristic and is often applied on elastic textiles for activewear.

Hardness	Specific Gravity	Tensile Strength	Tear Strength	300% Modulus	Elongation	Melting Point
(Shore A/D) D2240	D792	(kg/cm <sup>2</sup> ) D412	(kg/cm) D624(Die C)	(kg/cm <sup>2</sup> ) D412	(%) D412	(°C)
77A	1.13	weft: 335 warp: 324	weft: 64 warp: 67	weft: 77 warp: 66	weft: 677 warp: 764	135

DINDEX 091X3.3			
Thickness(mm)	Width(mm)	Packing(Meter/kg)	
0.12	3	2400	   Swimwear    Leotard    Brassieres and panties Baby clothes   Sports wear   T-shirts   Hats   Bra straps    
	4	1800	
	5	1500	
	6	1200	
	8	900	
	10	750	
	12	600	
0.22	10	420	
	12	350	
0.3	3	960	
	4	720	
	5	600	
	6	480	
	8	360	
	10	300	
	12	240	

The data and information provided are for reference only and are not guaranteed.

### About DingZing

DingZing is a leader in the development and production of high-performance polymers. We specialize in thermoplastic polyurethane and polyurethane products and solutions, with a focus on advanced technical films.

### DingZing Corporation

No.8-1, Pei-Lin Road, Hsiao-Kang District, Kaohsiung 812, Taiwan  
 T +886-7-807-0166  
 F +886-7-807-1616  
 www.dingzing.com

# DingZing

Science. Innovation. Collaboration.