

301 Roycefield Road
908-526-4445 Hillsborough, NJ 08844
Fax 908-526-9487

DATA SHEET

Sheet 1 of 1

	In Proc	1st Article
Quote		
Incoming		Other

Part #	A269-30400-224	Heat	Quantity	31200	Supplier	PO #	96121
Operation		Job #			Customer	Customer PO#	
Sampling Plan	n = 11	c = 0	Lot Disposition	Approved		By:	Date 04/14/26

Find # >	QD	ID
Max. Spec.	.183	.127
MEAN	.182	.126
Min. Spec.	.181	.125
1	.182	PIN
2	.182	Good
3	.182	.125
4	.182	.126
5	.182	is
6	.182	going
7	.182	
8	.182	.127
9	.182	is
10	.182	not
11	.182	going

Notes:

G & J Steel & Tubing Inc.
A 05
QA

ORIGINAL

INSPECTION CERTIFICATE

NO: KW 26-04-07-01

CUSTOMER: G&J Steel & Tubing Inc.

PRODUCT: Stainless Steel Tube

DUAL SPECIFICATION : A269-30400-224

Acc. to EN 10204/3.1B

KYOWOO CORPORATION

#1905-102 dong, Guseong-ro 15, Giheung-gu,

Yongin-si, Gyeonggi-do 16917, Korea

Tel : 82-31-263-7109

ASTM A269/ AMS 5563, TP304

DATE: April 7, 2026

NO	LOT NO.	TYPE	SIZE	Q'TY (FEET)	DIMENSION(INCHES)				COUNTRY OF MELT & POUR
					SPEC.	O.D	I.D	T	
					MAX	.1830"	.1270"	-	10ft 5"
					MIN	.1810"	.1250"	-	10ft 5"
					MAX	.1823"	.1256"	-	10ft 5"
					MIN	.1821"	.1256"	-	10ft 5"
1	GS040701	SS304 TUBE	OD 0.182" x ID 0.126" x 10 ft 5" L.	31,250 (640 kgs)					Republic of Korea

NO.	Product No. & Heat No. of Raw Steel	CHEMICAL COMPOSITION (%)										HARD NESS (HV)	T.S (MPa) Min 827	E.L. (%)	Remarks
		ELEMENT	C	Si	Mn	P	S	Ni	Cr	Mo					
		MAX	0.0800	0.750	2.0000	0.0400	0.0300	11.00	20.00	-					
		MIN						8.00	18.00	-					
1	QGP2047		0.0556	0.417	1.034	0.0329	0.0040	8.080	18.194	-		335	1,072	-	-
	SE49992														

IT IS HEREBY CERTIFIED THAT THE ABOVE RESULTS ARE TRUE AND CORRECT IN EVERY DETAILS.

CHIEF OF QUALITY ASSURANCE SECTION

G & J Steel & Tubing Inc.
A 05
QA

KYOWOO CORPORATION

#1905-102 Dong, Guseong-ro, Giheung-gu,
Yongin-si, Gyeonggi-do 16917, Korea

Tel: 82-31-263-7109 Fax: 82-31-263-0412

E-mail: kyowoo@kyowoo.or.kr