

Perspectives on the merits of cubic silver antimony sulfide-selenide thin films for solar cells

This manuscript ([permalink](#)) was automatically generated from [jesuscapistran/mymanuscript@9317895](#) on January 7, 2022.

Authors

- **Jesús Capistrán-Martínez**

 [0000-0001-8555-5440](#) ·  [jesuscapistran](#) ·  [capis](#)

Renewable Energy Institute - UNAM · Funded by Grant XXXXXXXX

- **Roman Romano Trujillo**

 [0000-0001-8824-025X](#)

Centro de Investigaciones en Dispositivos Semiconductores - BUAP · Funded by Grant XXXXXXXX

Abstract

Symposium: C7 Photovoltaics, Solar Energy Materials and, Technologies

Modality: Virtual Poster

URL: <https://jesuscapistran.com/courses/silver-antimony-sulfide-selenide/>

- The silver antimony sulfide-selenide – cubic- $AgSb(S, Se)_2$ is a potential p-type semiconductor for application in thin-film solar cells. In this work, we present perspectives of $AgSb(S, Se)_2$ to develop high-efficiency solar cells using this cubic metal chalcogenide semiconductor.
- Material characterization of the $AgSbS_{1.3}Se_{0.7}$ solid solution confirms p-type conductivity with a bandgap of 1.48 eV and photoconductivity (σ) of $10^5 \Omega^{-1}cm^{-1}$.
- The merit of incorporating silver atoms into the novel antimony chalcogenides (Sb_2S_3 , Sb_2Se_3) comes from the transformation of orthorhombic structure into an FCC lattice, similar to that in rock salt structure.
- The absorption coefficient of $\alpha > 10^5 cm^{-1}$ in the visible region of solar radiation in $AgSbS_{1.3}Se_{0.7}$ allows a maximum photo-generated current density of $29 mA/cm^2$ for a $1 \mu m$ thick film under standard air-mass 1.5 global (1000 W/m²) solar radiation.
- The thin film solar cells of CdS/ $AgSbS_{1.3}Se_{0.7}$ heterojunction presents a fill factor of 0.64, open-circuit voltage of 537 mV, but a low short circuit current density of $2 mA/cm^2$.
- At this stage, chemical deposition has served for prototyping the solar cells. Improvements are expected using industrial chalcogenide growth techniques, which would enhance their carrier collection.

References
