## Perspectives on the merits of cubic silver antimony sulfide-selenide thin films for solar cells

This manuscript (<u>permalink</u>) was automatically generated from <u>jesuscapistran/mymanuscript@7836718</u> on January 7, 2022.

## **Authors**

- Jesús Capistrán-Martínez
  - © 0000-0001-8555-5440 · © jesuscapistran · **S** capis Renewable Energy Institute - UNAM · Funded by Grant XXXXXXXX
- Roman Romano Trujillo
  - © 0000-0001-8824-025X

Centro de Investigaciones en Dispositivos Semiconductores - BUAP · Funded by Grant XXXXXXXX

## **Abstract**

Symposium: C7 Photovoltaics, Solar Energy Materials and, Technologies

Congress mode: Virtual Poster

**URL:** https://jesuscapistran.com/courses/silver-antimony-sulfide-selenide/

• The silver antimony sulfide-selenide – cubic- $AgSb(S,Se)_2$  is a potential p-type semiconductor for application in thin-film solar cells. In this work, we present perspectives of  $AgSb(S,Se)_2$  to develop high-efficiency solar cells using this cubic metal chalcogenide semiconductor.

- Material characterization of the  $AgSbS_{1.3}Se_{0.7}$  solid solution confirms p-type conductivity with a bandgap of 1.48 eV and photoconductivity ( $\sigma$ ) of  $10^5~\Omega^{-1}{\rm cm}^{-1}$ .
- The merit of incorporating silver atoms into the novel antimony chalcogenides ( $Sb_2S_3$ ,  $Sb_2Se_3$ ) comes from the transformation of orthorhombic structure into an FCC lattice, similar to that in rock salt structure.
- The absorption coefficient of  $\alpha>10^5{
  m cm}^{-1}$  in the visible region of solar radiation in  $AgSbS_{1.3}Se_{0.7}$  allows a maximum photo-generated current density of 29 mA/cm² for a 1  $\mu{
  m m}$  thick film under standard air-mass 1.5 global (1000 W/m²) solar radiation.
- The thin film solar cells of CdS/ $AgSbS_{1.3}Se_{0.7}$  heterojunction presents a fill factor of 0.64, open-circuit voltage of 537 mV, but a low short circuit current density of 2 mA/cm<sup>2</sup>.
- At this stage, chemical deposition has served for prototyping the solar cells. Improvements are
  expected using industrial chalcogenide growth techniques, which would enhance their carrier
  collection.

## References