Larkfield Glaze Co. / 라크필드코리아

Mid-Fire Glaze Data Sheets — Cone 5/6

Brushing glazes, 16 oz (473 ml) jars — 한글 요약 포함

문서번호 LF-DS-0526-KR
2026 Edition (KR distributor copy, 2026.01)
Distributor: 라크필드코리아, 서울 성동구 | Tel 02-498-2716

Contents / 목차

1. About This Guide 3

2. Food-Safety Terminology 5

3. 한국 사용자 안내 (라크필드코리아) 6

4. Application Basics 7

LF-101 Clear Gloss 10

LF-112 Satin White 12

LF-125 Oatmeal Speckle 14

LF-138 Celadon Mist 16

LF-142 Floating Blue 18

LF-156 Iron Red 20

LF-163 Shino Sand 22

LF-177 Sea Glass Green 24

LF-184 Charcoal Matte 26

LF-190 Midnight Crawl 28

LF-205 Lava Rose 30

LF-219 Copper Patina 32

LF-226 Honey Flux 34

LF-233 Speckled Cream 36

LF-248 Night Sky 38

5. Safety Data Sheet Summary 40

6. 국내 문의 및 주문 안내 42

1. About This Guide

Scope

This book collects the technical data sheets for the Larkfield Glaze Co. mid-fire brushing line as supplied to the Korean market. Each glaze in the line is formulated, tested and labeled for firing to Cone 5 or Cone 6 in an electric kiln in an oxidation atmosphere. The data sheets describe what the glaze is designed to do, how to apply it, what results to expect, and how the glaze is classified for food contact.

All glazes in this line are supplied ready to use in 16 fl oz (473 ml) wide-mouth jars. The suspension contains a brushing medium, so the glaze levels itself as it dries and can be applied in even coats with a soft fan or mop brush. The same products can be dipped or poured once thinned with water, but the coat counts and food-safety classifications in this book refer to brushing unless stated otherwise.

Who this guide is for

- Studio potters and ceramic instructors working with commercial stoneware or porcelain clay bodies
- Community studios and schools that fire electric kilns with a programmable controller
- Retailers and distributors who answer customer questions about color, firing range and food use

What is new in the 2026 Edition

- Five new colors: LF-205 Lava Rose, LF-219 Copper Patina, LF-226 Honey Flux, LF-233 Speckled Cream and LF-248 Night Sky
- LF-184 Charcoal Matte reclassified from Dinnerware Safe to Not Suitable for Dinnerware due to Surface Durability after extended abrasion testing (see the LF-184 data sheet)
- Layering chart expanded to twelve tested combinations
- Korean summary box added to every product page for the KR distributor copy

Our testing basis

Every color is test fired in our own lab on a white stoneware body and a buff-brown stoneware body, in electric kilns with witness cones on the shelf. Leach testing is carried out by an independent laboratory on production batches; abrasion, thermal shock and dishwasher cycling are performed in-house. A product's classification is reviewed every time a raw material supplier or the formula changes, and at least once per year.

> Note: All results in this book apply only when the glaze is applied as instructed (recommended number of coats on properly bisqued ware) and fired to the shelf cone listed on the data sheet. Heavier application, a lower or higher firing, a different clay body, or a different cooling rate can change the color, the surface and the food-safety performance of any glaze.

How to read the data sheets

Each product occupies two pages. The first page gives the specification table, the food-contact status box and a description of the glaze. The grey box at the bottom of the first page is a Korean summary prepared by our Korean distributor. The second page covers firing notes, tips, troubleshooting and frequently asked questions.

Field	What it means
Code	Larkfield product number. The same code is printed on the jar label and the lid.
Cone	The target shelf cone. "5/6" means the glaze is tested at both Cone 5 and Cone 6.
Surface	Gloss, satin or matte as measured on the white test body at Cone 6.
Opacity	Transparent, translucent, semi-opaque or opaque at the recommended coat count.
Movement / flow	Low, moderate, high or very high. High and very high glazes require a catcher.
Application	Brushing is the standard method. Dip/pour notes are given where relevant.
Recommended coats	Number of brushed coats on bisque, allowing each coat to dry to the touch.
Jar size	16 fl oz (473 ml). Approximately 1.6–1.8 ft² (0.15–0.17 m²) per jar at 3 coats.
Lot format	YYMM + plant line letter + three-digit batch, printed on the lid (2601B-047).
Color on white / brown body	Fired color on our white stoneware and on a buff-brown stoneware with about 2% iron.

Status box

The status box shows four answers: Food Safe, Dinnerware Safe, Microwave and Dishwasher. "Yes" means the glaze met our test criteria for that use when applied and fired as stated. "No" means it did not, or that it was not designed for that use. Read the definitions in the next chapter before relying on any status.

Cone and temperature

Pyrometric cones measure heat work, which combines temperature and time. At a final heating rate of 108 °F (60 °C) per hour, Cone 5 bends at approximately 2167 °F (1186 °C) and Cone 6 at approximately 2232 °F (1222 °C). A slower final rate brings the cone down at a lower temperature; a faster rate needs a higher temperature. Always confirm a new kiln program with witness cones on the shelf rather than relying on the controller reading alone.

Clay bodies

Our test bodies are mid-fire stoneware with absorption below 2% at Cone 6. A glaze can only be as watertight as the body underneath it. On open, porous bodies, or on bodies fired above or below their maturing range, crazing, shivering and seepage can occur even with a Dinnerware Safe glaze.

2. Food-Safety Terminology

The terms below are used on every data sheet. They describe how the glaze performed in our test program. They are not a guarantee for every piece of finished ware, because application, firing and clay body are outside our control.

Food Safe

The fired glaze, applied and fired as instructed, released lead, cadmium and other regulated metals below the applicable limits in standard acid-leach testing. A Food Safe glaze may be used on surfaces that touch food and drink. However, the surface may show gradual change with heavy use, such as slight color shift from acidic foods, dulling, or marking from cutlery. For daily-use dinnerware we recommend hand washing glazes that carry only the Food Safe status.

Dinnerware Safe

The glaze meets the Food Safe criteria and, in addition, passed our durability program: repeated dishwasher cycles, abrasion by stainless steel cutlery, thermal shock and microwave exposure, without measurable change in leach results or obvious change in appearance. Dinnerware Safe is our highest food-contact rating and is suitable for plates, bowls, mugs and serving ware in everyday use.

Not Suitable for Dinnerware due to Surface Durability

The glaze passed leach testing when new, but its surface does not hold up to daily use. Cutlery leaves grey marks, scouring pads leave scratches, or the surface becomes rough enough to trap food residue. We do not recommend this glaze on any surface that is cut on, stirred in, or scrubbed. It may be used on the outside of mugs and bowls, on rims below the lip line, and for decorative ware.

Decorative Use Only (Not Food Safe)

The glaze is designed for texture or visual effect and is not intended for food contact. Typical reasons are a crawled, blistered or deliberately rough surface, high colorant loading, or metal release above food-contact limits. Do not use these glazes on the inside of any functional piece or on the lip area of drinking ware. Where a product carries a specific reason, such as copper leaching, it is printed in the status line of that data sheet.

Microwave and dishwasher

"Microwave = Yes" means test pieces did not spark, did not overheat locally and did not change appearance after repeated microwave cycles. Glazes with high metallic colorant content, and any piece decorated with gold, platinum or luster overglaze, must not be used in a microwave. "Dishwasher = Yes" is given only to Dinnerware Safe glazes.

> Warning: Food-contact performance depends on correct application and firing. Applying more coats than recommended, underfiring, overfiring until the glaze runs thin, or mixing glazes in layers not tested by us can change the result. If finished ware will be sold or used to serve food, have the finished pieces tested by an accredited laboratory.

3. 한국 사용자 안내 (라크필드코리아)

본 자료는 Larkfield Glaze Co.의 2026년판 영문 데이터시트에 국내 대리점 라크필드코리아가 한글 요약과 국내 사용 안내를 덧붙인 배포본입니다. 제품 사양과 식품 접촉 등급은 원문(영문)이 기준이며, 한글 요약과 본문이 다르게 읽힐 경우 영문 본문을 따르십시오.

소성 온도: Cone 5/6과 국내 공방 재벌 온도

Cone 5/6은 마지막 승온 속도 시간당 60°C 기준 약 1186~1222°C에 해당합니다. 국내 공방에서 흔히 사용하는 재벌 온도 1230~1250°C(SK7 부근)는 이 범위보다 높습니다. 라크필드 유약을 1240°C 산화소성 가마에 함께 넣으면 다음 현상이 생길 수 있습니다.

- 유약이 묽어져 흘러내리고, 굽과 가마 선반에 붙음 (특히 Movement가 High·Very High인 제품)
- 발색이 연해지거나 반점(스페클)·결정 무늬가 사라짐
- 무광·새틴 제품이 유광으로 변하거나 표면 질감이 달라짐
- 시유 두께가 얇아져 식품 접촉 성능이 시험 조건과 달라짐

1240°C 가마에서 사용할 때는 반드시 다음을 지키십시오.

- 처음 쓰는 색은 같은 흙의 시험편(테스트 타일)을 먼저 구워 확인합니다.
- 굽에서 1cm 이상 유약을 닦아 내고, 아래쪽은 2회로 얇게 바릅니다.
- 작품 아래에 유약 받침(글레이즈 캐처·쿠키, 초벌 받침 접시)을 깝니다.
- 가능하면 가마 안에서 온도가 조금 낮은 아랫단에 놓습니다.

국내 식품용 기준과 미국 표기의 관계

국내에서 판매·제공되는 도자기 식기는 식품의약품안전처 「기구 및 용기·포장의 기준 및 규격」을 따릅니다. 액체를 채울 수 있고 깊이 2.5cm 이상인 가열조리용 도자기는 납 0.5 mg/L 이하, 카드뮴 0.05 mg/L 이하이어야 하며, 그 밖의 용기는 크기와 용도에 따라 공전 기준이 따로 적용됩니다. 깊이 2.5cm 미만이거나 액체를 채울 수 없는 제품은 단위면적당 기준이 적용됩니다.

본 자료의 Food Safe·Dinnerware Safe 표기는 제조사가 미국에서 실시한 시험 결과이며, **국내 식약처 기준 적합 인증을 자동으로 의미하지 않습니다.** 완성 식기를 판매하거나 영업용으로 제공하려면 완성품을 국내 공인 시험기관에서 시험하십시오. 또한 이 결과는 "권장 횟수로 시유하고 표기된 콘(Cone)까지 소성했을 때"에만 해당하며, 두껍게 바르거나 온도가 다르면 결과가 달라질 수 있습니다.

> 주의: Decorative Use Only(장식용) 및 Not Food Safe 표기 제품(LF-190, LF-205, LF-219)은 머그·그릇 안쪽과 입술이 닿는 부분에 사용하지 마십시오. LF-184는 수세미·수저 자국이 남으므로 식기 안쪽에 권하지 않습니다.

4. Application Basics

Preparing the ware

Bisque fire to Cone 04 (approximately 1060 °C) for the most predictable absorption. Ware bisqued lower, such as at 800–900 °C, is more porous and soaks up water quickly, so each brushed coat goes on thicker; reduce to two coats or thin the glaze slightly and test first. Wipe the bisque with a damp sponge to remove dust and hand oils. Do not apply glaze to ware that is still warm from the kiln.

Brushing: three coats

1. Stir the jar thoroughly with a flat stick, scraping the bottom. Do not shake a partly used jar; it introduces air bubbles that can pinhole.
2. Load a soft fan or mop brush fully. Flow the glaze on in one direction, overlapping strokes slightly. Do not scrub back and forth.
3. Let the first coat dry until it loses its sheen (usually 5–15 minutes).
4. Apply the second coat in a crosswise direction to the first, then the third coat in the original direction. Alternating directions evens out brush marks.
5. Keep the lower 1/4 in. (6 mm) of the foot clean on low-movement glazes and 3/8 in. (10 mm) or more on high-movement glazes.

Three coats produce a dry glaze layer about the thickness of a credit card. Two coats give a lighter, more transparent effect on most colors but may leave clear glazes slightly dry or cloudy. Four or more coats are not tested and are not recommended on interior surfaces.

Dipping and pouring

To dip, transfer the glaze to a wider container and add water in small amounts until the specific gravity is about 1.45–1.50. A dip of 2–3 seconds approximates three brushed coats. Food-contact results in this book were established on brushed coats; dipped ware should be tested.

Waxing and cleanup

Use a water-based wax resist on feet and lids. Clean drips with a damp sponge before firing; dry drips on the foot are the most common cause of pieces fusing to the shelf. Wash brushes in water; do not pour glaze residue down the drain.

Kiln loading

Leave at least 1/2 in. (13 mm) between glazed pieces and between ware and elements. Fire high- and very-high-movement glazes on a glaze catcher, a bisque cookie, or kiln wash–coated shelf, and keep kiln wash in good condition on every shelf.

Layering chart

Layering glazes creates effects that single glazes cannot. Apply the base glaze first, then the top glaze. Coats are listed as base + top. Layered combinations increase total thickness and almost always increase movement, so keep combinations away from the bottom third of a piece and always fire layered work on a catcher. All combinations below were fired to Cone 6 on our white stoneware body.

Base (coats)	Top (coats)	Result at Cone 6	Movement	Food contact
LF-125 Oatmeal Speckle (2)	LF-142 Floating Blue (1)	Cream speckles breaking through soft blue float	High	Tested Dinnerware Safe
LF-101 Clear Gloss (2)	LF-177 Sea Glass Green (1)	Clear watery green with deeper pooling	Moderate	Tested Dinnerware Safe
LF-233 Speckled Cream (2)	LF-138 Celadon Mist (1)	Pale celadon with fine iron dots	Moderate	Tested Dinnerware Safe
LF-248 Night Sky (2)	LF-142 Floating Blue (1)	Deep blue with pale blue cloud on rims	High	Tested Dinnerware Safe
LF-112 Satin White (2)	LF-156 Iron Red (1)	Rust breaking to white on edges	Moderate	Food Safe; hand wash
LF-163 Shino Sand (2)	LF-226 Honey Flux (1)	Amber pooling over orange-tan, heavy run	Very high	Food Safe; outside use advised
LF-156 Iron Red (2)	LF-226 Honey Flux (1)	Deep amber-brown with red edges	Very high	Food Safe; hand wash
LF-184 Charcoal Matte (2)	LF-142 Floating Blue (1)	Steel blue over charcoal, satin	High	Exterior only
LF-101 Clear Gloss (1)	LF-219 Copper Patina (2)	Green-turquoise with metallic patches	Moderate	Not food safe
LF-112 Satin White (2)	LF-190 Midnight Crawl (1)	Black crawl islands over white	Low	Decorative only
LF-248 Night Sky (2)	LF-205 Lava Rose (1)	Pink blistered crust over dark blue	Low	Decorative only
LF-177 Sea Glass Green (2)	LF-125 Oatmeal Speckle (1)	Oat speckle softened with green halo	Moderate	Tested Dinnerware Safe

Note: "Tested Dinnerware Safe" applies to the listed coat counts only. A combination is never safer than its least safe component; any combination that includes LF-190, LF-205 or LF-219 is decorative regardless of the base.

Layering tips

- Brush the top glaze on the upper half or the rim only, so the movement has room to travel before it reaches the foot.
- Allow the base coats to dry completely before applying the top glaze. Brushing into a wet base mixes the layers and gives a muddy result.
- Keep the total number of coats to four or fewer on interiors. Five and six coats of layered glaze will almost certainly run at Cone 6.
- Test every new combination on a vertical test tile with a horizontal ledge. Vertical tiles show movement; the ledge shows pooling.
- Record base, top, coats, cone, kiln position and clay body for every test. Small differences in thickness change layered results more than single glazes.

Cooling

Many glazes in this line develop their best surface during a slow cool. Our standard "Cone 6 with slow cool" program used for all photos and test results:

Segment	Rate	Target	Hold
1	200 °F/hr (93 °C/hr)	220 °F (104 °C)	1 hr (candling if ware is damp)
2	300 °F/hr (167 °C/hr)	1940 °F (1060 °C)	none
3	108 °F/hr (60 °C/hr)	2232 °F (1222 °C), Cone 6 down	10 min
4	Fast cool (off)	1900 °F (1038 °C)	none
5	150 °F/hr (83 °C/hr) down	1400 °F (760 °C)	none, then off

Glazes marked "slow cool recommended" on their data sheet (LF-142, LF-156, LF-163, LF-184, LF-248) depend on segment 5 for crystal growth, mottling or a stable matte surface. Fast-cooled pieces will be glossier and less varied.

Common problems at a glance

Problem	Most likely cause	First fix
Crawling (bare patches)	Dusty bisque, glaze too thick, coats applied wet-on-wet	Clean bisque, dry between coats
Pinholes	Air in shaken jar, underfiring, bisque too low	Stir instead of shake, add 10 min hold
Running onto shelf	Too many coats, overfiring, glaze near foot	Fewer coats low on piece, use catcher
Dry or rough surface	Too thin, underfired	Add a coat, check witness cones
Crazing	Glaze and body fit mismatch	Change clay body or test another glaze

LF-101 Clear Gloss

Code	LF-101
Cone	5/6 (oxidation, electric kiln)
Surface	High gloss
Opacity	Transparent
Movement / flow	Low
Application	Brushing; dip/pour after thinning
Recommended coats	3 (2 over underglaze)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601A-112)
Color on white body	Water-clear, slight warm tint where thick
Color on brown body	Clear, body color deepened to warm brown

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-101 Clear Gloss is the foundation of the line: a durable, bright, water-clear glossy glaze designed to fit most commercial mid-fire stoneware and porcelain bodies without crazing. It is the glaze we recommend over underglaze painting, slip decoration, carving and stamped texture, because it stays clear rather than milky even when slightly thick in recesses.

The formula is a balanced calcium–boron glass with low expansion. It melts smoothly at Cone 5 and remains stable at Cone 6, with little tendency to move. On white bodies it gives a clean porcelain-like finish; on iron-bearing bodies it deepens the clay color and shows speckling from the body.

Over underglazes, apply two coats rather than three. Three coats over dark underglaze can turn slightly cloudy and may soften fine linework. Clear Gloss is also the standard liner glaze for the interior of mugs and bowls decorated outside with decorative-only colors.

한글 요약

LF-101 Clear Gloss는 무색 투명 유광유로, 언더글레이즈 그림·화장토·조각 위에 덮는 기본 투명유입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 모두 사용할 수 있습니다.
그림 위에는 2회, 맨 흙 위에는 3회 바르는 것이 기준입니다.
흐름이 적은 편이지만 1240°C 공방 재벌에서는 조금 더 녹아 굽 쪽으로 흐를 수 있으니 굽에서 6mm 이상 닦아 내고 시험편으로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 5 or Cone 6 using a standard medium-speed program. A 10-minute hold at peak helps heal pinholes, especially over textured or carved surfaces. Clear Gloss does not require slow cooling; fast-cooled ware is fully clear. Slow cooling on heavily applied interiors can create a faint haze, which is a normal micro-crystal effect and not a defect.

Tips

- Over underglaze, let the underglaze dry completely and apply the first coat of Clear Gloss with a light, loaded brush so the color is not dragged.
- For liners, pour Clear Gloss into the interior, swirl, and pour out; one pour equals about three brushed coats.
- On dark clay bodies, apply two coats for maximum clarity of the body color.

Troubleshooting

Symptom	Cause	Remedy
Milky or cloudy areas	Applied too thick, or underfired	Two coats only; confirm Cone 6 with witness cones
Fine crazing	Body expansion too low for glaze	Test on a different clay body or fire to full Cone 6
Underglaze smeared	First coat brushed too hard	Dab or flow first coat; do not scrub
Small bubbles in recesses	Glaze pooled thickly in carving	Wipe high spots, add 10 min hold

FAQ

Q. Can I use Clear Gloss over decals or gold? A. Clear Gloss is fired before overglaze decoration, never over it. Apply decals, gold or luster on the fired Clear Gloss surface in a separate low-temperature firing. Pieces with gold or luster are not microwave safe.

Q. Is it safe on the inside of a mug whose outside uses a decorative glaze? A. Yes, as a liner it keeps its Dinnerware Safe status, provided the decorative glaze does not run over the rim onto the drinking area or into the interior.

Q. Why is my clear yellowish on a red body? A. Iron from the clay dissolves into the glaze at the interface. This is normal and does not affect the rating.

LF-112 Satin White

Code	LF-112
Cone	5/6 (oxidation, electric kiln)
Surface	Satin (soft sheen)
Opacity	Opaque
Movement / flow	Low
Application	Brushing; dip/pour after thinning
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601A-127)
Color on white body	Clean soft white
Color on brown body	Warm white with brown breaking on edges

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-112 Satin White is an opaque white with a smooth, low-sheen surface that feels pleasant in the hand and does not show fingerprints. It is our most popular base color for dinnerware and for layering under colored glazes. The satin surface is developed by a fine, stable melt rather than by crystal growth, which is why it holds up to cutlery and dishwasher cycling better than a true matte.

On white clay the result is a clean, quiet white. On brown and speckled bodies, the glaze thins over edges and throwing rings, revealing a warm brown line that emphasizes form. The glaze holds crisp edges and does not soften fine texture.

Satin White is a reliable base for layering. One coat of LF-156 Iron Red or LF-142 Floating Blue over two coats of Satin White gives broken, two-tone effects on rims.

한글 요약

LF-112 Satin White는 은은한 광택의 불투명 백색 유약으로, 식기용 기본 흰색으로 많이 쓰입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
갈색 흙에서는 모서리에 흙색이 비쳐 자연스러운 선이 생깁니다.
1240°C 공방 재벌에서는 표면이 유광에 가깝게 변할 수 있으니 테스트 타일로 질감을 확인하십시오.

Firing schedule notes

Satin White reaches its intended satin surface at Cone 6 with a normal cooling rate. At Cone 5 it is slightly more matte; above Cone 6 the sheen increases and the surface gradually becomes glossy. A slow cool is not required, but the standard slow-cool program in Chapter 4 gives a slightly softer surface and is fully compatible with the rating.

Tips

- Three even coats are important. Two coats leave thin, grey-looking patches on brown bodies; four coats can crawl at the rim.
- Use as a base under any color in the line to brighten it. Colors over Satin White are lighter and cleaner than the same color on bare clay.
- To highlight carving on a brown body, wipe the high points lightly with a damp sponge after the third coat dries.

Troubleshooting

Symptom	Cause	Remedy
Crawling on rim	Glaze too thick, dusty bisque	Wipe bisque; reduce rim coats to 2
Glossy instead of satin	Overfired	Confirm cone; fire lower in kiln
Grey spots	Thin coat over brown body	Apply three full coats
Grey cutlery marks	Normally none; check firing	Underfired surface is softer — fire to full cone

FAQ

Q. Is Satin White a matte glaze? A. No. It is satin, with a soft reflection. If you need a dry matte black, see LF-184 Charcoal Matte, but note that it has a different food-contact rating.

Q. Can I use it on the inside of a bowl? A. Yes. Satin White is Dinnerware Safe on interiors when applied in three coats and fired to Cone 5 or 6.

Q. Why did my white turn slightly yellow? A. Iron and titanium from some clay bodies migrate into the glaze, and a very slow cool can add a faint cream tone. Try a whiter body or a standard cooling rate.

LF-125 Oatmeal Speckle

Code	LF-125
Cone	5/6 (oxidation, electric kiln)
Surface	Satin-matte
Opacity	Semi-opaque
Movement / flow	Low to moderate
Application	Brushing; dip/pour after thinning
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601B-031)
Color on white body	Warm oatmeal beige with dark brown speckles
Color on brown body	Toasted tan, speckles more pronounced, rust edges
Special feature	Granular manganese-iron speckle in suspension

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-125 Oatmeal Speckle is a warm, earthy satin-matte with scattered dark speckles that bloom during firing. It gives the look of a speckled stoneware even on smooth white clay, and on speckled or brown bodies the effect becomes richer, with the glaze breaking to a toasty rust where it thins over edges.

The speckles are produced by coarse colorant granules suspended in the glaze. Each granule melts into a small dark spot with a slightly lighter halo. Because the speckles are in the glaze, stirring is essential: if the granules settle, the first pieces glazed from the jar will be pale and the last pieces will be heavily speckled.

Oatmeal Speckle is one of the best-selling colors in the line and is a reliable choice for mugs, bowls and plates. It works well layered under LF-142 Floating Blue and with a single coat of LF-177 Sea Glass Green.

한글 요약

LF-125 Oatmeal Speckle은 따뜻한 베이지 바탕에 갈색 반점이 생기는 반무광 유약으로, 공방에서 가장 인기 있는 색 중 하나입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
반점 알갱이가 바닥에 가라앉으므로 바르기 전 바닥까지 충분히 저어 주십시오.
1240°C 공방 재벌에서는 반점이 번지고 표면이 유광에 가까워질 수 있으며, 아래쪽이 조금 흐를 수 있으니 굽을 1cm 정도 남기십시오.

Firing schedule notes

Fire to Cone 6 for the classic oatmeal look. At Cone 5 the speckles are smaller and sharper and the surface more matte. Overfiring causes the speckles to spread into soft blotches and the surface to become shiny. The standard slow-cool program gives the most even satin surface but is not required for the rating.

Tips

- Stir for at least one minute, scraping the jar bottom, before every glazing session, and stir again every few pieces.
- Brush in three full coats. Thin application gives a pale, washed-out beige with few speckles.
- On textured surfaces the glaze breaks to a warm brown on high points. Wiping texture lightly after glazing increases this contrast.
- For a cozy two-tone mug, dip the top third in LF-142 Floating Blue over Oatmeal Speckle and fire on a catcher.

Troubleshooting

Symptom	Cause	Remedy
Few or no speckles	Granules settled in jar	Stir from the bottom, re-stir often
Large brown blotches	Overfired or too thick	Fire to Cone 6, not higher; 3 coats max
Pinholes	Bisque dusty or fired too low	Clean bisque; add 10 min hold
Glossy surface	Overfired, or placed in hot spot	Move piece lower in kiln; check cones

FAQ

Q. Do the speckles affect food safety? A. No. The rating was established with the speckles fully developed at Cone 5 and Cone 6.

Q. Can I get a lighter oatmeal? A. Fire on a white body at Cone 5, or apply two coats over one coat of LF-112 Satin White. Test layered interiors before use.

Q. Why does the color differ between two jars? A. Check the lot numbers on the lids. Small natural variation between batches is normal; mix jars from different lots for large sets.

LF-138 Celadon Mist

Code	LF-138
Cone	5/6 (oxidation, electric kiln)
Surface	Gloss
Opacity	Transparent to translucent
Movement / flow	Moderate
Application	Brushing; dip/pour after thinning
Recommended coats	3 (2 over carved surfaces)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601B-058)
Color on white body	Pale blue-green, deeper green in recesses
Color on brown body	Olive-grey green
Special feature	Celadon appearance without reduction firing

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-138 Celadon Mist brings the look of a classic celadon to the electric kiln. Traditional celadons depend on a small amount of iron fired in a reduction atmosphere to produce their blue-green color. In oxidation, the same iron gives yellow or olive. Celadon Mist is formulated with a colorant balance that produces a cool, pale blue-green in a clean oxidation firing, so potters without a gas kiln can achieve a celadon-style finish.

The glaze is glossy and transparent. It pools to a deeper green in carved lines, stamped impressions and the bottoms of bowls, and thins to a pale mist on edges. It is at its best on white stoneware and porcelain; on brown bodies the color turns grey-olive.

Because it is transparent, Celadon Mist reveals every detail of carving, fluting and incised decoration. Brush only two coats over deep carving to keep the pooled areas from becoming too dark.

한글 요약

LF-138 Celadon Mist는 산화소성(전기가마)에서도 청자 느낌의 연한 청록색이 나오도록 만든 투명 유광유입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
백자토·백색 흙에서 가장 맑은 색이 나고, 조각·음각 부분에 고여 진한 녹색이 됩니다.
흐름이 중간 정도라 1240°C 공방 재벌에서는 아래로 흘러 굽에 고일 수 있으니 굽을 1cm 남기고 받침을 사용하십시오.

Firing schedule notes

Fire to Cone 6 in oxidation. Celadon Mist is designed for electric kilns; in reduction it turns a greener, darker tone and is not covered by the rating. A 10-minute hold at peak clears small bubbles, which can otherwise give a cloudy "mist" deeper than intended. Fast or standard cooling keeps the glaze clearest; very slow cooling may add a faint haze.

Tips

- Use white stoneware or porcelain for the cleanest celadon color.
- Carve, flute or stamp the surface before bisque; the glaze rewards texture.
- Pour the interior of bowls rather than brushing to avoid brush marks in the transparent glaze.
- To mimic a traditional crackle-free celadon cup, brush two coats outside and pour one coat inside.

Troubleshooting

Symptom	Cause	Remedy
Yellow-olive color	Iron-bearing clay, or reduction atmosphere	Use white body; fire in clean oxidation
Cloudy, bubbly glaze	Too thick or no hold	Two coats on carving; 10 min hold
Glaze pooled at foot	Too much glaze on lower wall	Thin lower third; keep foot 3/8 in. clean
Crazing	Fit with body	Test another clay body

FAQ

Q. Is this a true celadon? A. It is a celadon-style glaze. The appearance comes from a colorant blend fired in oxidation, not from iron in reduction. It is formulated for consistent results in electric kilns.

Q. Can I fire it in a gas kiln? A. Results in reduction have not been rated. Color will shift greener and darker.

Q. Why does it look blue-grey in the jar? A. Unfired glaze colors are not representative. Always judge by a fired test tile.

LF-142 Floating Blue

Code	LF-142
Cone	5/6 (oxidation, electric kiln)
Surface	Gloss with satin variegation
Opacity	Semi-opaque, variegated
Movement / flow	High
Application	Brushing
Recommended coats	3 (2 on lower half)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601C-014)
Color on white body	Blue with pale blue float, mottled
Color on brown body	Deep blue with amber-brown breaking on edges
Firing note	Slow cool recommended; catcher required

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-142 Floating Blue is a fluid, variegated blue in which a pale, cloud-like layer appears to float over a deeper blue base. The effect is produced by fine crystals and phase separation that develop as the glaze melts and cools. Where the glaze thins over edges and rims it breaks to a warm amber-brown on iron-bearing clay, giving the characteristic two-tone look.

Floating Blue moves considerably in the firing. It is fluid enough to flow over texture and pool in recesses, which is part of its appeal, but it will run onto the shelf if applied heavily near the foot. Always fire on a glaze catcher.

The glaze layers beautifully: over LF-125 Oatmeal Speckle it gives soft speckled blues; over LF-248 Night Sky it adds a pale cloud on rims. Because it is highly reactive, every combination should be test fired before use on functional ware.

한글 요약

LF-142 Floating Blue는 진한 파랑 위에 연한 하늘색 구름 무늬가 떠오르는 유광 유약입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
흐름이 많은 제품이므로 아래쪽 절반은 2회만 바르고, 굽을 1cm 이상 남기며, 반드시 받침 위에서 소성하십시오.
1240°C 공방 재벌에서는 표기 온도보다 높아 더 많이 흘러내리므로 가마 아랫단에 두고 테스트 타일로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 6 with the slow-cool program described in Chapter 4. The floating pale layer develops during cooling between 1900 °F (1038 °C) and 1400 °F (760 °C). With a fast cool, the glaze becomes a more uniform glossy blue with little float. At Cone 5 the effect is quieter and the glaze moves less; this is a good choice for pieces with narrow feet.

Tips

- Three coats on the upper half, two on the lower half, none in the bottom 3/8 in. (10 mm).
- The effect is strongest on rims, edges and texture. Throwing lines and carved bands are ideal.
- Fire tall pieces on a bisque cookie or glaze catcher slightly wider than the foot.
- Dark clay bodies give stronger brown breaking; white bodies give brighter blues.

Troubleshooting

Symptom	Cause	Remedy
Glaze ran onto shelf	Too thick at bottom, overfired	Fewer coats low; fire at Cone 6, not above
Plain blue, no float	Fast cool, or too thin	Use slow cool; three coats on upper half
Pinholes and pits	Gas from body, underfired	Bisque to Cone 04; add 10 min hold
Foot stuck to cookie	Run-off reached cookie	Grind foot; reduce lower coats next time

FAQ

Q. Can I use Floating Blue on a mug interior? A. Yes, it is Dinnerware Safe. For a smoother interior, pour two coats inside rather than three brushed coats.

Q. My float looks grey rather than pale blue. Why? A. Underfiring or a thin coat. Check witness cones and apply three full coats on the upper half.

Q. Can I sand the foot after the glaze ran? A. Yes. Grind with a diamond pad and smooth sharp edges so the piece does not scratch tables.

LF-156 Iron Red

Code	LF-156
Cone	5/6 (oxidation, electric kiln)
Surface	Satin-gloss
Opacity	Opaque
Movement / flow	Moderate
Application	Brushing
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601C-022)
Color on white body	Brick red to rust, black where thin
Color on brown body	Deep rust-brown with dark breaking
Firing note	Slow cool recommended

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	△ Limited (hand wash)	○ Yes	✕ No (hand wash recommended)

LF-156 Iron Red is a high-iron glaze that develops a brick-red to rust surface through the growth of iron crystals as the glaze cools. Where it is thick it turns red-orange; where it thins over edges it shifts to a dark brown-black. The surface is a satin-gloss with fine variation that changes with clay body and cooling rate.

The red color depends heavily on firing. A slow cool through the crystallization range is necessary for a true red; a fast cool gives a glossy dark brown. Because iron crystals at the surface are softer than glass, the surface can show slight color change with acidic foods and long-term dishwasher use. Iron Red therefore carries the Food Safe rating rather than Dinnerware Safe: it may be used for food contact, and hand washing is recommended.

Iron Red pairs well with LF-112 Satin White for broken red rims, and with LF-226 Honey Flux for deep amber pools.

한글 요약

LF-156 Iron Red는 철 결정이 생기면서 벽돌색·녹슨 붉은색이 나오는 고철분 유약입니다.
음식 접촉은 가능(Food Safe)하나 식기세척기 반복 사용 시 표면이 변할 수 있어 손 세척을 권장합니다. 전자레인지 사용은 가능합니다.
붉은 발색은 천천히 식혀야(서랭) 나오며, 빨리 식으면 진한 갈색이 됩니다.
1240°C 공방 재벌에서는 붉은색이 갈색·검정으로 어두워지기 쉬우니 반드시 시험편으로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 6 and use the slow-cool program in Chapter 4, cooling at no more than 150 °F/hr (83 °C/hr) from 1900 °F (1038 °C) to 1400 °F (760 °C). In small kilns that cool quickly on their own, the controlled cool is essential. Overfiring dissolves the iron crystals back into the glass and darkens the color.

Tips

- Three full coats. Thin areas fire black; this can be used deliberately on rims.
- Iron Red is strongest on white and buff bodies. On dark bodies it becomes rust-brown.
- Place pieces in the middle of the kiln, where cooling is most even.
- A small test bowl in every firing is the best way to monitor the cooling rate of your kiln.

Troubleshooting

Symptom	Cause	Remedy
Dark brown, not red	Fast cool or overfire	Program slow cool; check cones
Black patches	Too thin	Three full coats
Dull, rough red	Underfired	Fire to full Cone 6
Runs at foot	Too thick low on piece	Two coats on lower third

FAQ

Q. Why is Iron Red not Dinnerware Safe if it is Food Safe? A. The iron crystal surface passed leach testing, but after extended dishwasher cycling and acidic contact some test pieces showed slight dulling and color change. The rating reflects that.

Q. Will lemon juice or vinegar damage it? A. Brief contact during a meal is fine. Avoid storing acidic foods in Iron Red pieces for long periods.

Q. Can I use it inside a mug? A. Yes, it is Food Safe. Many potters prefer LF-101 Clear Gloss as a liner and Iron Red outside.

LF-163 Shino Sand

Code	LF-163
Cone	5/6 (oxidation, electric kiln)
Surface	Satin, slightly dry on edges
Opacity	Semi-opaque
Movement / flow	Low
Application	Brushing
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601C-036)
Color on white body	Sandy white with orange-tan flashing on edges
Color on brown body	Toasty orange-tan, darker on texture
Firing note	Slow cool recommended

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	△ Limited (hand wash)	○ Yes	✕ No (hand wash recommended)

LF-163 Shino Sand recreates the warm, flashed look of traditional shino-style glazes in an electric kiln. Classic shinos are high-feldspar glazes fired in reduction, often with carbon trapping. Shino Sand uses a high-alumina, low-flux base to give a soft, sandy white surface that flashes to orange-tan where it thins over edges, rims and throwing lines.

The surface is satin with a slightly dry feel at edges. This texture is intentional and part of the shino character, but because it is less smooth than a full glass, the glaze carries the Food Safe rating rather than Dinnerware Safe. It passed leach testing for food contact; hand washing is recommended to keep the surface looking its best.

Shino Sand is at its best on textured, altered and handbuilt forms. It moves very little, so it can be used close to the foot and on pieces with complex edges.

한글 요약

LF-163 Shino Sand는 시노(志野)풍의 모래빛 흰색 바탕에 모서리가 주황·황갈색으로 물드는 반무광 유약입니다.
음식 접촉은 가능(Food Safe)하나 표면이 약간 거칠어 손 세척을 권장하며, 전자레인지 사용은 가능합니다.
흐름이 적어 핸드빌딩·질감 작품에 적합합니다.
1240°C 공방 재벌에서는 주황빛이 줄고 광택이 늘 수 있으니 테스트 타일로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 6 with slow cooling. The orange flashing comes from iron and titanium in the body interacting with the glaze edge, and it develops most strongly during a slow cool. At Cone 5 the surface is drier and whiter. Do not use a hold longer than 10 minutes; extended holds smooth out the flashing.

Tips

- Apply three coats but feather the third coat off toward edges so the glaze is thinner there; thin edges flash more.
- Use iron-bearing or speckled bodies for warm, toasted color. On porcelain, flashing is faint.
- Combine with a single coat of LF-226 Honey Flux on the rim for amber runs (fire on a catcher).

Troubleshooting

Symptom	Cause	Remedy
All white, no flashing	Body too white, fast cool	Use buff body; slow cool
Rough, dry surface overall	Underfired or too thin	Fire to Cone 6; three coats
Crawling	Thick glaze on dusty bisque	Wipe bisque; avoid thick pools
Glossy, plain surface	Overfired	Fire lower; check cones

FAQ

Q. Is this a carbon-trap shino? A. No. Carbon trapping requires a fuel-burning kiln. Shino Sand gives a shino-style appearance through formulation and a slow cool in oxidation.

Q. Can I use it on plates? A. It is Food Safe. On cutting surfaces such as plates, cutlery may leave light marks over time; for daily-use plates choose LF-112 Satin White or LF-233 Speckled Cream.

Q. Why does the color change from piece to piece? A. Flashing varies with body, thickness and kiln position. This variation is the character of the glaze.

LF-177 Sea Glass Green

Code	LF-177
Cone	5/6 (oxidation, electric kiln)
Surface	Gloss
Opacity	Transparent
Movement / flow	Moderate
Application	Brushing; dip/pour after thinning
Recommended coats	3 (2 over texture)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601D-009)
Color on white body	Clear aqua-green, deeper in pools
Color on brown body	Teal-olive, body visible through glaze
Special feature	Glassy depth; ideal over texture

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-177 Sea Glass Green is a clear, watery aqua-green inspired by frosted glass washed up on a beach. It is glossy and transparent, pooling to a deeper teal in recesses and thinning to a pale wash on rims. Unlike LF-138 Celadon Mist, which aims for a cool grey-blue celadon tone, Sea Glass Green is brighter and greener, with a fresh, summery feel.

The glaze is highly stable for a transparent color and fits most mid-fire bodies without crazing. Stamped patterns, impressed leaves and slip trailing show clearly through it. It is fully Dinnerware Safe and is a good choice for serving bowls, cups and platters.

Sea Glass Green can be layered over LF-101 Clear Gloss to lighten it, or under LF-125 Oatmeal Speckle for a speckled green halo effect.

한글 요약

LF-177 Sea Glass Green은 바다 유리처럼 맑은 청록색 투명 유광유로, 무늬·질감 위에 고여 진한 색을 냅니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
셀라돈 미스트(LF-138)보다 더 밝고 초록빛이 강합니다.
흐름이 중간 정도이므로 1240°C 공방 재벌에서는 굽을 1cm 남기고 받침을 깔아 소성하십시오.

Firing schedule notes

Fire to Cone 5 or 6. A 10-minute hold at peak gives a clearer, bubble-free glass. Standard cooling is recommended; very slow cooling may produce a faint surface haze on thick pools. In kilns that run hot at the top, place Sea Glass Green pieces on middle or lower shelves to control movement.

Tips

- Two coats over strong texture keep the pools from turning too dark.
- Pour interiors for an even, brush-mark-free surface.
- For a frosted look, sandblasting is not recommended on food surfaces; use LF-112 Satin White layered under one coat of Sea Glass Green instead (test first).

Troubleshooting

Symptom	Cause	Remedy
Too dark in pools	Too many coats on texture	Two coats on texture
Bubbles, seeds	No hold, glaze thick	10 min hold; thinner coats
Runs at foot	Overfired or thick low	Clean foot 3/8 in.; fire at Cone 6
Faint white haze	Very slow cool	Use standard cooling

FAQ

Q. How is this different from Celadon Mist? A. Celadon Mist is a softer, grey-blue celadon-style glaze. Sea Glass Green is a brighter, more saturated aqua-green.

Q. Does it work on dark clay? A. Yes, but the color turns teal-olive. For a true sea glass color use a white body.

Q. Can I use it over underglaze? A. Yes. It tints underglaze colors green; blues and blacks show best.

LF-184 Charcoal Matte

Code	LF-184
Cone	5/6 (oxidation, electric kiln)
Surface	Dry matte
Opacity	Opaque
Movement / flow	Low
Application	Brushing
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601D-018)
Color on white body	Soft charcoal black, velvet matte
Color on brown body	Deep black-brown matte
Firing note	Slow cool recommended for stable matte

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes (leach test passed)	✕ **No (surface durability)**	○ Yes	✕ **No**

Status: Not Suitable for Dinnerware due to Surface Durability

LF-184 Charcoal Matte is a velvety, deep charcoal-black matte with a soft, stone-like surface. It is ideal for modern vases, planters, the exteriors of mugs and bowls, and sculptural work. Its quiet, non-reflective finish makes forms look crisp and contemporary.

In the 2026 Edition, Charcoal Matte has been reclassified. The glaze continues to pass leach testing, but in extended abrasion testing stainless steel cutlery left grey metal marks on the dry matte surface, and scouring pads gradually polished and scratched it. Because the surface does not withstand daily cutlery and scrubbing, it is now rated Not Suitable for Dinnerware due to Surface Durability.

Use Charcoal Matte on exteriors and decorative ware, and line functional interiors with LF-101 Clear Gloss or LF-112 Satin White. Keep it below the lip line of drinking ware.

한글 요약

LF-184 Charcoal Matte는 벨벳 같은 질감의 짙은 숯색 무광 유약으로, 화병·화분·머그 바깥면에 많이 쓰입니다.
2026년판부터 "표면 내구성 부족으로 식기 부적합" 등급으로 변경되었습니다. 수저·수세미 자국(회색 금속 자국, 긁힘)이 남으므로 식기 안쪽과 입술 닿는 부분에는 쓰지 마십시오.
전자레인지는 가능하나 식기세척기는 권하지 않습니다. 안쪽은 LF-101·LF-112로 시유하십시오.
1240°C 공방 재벌에서는 무광이 반광택으로 변할 수 있으니 테스트 타일로 확인하십시오.

Firing schedule notes

Fire to Cone 6 with the slow-cool program. The matte surface is formed by fine crystals that grow during cooling; with a fast cool the glaze becomes semi-gloss and loses its velvet character. Overfiring above Cone 6 also increases the gloss. At Cone 5 the surface is driest.

Tips

- Brush three even coats; thin areas look grey and patchy.
- Combine with a Clear Gloss interior for a striking contrast on cups and bowls.
- One coat of LF-142 Floating Blue over Charcoal Matte gives a steel-blue satin exterior (catcher required).
- Handle fired pieces with clean hands; oils show on dry matte surfaces. Clean with mild soap and a soft cloth.

Troubleshooting

Symptom	Cause	Remedy
Semi-gloss surface	Fast cool or overfire	Slow cool; fire no higher than Cone 6
Grey patches	Thin application	Three full coats
Crawling on edges	Matte glazes have high surface tension; thick coat	Clean bisque, even coats
Grey marks on surface	Metal from cutlery or tools	Remove with mild cleanser; avoid utensils

FAQ

Q. My older Charcoal Matte mugs were sold as dinnerware. Are they unsafe? A. The glaze still passes leach testing. The change concerns surface durability: cutlery marks and scratching. We recommend using such pieces for decorative purposes or for drinks without utensils, and hand washing them.

Q. Why can I use it in the microwave but not the dishwasher? A. Microwave testing showed no change. Dishwasher detergents and cycling slowly polish and dull the matte surface.

Q. Can I seal the surface? A. Sealers are not food-contact materials and are not recommended on interiors.

LF-190 Midnight Crawl

Code	LF-190
Cone	5/6 (oxidation, electric kiln)
Surface	Crawled texture, matte islands
Opacity	Opaque
Movement / flow	Low (does not run)
Application	Brushing, single thick coat or 2 coats
Recommended coats	2 (thick)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2601D-041)
Color on white body	Black islands with white body showing between
Color on brown body	Black islands over brown, lower contrast
Special feature	Intentional crawl (beads and islands)

Food Safe	Dinnerware Safe	Microwave	Dishwasher
✕ No	✕ No	✕ No	✕ No

Status: Decorative Use Only (Not Food Safe)

LF-190 Midnight Crawl is a texture glaze that deliberately pulls apart during firing, forming rounded black islands separated by lines of bare body or underlying glaze. The effect resembles dried lakebeds or lizard skin. The crawling is produced by a high-shrinkage, high-surface-tension formula that cracks as it dries and beads up as it melts.

Because the fired surface has exposed edges, crevices and bare clay, it cannot be cleaned reliably and is not intended for food contact. Midnight Crawl is rated Decorative Use Only. Do not use it inside mugs, bowls or plates, or on the lip area of any drinking vessel.

The glaze is striking over LF-112 Satin White, which shows through the cracks as bright white lines. Over Night Sky or Celadon Mist it gives a more subtle, layered effect.

한글 요약

LF-190 Midnight Crawl은 소성 중 유약이 일부러 갈라지며 검은 섬 모양으로 뭉치는 장식용 질감 유약입니다.
장식용 전용(Not Food Safe)으로 식기 안쪽·입술 닿는 부분에 사용할 수 없으며, 전자레인지·식기세척기도 불가입니다.
머그를 만든 경우 바깥면 아래쪽에만 쓰고, 안쪽과 입 닿는 부분은 LF-101 등 식기용 유약으로 시유하십시오.
흐르지 않는 유약이지만 1240°C 공방 재벌에서는 갈라진 무늬가 녹아 뭉개질 수 있으니 시험편으로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 5 or 6 with a standard program. Midnight Crawl does not run; it pulls back from edges. Overfiring softens the islands and rounds them into smaller beads. No hold or slow cool is required.

Tips

- Apply as two thick coats, or one heavy coat with a loaded brush. Thin coats do not crawl.
- Let the glaze dry completely; the drying cracks determine the pattern. A fan or warm air speeds up cracking and gives larger islands.
- Apply over a fired-compatible base glaze such as LF-112 Satin White for contrast.
- Islands can fall off the piece if the glaze is applied over a dusty or very smooth surface; handle dry glazed ware gently.

Troubleshooting

Symptom	Cause	Remedy
No crawling	Too thin	Apply thicker, two heavy coats
Islands fall off before firing	Bisque dusty, glaze over-thick	Clean bisque; load kiln carefully
Small beads instead of islands	Overfired	Fire to Cone 5
Glaze on kiln shelf	Loose beads dropped	Fire on a cookie

FAQ

Q. A student made a mug with Midnight Crawl inside. Can it be used? A. No. Pieces with Midnight Crawl on the interior or lip should be used as decorative objects only, such as a pen holder or planter with a liner.

Q. Can I put Clear Gloss over it to make it food safe? A. No. Clear over a crawled glaze does not fill the crevices reliably and the combination is not tested.

Q. Is the glaze toxic to handle? A. Unfired, follow the SDS. Fired, it is safe to handle as a decorative object.

LF-205 Lava Rose

Code	LF-205
Cone	5/6 (oxidation, electric kiln)
Surface	Blistered, cratered, rough
Opacity	Opaque
Movement / flow	Low (expands, does not run)
Application	Brushing, thick dabbed coats
Recommended coats	2–3 (dabbed)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2602A-006)
Color on white body	Dusty rose-pink with white crater rims
Color on brown body	Muted mauve-brown
Special feature	Volcanic texture from gas release during melt

Food Safe	Dinnerware Safe	Microwave	Dishwasher
✕ No	✕ No	✕ No	✕ No

Status: Decorative Use Only (Not Food Safe)

LF-205 Lava Rose is a volcanic texture glaze that bubbles, swells and cracks during firing to create a cratered, pumice-like surface in dusty rose. It is new for the 2026 Edition. The texture is produced by an additive that releases gas while the glaze is molten, leaving frozen bubbles and open craters as the glaze cools.

The surface is sharp-edged and porous. It traps dirt and food, cannot be cleaned effectively, and may chip. Lava Rose is rated Decorative Use Only and must never be used on food-contact or lip surfaces. It is intended for sculpture, vases, planters and the lower exterior of decorative vessels.

The texture is dramatic over LF-248 Night Sky or LF-184 Charcoal Matte, where the pink crust contrasts with the dark base.

한글 요약

LF-205 Lava Rose는 소성 중 부풀고 터지며 용암처럼 울퉁불퉁한 분홍색 표면을 만드는 장식용 유약입니다.
장식용 전용(Not Food Safe)으로 식기·머그 안쪽, 입술 닿는 부분에 사용할 수 없고 전자레인지·식기세척기 모두 불가입니다.
표면이 날카롭고 오염물이 끼므로 화병·오브제 바깥면에만 쓰십시오.
1240°C 공방 재벌에서는 부풂이 심해져 터진 조각이 선반에 떨어질 수 있으니 반드시 받침 위에서 소성하십시오.

Firing schedule notes

Fire to Cone 5 or 6. The texture develops between about 2100 °F (1150 °C) and peak. Overfiring causes the bubbles to collapse into a flatter, glossier crust; underfiring leaves a powdery, unattached surface. Do not hold at peak for more than 10 minutes. Always fire on a cookie or catcher: bubbles near the foot can burst and drop fragments onto the shelf.

Tips

- Dab the glaze on with the brush rather than stroking; thick, uneven deposits give the most dramatic craters.
- Keep Lava Rose at least 1/2 in. (13 mm) above the foot.
- Apply only on exterior surfaces. Mask rims of vessels with tape or wax.
- Sharp crater edges can be softened after firing with a diamond pad.

Troubleshooting

Symptom	Cause	Remedy
Flat, glossy crust	Overfired	Fire at Cone 5–6, short hold
Powdery surface	Underfired or too thin	Fire to full cone; dab thicker
Fragments on shelf	Bubbles burst near foot	Keep 1/2 in. clear; use cookie
Very sharp edges	Normal texture	Soften with diamond pad

FAQ

Q. Can I make a mug with Lava Rose outside only? A. Yes, on the lower exterior, with a Dinnerware Safe glaze inside and on the lip area. Sharp texture on a handle or grip area is uncomfortable; keep it away from where the hand holds.

Q. Why is the color brown on my clay? A. Iron in the clay body dulls the pink. Use a white base or LF-112 Satin White under it.

Q. Can it be fired with other pieces nearby? A. Yes, with at least 1/2 in. clearance; craters can spit small fragments during firing.

LF-219 Copper Patina

Code	LF-219
Cone	5/6 (oxidation, electric kiln)
Surface	Satin-matte with metallic patches
Opacity	Opaque
Movement / flow	Moderate
Application	Brushing
Recommended coats	2–3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2602A-019)
Color on white body	Turquoise-green with bronze metallic areas
Color on brown body	Dark green-black with bronze sheen
Special feature	High copper content, weathered metal look

Food Safe	Dinnerware Safe	Microwave	Dishwasher
✕ No (copper leaching)	✕ No	✕ No	✕ No

Status: Not Food Safe — copper leaching. Exterior decorative use only.

LF-219 Copper Patina recreates the look of weathered bronze and aged copper roofs: turquoise and green fields broken by areas of dark bronze metallic sheen. New for the 2026 Edition, it is a heavily loaded copper glaze in which the metallic areas form where the copper saturates the surface.

Copper at this loading is not fully held in the glass. In leach testing, copper release exceeded our limits for food contact, especially with acidic solutions. Copper Patina is therefore rated Not Food Safe. It must be used only on exterior, non-food surfaces and kept away from rims and lips. The metallic areas can also cause local heating in a microwave, so pieces glazed with it are not microwave safe.

Use Copper Patina for vases, lamp bases, garden pieces and tiles. Over one coat of LF-101 Clear Gloss the color is brighter and more turquoise.

한글 요약

LF-219 Copper Patina는 산화된 청동·구리 지붕처럼 청록색과 금속성 갈색이 섞이는 장식용 유약입니다.
구리가 많이 녹아나와(copper leaching) 음식 접촉 불가(Not Food Safe)이며, 금속성 부분 때문에 전자레인지 사용도 불가합니다. 식기세척기도 쓰지 마십시오.
화병·조명·타일 등 바깥면 장식에만 쓰고, 그릇 안쪽과 입 닿는 부분에는 바르지 마십시오.
1240°C 공방 재벌에서는 흘러내리고 금속광이 사라질 수 있으니 받침 위에서 소성하고 시험편으로 확인하십시오.

Firing schedule notes

Fire to Cone 5 or 6 in oxidation. The metallic bronze areas are strongest at Cone 5 and with a standard cooling rate; at Cone 6 and above, more copper dissolves into the glass and the surface shifts toward glossy green. Copper is volatile at high temperatures and can "flash" onto neighboring pieces, especially white or clear-glazed ware placed closely. Leave at least 1 in. (25 mm) of space around Copper Patina pieces.

Tips

- Two coats give more turquoise; three coats give more bronze metallic.
- Do not use on the same piece as food-surface glazes without a clean, glaze-free gap or a wax line between them.
- Keep the glaze off the rim. For vases used with fresh flowers, the interior can be lined with LF-101 Clear Gloss for easier cleaning.
- Wash hands after glazing; copper compounds should not be ingested.

Troubleshooting

Symptom	Cause	Remedy
No metallic areas	Overfired or thin	Fire Cone 5; three coats
Green halo on nearby pieces	Copper vapor	Increase spacing; shield with kiln furniture
Black, dry patches	Too thick	Two to three coats only
Runs at foot	Overfired	Keep foot clear; use catcher

FAQ

Q. Why does the label say Not Food Safe instead of Decorative Use Only? A. Because the reason is specific: copper release in leach testing. We print the reason so that it is not mistaken for a surface-only limitation.

Q. Can a clear liner make a Copper Patina mug safe? A. The interior lined with LF-101 can be used, but copper glaze must not reach the rim or interior. Copper can also flash onto the liner in the kiln; test such pieces before food use.

Q. Can I use it on tiles in a kitchen? A. As wall tiles behind a counter, yes. Not on countertops or food-prep surfaces.

LF-226 Honey Flux

Code	LF-226
Cone	5/6 (oxidation, electric kiln)
Surface	High gloss
Opacity	Transparent
Movement / flow	Very high
Application	Brushing, upper areas only
Recommended coats	2 (1 when layered)
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2602B-004)
Color on white body	Clear golden honey, amber in pools
Color on brown body	Deep amber-brown
Firing note	Catcher mandatory; runs at Cone 6

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	△ Limited (hand wash)	○ Yes	✕ No (hand wash recommended)

LF-226 Honey Flux is a very fluid, glossy amber glaze designed to run. Applied to rims and upper walls, it flows down the piece in rivulets and pools into golden amber drips, like honey poured over the form. It is new for the 2026 Edition and is primarily intended as a layering and accent glaze.

Because it is so fluid, the fired thickness varies greatly: thin streaks on vertical walls, thick glassy pools at shoulders and bowl bottoms. Honey Flux passed leach testing and is rated Food Safe. Thick pools can develop fine crazing over time on some bodies, so the glaze does not carry the Dinnerware Safe rating, and hand washing is recommended.

Honey Flux runs heavily even at Cone 5. At Cone 6 it can travel 1 in. (25 mm) or more down a vertical wall. It must always be fired on a glaze catcher.

한글 요약

LF-226 Honey Flux는 꿀이 흘러내리듯 호박색으로 흐르는 투명 유광유로, 주로 다른 유약 위 테두리에 겹쳐 씁니다.
음식 접촉은 가능(Food Safe)하나 두껍게 고인 부분에 잔금이 생길 수 있어 손 세척을 권장하며, 전자레인지는 가능합니다.
흐름이 매우 많아 Cone 6에서도 2.5cm 이상 흘러내리므로 위쪽 1/3에만 바르고 받침이 반드시 필요합니다.
1240°C 공방 재벌에서는 선반까지 흘러 작품이 붙을 위험이 매우 크므로, 가마 아랫단과 넓은 받침을 사용하고 시험편 확인 전에는 작품에 쓰지 마십시오.

Firing schedule notes

Fire to Cone 5 for controlled runs and Cone 6 for long, dramatic drips. No hold at peak; a hold adds significantly to movement. Standard cooling. In kilns that overfire the top shelf, place Honey Flux pieces on the lower shelves.

Tips

- Apply only to the upper third of a piece, or as a single band on the rim.
- Use one coat over two coats of a base glaze; two coats alone on bare clay.
- On bowls, the glaze pools in the bottom; brush only the rim and upper wall of the interior.
- Fire every piece on a catcher at least 1/2 in. (13 mm) wider than the foot.

Troubleshooting

Symptom	Cause	Remedy
Glaze on shelf	Applied too low, overfired, hold	Upper third only; no hold; Cone 5
Crazing in pools	Thick pool, body fit	Brush less in bowl interiors
Pale, no amber	Too thin	One more coat at rim
Base glaze bubbling under flux	Layers too thick	Total coats 3 maximum

FAQ

Q. Can I use Honey Flux inside a bowl? A. It is Food Safe. Keep the interior application to the rim area; a deep pool in the bottom is more prone to crazing, which makes cleaning harder.

Q. How much does it run at 1240 °C? A. That is above Cone 6 and outside the tested range. Expect much heavier running; test tiles on catchers are essential.

Q. Does it change the rating of the base glaze? A. Layered pieces are only as safe as the least safe glaze in the combination, and every layered combination should be tested.

LF-233 Speckled Cream

Code	LF-233
Cone	5/6 (oxidation, electric kiln)
Surface	Satin-gloss
Opacity	Opaque
Movement / flow	Low
Application	Brushing; dip/pour after thinning
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2602B-027)
Color on white body	Warm cream with fine brown pepper speckle
Color on brown body	Creamy tan, speckles merge with body iron
Special feature	Fine speckle, smoother and lighter than LF-125

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-233 Speckled Cream is a soft, warm cream with a fine pepper speckle and a smooth satin-gloss surface. New for 2026, it was developed as a lighter, cleaner companion to LF-125 Oatmeal Speckle. The speckles are smaller and evenly scattered, and the surface is smoother, which makes it particularly suited to plates and everyday dinner sets.

The glaze is stable from Cone 5 to Cone 6, moves very little, and holds crisp edges and fine texture. On white bodies it reads as a clean farmhouse cream; on speckled stoneware the body speckle and glaze speckle combine for a richer, more rustic look.

Speckled Cream is fully Dinnerware Safe and is an excellent base for layering. One coat of LF-138 Celadon Mist over it gives a pale celadon with fine iron dots.

한글 요약

LF-233 Speckled Cream은 따뜻한 크림색에 고운 후추 같은 반점이 있는 반광 유약으로, 오트밀 스페클(LF-125)보다 밝고 매끈합니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다. 접시·밥그릇 등 일상 식기에 적합합니다.
흐름이 적어 다루기 쉬운 편입니다.
1240°C 공방 재벌에서는 광택이 늘고 반점이 번질 수 있으니 굽을 6mm 이상 남기고 테스트 타일로 확인하십시오.

Firing schedule notes

Fire to Cone 5 or Cone 6. At Cone 5 the surface is more satin and the speckle crisp; at Cone 6 it becomes a soft satin-gloss with slightly larger dots. Slow cooling is not required. A 10-minute hold helps heal pinholes on porous bisque.

Tips

- Stir well before use; speckle granules settle, although less than in LF-125.
- For a matching set, glaze all pieces from one jar or from mixed jars of the same lot.
- Wipe edges lightly after glazing to reveal a fine brown line on rims of speckled bodies.

Troubleshooting

Symptom	Cause	Remedy
Uneven speckle	Settled granules	Stir from bottom often
Pinholes	Bisque low or dusty	Bisque to Cone 04; 10 min hold
Grey tone	Thin over dark body	Three full coats
Crawl on rim	Thick on dusty rim	Wipe bisque; even coats

FAQ

Q. Should I choose Oatmeal Speckle or Speckled Cream? A. Oatmeal Speckle is darker, warmer and more matte, with larger speckles. Speckled Cream is lighter and smoother, preferred for plates.

Q. Can I use it with underglaze? A. It is opaque; underglaze painted beneath it will be hidden. Paint underglaze on top of the unfired glaze for soft-edged decoration (test first).

Q. Is it suitable for a full dinner set? A. Yes. It is Dinnerware Safe, dishwasher and microwave tested.

LF-248 Night Sky

Code	LF-248
Cone	5/6 (oxidation, electric kiln)
Surface	Gloss
Opacity	Opaque
Movement / flow	Moderate
Application	Brushing
Recommended coats	3
Jar size	16 fl oz (473 ml)
Lot format	YYMM + line + batch on lid (2602C-008)
Color on white body	Deep midnight blue with tiny white and pale blue flecks
Color on brown body	Blue-black with sparse flecks
Firing note	Slow cool recommended for fleck development

Food Safe	Dinnerware Safe	Microwave	Dishwasher
○ Yes	○ Yes	○ Yes	○ Yes

LF-248 Night Sky is a deep, glossy midnight blue scattered with tiny white and pale blue flecks that resemble stars on a clear night. New for 2026, it combines a dark cobalt-based glass with fine light-colored particles that partially melt to form the "stars". On rims and edges the blue lightens slightly and the flecks become denser.

Night Sky is an opaque glaze that covers the clay body well and moves moderately. It is fully Dinnerware Safe, and its dark gloss resists showing cutlery marks. It is a popular choice for mugs, ramen bowls and serving dishes.

The glaze is an excellent base for layering: one coat of LF-142 Floating Blue on the rim adds a pale cloud, and for decorative pieces, LF-205 Lava Rose over it gives a striking pink crust.

한글 요약

LF-248 Night Sky는 짙은 남색 바탕에 작은 흰색·하늘색 점이 별처럼 박히는 유광 유약입니다.
식기 사용 가능(Dinnerware Safe)하며 전자레인지·식기세척기 사용 가능합니다.
별 무늬는 천천히 식힐 때 더 잘 생기며, 흐름은 중간 정도입니다.
1240°C 공방 재벌에서는 흰 점이 녹아 사라지고 아래로 흐를 수 있으니 굽을 1cm 남기고 받침을 깔며 시험편으로 먼저 확인하십시오.

Firing schedule notes

Fire to Cone 6 with slow cooling for the best flecks. At Cone 5 the flecks are sharper but fewer; above Cone 6 they dissolve into the glass and the glaze becomes a plain dark blue. The glaze moves moderately at Cone 6; keep the foot clear by 3/8 in. (10 mm).

Tips

- Stir thoroughly; the fleck particles settle.
- Three coats for a deep, even blue. Two coats give a lighter, streakier blue.
- Wax resist dots or lines beneath Night Sky become bare clay "constellations" — a popular decoration on mugs.
- Pair with an LF-112 Satin White interior for a bright contrast in mugs and bowls.

Troubleshooting

Symptom	Cause	Remedy
No stars	Unstirred, overfired, or fast cool	Stir; Cone 6 max; slow cool
Black, not blue	Too thick or dark body	Three coats; use white body
Runs at foot	Too thick low, overfired	Two coats low; keep foot clear
Pinholes	Bisque too low	Bisque Cone 04; add hold

FAQ

Q. Is the cobalt in Night Sky a concern for food safety? A. The glaze passed leach testing including cobalt, and its durability tests support the Dinnerware Safe rating when applied and fired as stated.

Q. Can I add gold dots for stars? A. Gold or platinum overglaze may be added in a separate low firing, but the piece will no longer be microwave safe.

Q. Why are my stars blue rather than white? A. A slightly higher firing partly dissolves the flecks. Fire to Cone 5–6 and verify with witness cones.

5. Safety Data Sheet Summary

This summary covers the brushing glaze line in its unfired, liquid state. Full Safety Data Sheets (SDS) for each product code are available from the distributor. Where a product contains a specific hazardous ingredient above reporting thresholds, it is listed on that product's SDS.

Section 1 — Identification

Item	Information
Product	Larkfield mid-fire brushing glazes, LF-101 to LF-248
Use	Ceramic glaze for application to bisque ware and firing at Cone 5/6
Manufacturer	Larkfield Glaze Co., Technical Service Department (U.S.A.)
Korean distributor	라크필드코리아, 서울 성동구 — Tel 02-498-2716

Section 2 — Hazard identification

Liquid glaze is not classified as acutely hazardous in normal use. Dried glaze dust may contain crystalline silica, which can cause lung damage with prolonged inhalation. LF-219 Copper Patina contains copper compounds; LF-142, LF-248 and LF-177 contain small amounts of cobalt or copper colorants. Avoid ingestion and inhalation of dust. No lead is used as an ingredient in any product in this line.

Section 3 — Composition

Mixtures of silica, feldspars, kaolin, frits (boro-silicate glass), whiting, metal oxide colorants and stains, water, and a brushing medium (gums, glycols). Exact percentages are trade secret; hazardous components above threshold are disclosed on individual SDS.

Section 4 — First aid

- Eyes: rinse with water for 15 minutes. Seek medical advice if irritation persists.
- Skin: wash with soap and water.
- Ingestion: rinse mouth, drink water, contact a doctor; show the label.
- Inhalation of dust: move to fresh air.

Section 8 — Exposure controls / personal protection

Work wet. Clean spills and dried drips with a damp sponge, not by sweeping. Wear a NIOSH-approved N95 (or equivalent KF94) respirator when sanding or grinding glazed ware or when handling dry glaze. Wear gloves if you have cuts or sensitive skin. Do not eat, drink or smoke in glaze areas. Ventilate the kiln room during firing.

Section 11 — Toxicological information

Chronic inhalation of crystalline silica may cause silicosis. Copper and cobalt compounds may be harmful if swallowed in quantity. Fired glazes classified Food Safe or Dinnerware Safe met leach criteria under the conditions stated on their data sheets.

국내 MSDS(물질안전보건자료) 안내

라크필드코리아는 수입 제품별 국문 물질안전보건자료(MSDS)를 비치하고 있습니다. 공방·학교·기관에서 사업장 비치용 국문 MSDS가 필요한 경우 제품 코드와 Lot 번호(뚜껑 표기)를 알려 주시면 이메일로 보내 드립니다.

구분	내용
요청 방법	이메일 또는 전화로 제품 코드·Lot 번호·기관명 전달
제공 형태	국문 MSDS PDF (영문 SDS 원본 함께 제공)
제공 기간	영업일 기준 2~3일
개정 안내	원료·배합 변경 시 개정본을 등록 고객에게 발송

공방 사용 시 기본 안전 수칙

- 유약은 젖은 상태로 다루고, 바닥·작업대의 마른 유약 가루는 쓸지 말고 젖은 걸레로 닦습니다.
- 소성 후 굽을 갈거나 흘러내린 유약을 그라인더로 제거할 때는 KF94 이상 마스크와 보안경을 착용합니다.
- 유약 작업 공간에서 음식물을 먹거나 마시지 않습니다. 붓·손을 씻은 물은 하수구에 바로 버리지 말고 침전시킨 뒤 앙금은 일반 폐기물로 처리합니다.
- 어린이 수업에서는 장식용 등급(LF-190, LF-205, LF-219) 제품 사용을 피하고, 사용 시 강사가 직접 시유합니다.
- 소성 중에는 가마실을 환기합니다.

> 주의: SDS는 소성 전 유약(액상)에 대한 자료입니다. 완성 식기의 식품 안전성은 SDS가 아니라 각 제품 데이터시트의 등급과 국내 시험 결과로 판단하십시오.

6. 국내 문의 및 주문 안내

라크필드코리아 (Larkfield Glaze Co. 국내 공식 대리점)

항목	내용
주소	서울 성동구 (사무실·물류)
대표 전화	02-498-2716 (평일 09:30~17:30, 점심 12:00~13:00)
팩스	02-498-2719
이메일	order@larkfieldkorea.co.kr (주문) / tech@larkfieldkorea.co.kr (기술 문의)
공방·학교 거래	사업자 등록 후 거래처 단가 적용

주문 및 배송

- 판매 단위: 16 fl oz(473 ml) 병 단위. 같은 색 6병 이상 주문 시 같은 Lot로 맞추어 출고합니다.
- 결제 후 재고 제품은 영업일 기준 1~2일 내 출고하며, 결품 시 미국 본사 입고 일정(통상 4~6주)을 안내해 드립니다.
- 액상 유약 특성상 동절기(12~2월)에는 얼지 않도록 보온 포장하여 발송합니다. 언 유약은 상온에서 녹인 뒤 충분히 저어 사용하면 됩니다.
- 파손·누액 제품은 수령 후 7일 이내 사진과 함께 연락 주시면 교환해 드립니다.

기술 상담

- 처음 사용하는 색은 테스트 타일 소성을 먼저 권합니다. 공방 가마 온도(예: 1240°C 재벌)와 흙 종류를 알려 주시면 흐름·발색 관련 조언을 드립니다.
- 식기 등급(Food Safe·Dinnerware Safe)에 관한 문의는 제품 코드와 시유 횟수, 소성 온도를 함께 알려 주십시오. 국내 판매용 식기의 공인 시험은 고객이 직접 공인 시험기관에 의뢰해야 합니다.
- 본 자료집의 최신판과 제품별 국문 MSDS는 이메일로 요청할 수 있습니다.

문서 정보

항목	내용
문서번호	LF-DS-0526-KR
판	2026 Edition (KR distributor copy, 2026.01)
원문	Larkfield Glaze Co. Mid-Fire Glaze Data Sheets — Cone 5/6
한글 요약 작성	라크필드코리아 기술지원팀

본 자료집의 사양과 등급은 사전 예고 없이 변경될 수 있습니다. 제품 사용 전 병 라벨과 최신판 데이터시트를 확인하십시오.