

Exercice :

Q1. $\text{Al} \text{ et } \text{Hg} \Rightarrow x(\text{Al}) = x(\text{Hg}) = 0.5$

$$w(\text{Al}) = \frac{x(\text{Al}) M(\text{Al})}{x(\text{Al}) M(\text{Al}) + x(\text{Hg}) M(\text{Hg})}$$

$$= \frac{M(\text{Al})}{M(\text{Al}) + M(\text{Hg})}$$

A.N: $w(\text{Al}) = 0.53$
 $w(\text{Hg}) = 0.47$

$\text{Cu}_2\text{Al} \Rightarrow x(\text{Al}) = 0.25 \text{ et } x(\text{Cu}) = 0.75$

$$w(\text{Al}) = \frac{M(\text{Al})}{M(\text{Al}) + 2M(\text{Cu})}$$

A.N: $w(\text{Al}) = 0.12$
 $w(\text{Cu}) = 0.88$

Q2. Conversion $w(\text{Li})$ en $x(\text{Li})$

$$x(\text{Li}) = \frac{\frac{w(\text{Li})}{M(\text{Li})}}{\frac{w(\text{Li})}{M(\text{Li})} + \frac{1-w(\text{Li})}{M(\text{Hg})}}$$

$w(\text{Li})$ [%]	1.15	1.72	3.38	6.55	9.5
$x(\text{Li})$	0.252	0.336	0.503	0.670	0.752
Bilan	LiHg_3	LiHg_2	LiHg	Li_2Hg	Li_3Hg