

Impaextuco

Impaextuco is a white powder plastic stucco for outdoor use; it is designed to give construction finishes. It is a cement-based material, manufactured with high purity minerals and state-of-the-art materials, providing cost-effective fine, durable and weather-resistant finishes.

Advantages

Impaextuco is a very resistant product, with great hardness and workability, similar to plastic stucco; because it is a cement-based product, it is highly compatible with a wide variety of substrates. It is easy to prepare and apply. Its color minimizes the use of paint.

Although it is a product designed to polish, it can be used for "filling" or patching at specific spots of the facade. It can be leveled with a strut for completely flat finishes. It allows integral finishing of walls, edges, narrow walls, false ceilings and expansions without using other products.

Impaextuco is a high yield material for your work since compared to a Plastic Stucco, it requires less drying time, therefore you can complete your work in less time at lower costs; in addition, it poses no problem in the rainy season, since the product is not washed off.

Applications

- Impaextuco is the perfect finish for exteriors; it is appropriate on Impadoc's Rellenolisto Exteriors or Morterolisto, plaster, mortar or stucco. It can also be applied on poured concrete and fiber cement.
- It can be applied indoors on Impadoc Interior Fillers or on any type of compatible substrate with varying drying time depending on the degree of ventilation in the application environment.

Technical Characteristics

*Color: White with a brilliant appearance.

*Consumption: 1.2 -1.4 kg/m² per millimeter of thickness, depending on the type and level of the surface.

Drying time: 30 minutes for polished layers (less than 2 mm). For thicker layers, 60 minutes or more depending on the thickness and the environmental conditions.

**These properties are reported in the certificate of analysis at the client's request.*

Presentation: Laminated polypropylene packaging reinforced with liner 25 kg.

Durability: Six (6) months in its original sealed moisture resistant packaging

Preparation and Application

Hydrate the surface of the substrate before applying the product. The quantity of layers to be applied depends on the condition of the surface.

Remove dust and any loose particles from surfaces where the product is to be applied. Use face mask for dust during this preparation.

Preparation and Application

Because it is a cement-based product, it requires less water for mixing than Stuccolisto. First add the water and then the Impaextruco; wear gloves to mix thoroughly by hand until complete homogenization obtaining a paste with the appropriate consistency according to your application. (for a proper application, use the following ratio: between 2.5 - 3 parts of Impaextruco to 1 part of water)

For filling, apply the most consistent Impaextruco, using a metal trowel, spreading it in alternating vertical and horizontal coats, allowing the first coat to harden sufficiently before applying the second coat.

Refine and settle the product between coats with a trowel, compacting and sealing the surface.

Recommendations

Keep Impaextruco in a dry place and protected from humidity. This powder product is highly sensitive to moisture and water.

Do not mix Impaextruco with another substance or product; use only pollutant-free potable water.

Let the Impaextruco dry before applying the paint; water must be released in order to avoid blistering.

Clean the work tools on a periodical basis.

The quality of the finish depends on the skill of the stucco operator, the correct preparation and application of the product, the condition of the surface and the strict observance of these instructions.

The water used in the mixing must be clean, free of acids, oils, salts, organic matter or any other substance that could impair the properties of Impaextruco.

Avoid applying Impaextruco on damp surfaces and do not glue tiles or veneers of any kind on top of this product.

Impaextruco must not be applied on paintings and at least 24 hours are required to elapse before applying the paint.

The smooth finish of Impaextruco is obtained with a trowel. Not to be sanded.

If after preparation the material loses workability in the container, it may be remixed without adding more water and it will regain its normal consistency for its application.

Technical Assistance

IMPADOC's technical team works hand by hand to offer the best knowledge and optimal use of construction and industry products. If you have any concerns or suggestions, please contact us: asistenciatecnica@impadoc.com

The information provided in this document refers to the product data supplied by Impadoc S.A. and is not intended to guarantee its correct use by the client. When buying the product the client agrees with the characteristics of the product in meeting his requirements, regardless of the particular final use. In case of any failure to meet the conditions of the agreement, within 30 days after the delivery of the product the client will be able to make a claim, as long as the product has been stored in appropriate conditions.

OFFICE AND MANUFACTURING PLANT CALI Address: km 7 vía Jamundí - Cascajal PBX: (602) 555 2406
e-mail: ventas@impadoc.com - Cali - Colombia

OFFICE AND MANUFACTURING PLANT SIBATÉ km 0 + 750 m Vía Silvania, Parque Industrial Tequendama IV. PBX: (571) 3571800 e-mail: ventasbogota@impadoc.com - Sibaté - Colombia.