

Estucolisto

Estucolisto is a cream-white powder product designed to give construction finishes, industrially manufactured with binders, high-purity limestone and the state-of-the-art additives, ensuring cost-effective fine and durable finishes.

Advantages

Estucolisto is very resistant, highly workable and adherent. It is easy to apply. Just mix with water and it will be ready for usage.

It allows repairing fills or gaps on the surface of up to 1 cm and pockets of up to 3 cm deep, without cracking. It can be leveled-off with a strut for completely flat finishes. It allows to integrally finish walls, edges, pockets, floating ceilings and expansions without using other products.

Applications

- Estucolisto is the perfect finish for interiors. It can be applied over interior fillers or Impadoc Morterolisto, plasterwood, motar coverings or stucco.
- It can also be applied on cement blocks, pressed brick, smooth or grooved brick, common brick, clean brick and poured concrete.

Technical characteristics

*Consumption: 1.2 - 1.3 kg/m² per millimeter of thickness, depending on the type and level of the surface.

Setting time: 25 to 35 minutes under normal conditions (23-25°C, 50-70% RH).

* Colour: Cream White.

**These properties can be found in the certificate of analysis at the request of the client.*

Presentation: 10 kg and 25 kg laminated polypropylene packaging.

Polyethylene packaging per 2 kg. Packing unit of 5 bags per 2 kg.

Durability: Three (3) months in its original sealed packaging and protected from moisture.

Preparation and Application

1. Remove dust and loose particles from surfaces to be applied. Wear a dust mask during preparation.
2. Add Estucolisto powder to the mixing water, two (2) parts of powder per one (1) part of water or 50% of the amount of powdered product to be used, mix very well with a gloved hand until you obtain a paste with the right consistency for your application.
3. To fill, apply the denser Stuccolist with a metal trowel, spreading it in alternate vertical and horizontal layers, allowing it to dry enough to apply the second layer. To polish the consistency, more water can be added.
Between layers, refine or settle the product with the trowel, for a better compacting and sealing of the surface.
4. To level the surface, pass the strut with some pressure, both horizontally and vertically, after each layer.
5. Remove the material collected in the strut and apply it again with the trowel in the marked depressions, until they are filled. Then go over the surface with the strut until the surface is completely leveled.
6. Generally three (3) coats of Estucolisto are sufficient for a satisfactory finish.

Recommendations

1. Keep Estucolisto in a dry place protected from moisture. This product is highly sensitive to moisture and may coagulate.
2. Only prepare the amount of material that will be applied within 15 minutes, the time in which it begins to set (avoid reusing), once it is consumed. Wash the container with clean water to avoid stone chips caused by the set material.
3. Do not prepare Estucolisto in containers contaminated with paints, lacquers, release agents, etc., to avoid changes in the behavior of the product.
4. Do not mix Estucolisto with another substance or product as it alters the formulation and therefore its physicochemical characteristics, use only contaminant-free clean water.
5. Allow Estucolisto to dry before applying paint to avoid blistering from trapped water. The complete drying time will be reached in 24 hours under normal ventilation and environmental conditions (23-25°C, RH.%50-70), with thicknesses of 6 mm, and following the information recommended in this technical sheet for preparation and application. The state and type of substrate must be taken into account.
6. Periodically clean the spatula, the trowel and the strut to maintain the smoothness of the application.
7. The quality of the final finish depends on the skill of the plasterer, the correct application of the product, the condition of the surface and the observance of these instructions.
8. The water for the mixture must be clean, free of acids, oils, salts, organic matter or any other substance that may impair the quality, resistance or durability of the product.
9. In order not to affect the adhesion of the Estucolisto when it is being applied on prefabricated and concrete plates, completely remove the residues of release agents or grease. In these cases, it is recommended to apply a water-based primer with a roller (1/2 gallon of acrylic primer per 4.5 gallons of water).
10. If the Estucolisto is applied directly on concrete plates, it is necessary to verify that they are completely set.
11. Do not apply the Estucolisto on damp surfaces and do not stick tiles or veneers of any kind at all.
12. Estucolisto should not be applied on paints.
13. The smooth finish of Estucolisto is obtained with the use of a trowel and should not be sanded.
14. Keep in mind that the environmental and ventilation conditions of the location of the application can alter the drying times of the product.

Technical assistance

IMPADOC S.A. works with its clients on a daily basis, ensuring through its technical team, the optimal knowledge and use of products for construction and industry. For any questions or concerns, contact us by email: Asistenciatecnica@impadoc.com

The information provided in this document corresponds to characteristic data of products supplied by Impadoc S.A. and does not guarantee correct use by the customer. The sale is made under the approval of the client regarding the conformity of the product with its requirements, regardless of the particular uses. If there is any breach of the conditions of the established contract, the client has 30 days after dispatch to make the respective claim, as long as it has been stored in optimal conditions.

OFFICE and PLANT CALI- Address km 7 vía Jamundí - Cascajal PBX: (602) 555 2406
e-mail: ventas@impadoc.com - Cali – Colombia

OFFICE and PLANT SIBATÉ km 0 + 750 m Vía Silvania, Parque Industrial Tequendama IV. PBX: (601) 3571800
e-mail: ventasbogota@impadoc.com - Sibaté - Colombia.