

TS-411A

Unitech Laboratories Services LLP
 16, Samrat Industrial Area, B/h. S. T. Workshop
 Gondal Road, Rajkot - 360 004. Gujarat, INDIA
 M+91 84600 60450, 99742 01090, 79901 74169
 E unitech_lab@yahoo.com



TEST REPORT

Name of the Customer : METAL MECH ENGINEERING		Lab No. : ULS/026/0825
		Date of Reporting : 03/08/2025
		Date of Smp. Receipt : 03/08/2025
Group	: Chemical Testing of Metals and Alloys	
Sub Group	: Stainless Steel	
#Customer Reference No.	: Letter Date-03/08/2025	
Condition of Sample	: Cut Piece	
Material Specification	: ASTM A276/A276M-24a Gr. 316L(S31603)	
#Identification of Sample	: Size : Ø 20.00 MM	
#Type of Test	: Chemical Analysis	
Instrument Utilized	: Optical Emission Spectrometer-Bruker- German make-Q4 TASMAN	
Date of Testing	: 03/08/2025	
Test Method	: ASTM E1086-22, IIS G-1253-2002	
ELEMENTS	OBSERVATION	REQUIRED VALUE
% CARBON	: 0.018	0.03 max
% SILICON	: 0.343	1.00 max
% MANGANESE	: 1.792	2.00 max
% PHOSPHORUS	: 0.043	0.045 max
% SULFUR	: 0.019	0.030 max
% CHROMIUM	: 16.870	16.00-18.00
% MOLYBDENUM	: 2.027	2.00-3.00
% NICKEL	: 10.070	10.00-14.00
Conformity statement : The above result is conform to ASTM A276/A276M-24a Gr. 316L(S31603)		
End of Report		
Tested By: Jaimini Vadodariya (Technician)   Authorized signatory: Deepak Solanki (Quality Manager)		
Note : (1) Sample(s) not drawn by ULS. The results relate only to the sample(s) tested. (2) This certificate shall not be reproduced, except in full, without the written approval of ULS. (3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in writing or he can collect the same. (4) While "ULS" has made their best endeavors to provide accurate and reliable information. (5) The conformity statement is given bases of decision rule documented in Quality Manual Annexure-3. # Information Given by Customer		