

P.O.No-25100321

313022-07 m.Bod y
313020-07 P. Bod y
313023-02 Cap

TS-320-TS-32d


Unitech Laboratories Services

16, Samrat Industrial Area, B/h. S. T. Workshop
Gondal Road, Rajkot-360 004 Gujarat, INDIA
M +91-84600 60450, 99742 01090, 79901 74169
E unitech_lab@yahoo.com

*You can always trust on our accuracy.***TEST REPORT**

Name of the Customer : METAL MECH ENGINEERING		Lab No. : ULS/533/0725
		Date of Reporting : 25/07/2025 Date of Smp. Receipt : 25/07/2025
Group : Chemical Testing of Metals and Alloys		
Sub Group : Stainless Steel		
#Customer Reference No. : Letter Date-25/07/2025		
Condition of Sample : Cut Piece		
Material Specification : ASTM A276/A276M-24a Gr. 316L(S31603)		
#Identification of Sample : Size : 32.00 MM HEX		
#Type of Test : Chemical Analysis		
Instrument Utilized : Optical Emission Spectrometer-Bruker- German make-Q4 TASMAN		
Date of Testing : 25/07/2025		
Test Method : ASTM E1086-22, JIS G-1253-2002		
ELEMENTS	OBSERVATION	REQUIRED VALUE
% CARBON	0.018	0.03 max
% SILICON	0.357	1.00 max
% MANGANESE	1.425	2.00 max
% PHOSPHORUS	0.045	0.045 max
% SULFUR	0.016	0.030 max
% CHROMIUM	16.870	16.00-18.00
% MOLYBDENUM	2.047	2.00-3.00
% NICKEL	10.100	10.00-14.00
Conformity statement : The above result is conform to ASTM A276/A276M-24a Gr. 316L(S31603)		

End of Report



Tested By :
Jaimini Vadodariya
(Technician)

Authorized signatory:
Deepak Solanki
(Quality Manager)

Note : (1) Sample(s) not drawn by ULS. The results relate only to the sample(s) tested.

(2) This certificate shall not be reproduced, except in full, without the written approval of ULS.

(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in writing or he can collect the same.

(4) While "ULS" has made their best endeavors to provide accurate and reliable information.

(5) The conformity statement is given bases of decision rule documented in Quality Manual Annexure-3. # Information Given by Customer

