

TS-459

P.O.No - 26100007

PLG 2007


Unitech Laboratories Services LLP

16, Samrat Industrial Area, B/h. S. T. Workshop
Gondal Road, Rajkot - 360 004, Gujarat, INDIA
M+91 84600 60450, 99742 01090, 79901 74169
E unitech_lab@yahoo.com



SINCE 2010

unitech
TEST REPORT
You can always trust on our accuracy.
ULR-TC161762600041571F
Name of the Customer : METAL MECH ENGINEERING
Lab No. : US/1600/0426
Date of Reporting : 14/04/2026
Date of Smp. Receipt : 14/04/2026

Group : Chemical Testing of Metals and Alloys
Sub Group : Stainless Steel
#Customer Reference No. : Letter Date-14/04/2026
Condition of Sample : Cut Piece
Material Specification : ASTM A276/A276M-25 Gr. 316L(S31603)
#Identification of Sample : Size: Ø 42.00 MM
#Type of Test : Chemical Analysis
Instrument Utilized : Optical Emission Spectrometer.-German make-SPECTRO MAXx - LMA110
Date of Testing : 14/04/2026
Test Method : ASTM E1086-22, JIS G-1253-2002

ELEMENTS	OBSERVATION	REQUIRED VALUE
% CARBON	0.017	0.03 max
% SILICON	0.523	1.00 max
% MANGANESE	1.297	2.00 max
% PHOSPHORUS	0.038	0.045 max
% SULFUR	0.005	0.030 max
% CHROMIUM	16.242	16.00-18.00
% MOLYBDENUM	2.032	2.00-3.00
% NICKEL	10.140	10.00-14.00

Conformity statement : The above result is conform to ASTM A276/A276M-25 Gr. 316L(S31603)
(Decision Rule:Statement of conformity is provided without consideration measurement uncertainty)

End of Report

Tested By :
 Avin Hirapara
 (Technician)



Reviewed & Authorized By:
 Deepak Solanki
 (Quality Manager)

Note : (1) Sample(s) not drawn by ULS. The results relate only to the sample(s) tested.
 (2) This certificate shall not be reproduced, except in full, without the written approval of ULS.
 (3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in writing or he can collect the same.
 (4) While "ULS" has made their best endeavors to provide accurate and reliable information.
 (5) The conformity statement is given bases of decision rule documented in Quality Manual Annexure-3.'# Information Given by Customer

