



P.O.NO-25100653

TS-383

TS-375



RAJKOT METALAB SERVICES LLP

Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Manuti Showroom,
Vavdi, Rajkot, Gujarat 360004, India

testing@rajkotlab.com

www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : VK-0013

Customer Name : METAL MECH ENGINEERING.		ULR No. : TC521225000042791F
Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared, Jamnagar - 361004 (Gujarat, India)		Report No. : MVSK-0013.1
		Report Date : 16/11/2025
		Date of Receipt : 16/11/2025

Type of Test	: Chemical Analysis By Optical Emission Spectrometer.
Discipline & Group	: Chemical & Metals & Alloys
Instrument Utilized	: Optical Emission Spectrometer, Spectromaxx, LMX10
Calibration Date	: 04/07/2025 & Due On 03/07/2026
**Customer's Reference	: Nil
**Condition of Sample	: Test Piece
**Material Specification	: ASTM A276/A276M-24a Gr. 316L
**Identification of Sample	: 25 MM Round Bar
Date of Testing	: 16/11/2025
Test Method	: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

Elements	Results	Required Value	
		Min	Max
% Carbon	: 0.017		0.030
% Silicon	: 0.539		1.000
% Manganese	: 1.400		2.000
% Phosphorus	: 0.042		0.045
% Sulphur	: 0.004		0.030
% Chromium	: 16.240	16.000	18.000
% Molybdenum	: 2.036	2.000	3.000
% Nickel	: 10.050	10.000	14.000
% Copper	: 0.433		
% Titanium	: 0.0089		
% Magnesium	: 0.010		
% Zirconium	: 0.005		
% Nitrogen	: 0.074		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

Remark : This material does not contain, by mass, more than 7.5% of Magnesium, Titanium and Zirconium.

*** END OF REPORT ***



Vishal

Tested By



Reviewed & Authorized By

Ankur (QM)

Terms & Conditions :

- The results relate only to the sample tested, Sample(s) drawn by party. * Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. ** Information provided by Customer.