



P.O. NO 25100683
TS-383
TS-375
313003-02 Cell
3130020-02 1PT. Body
313002-02 M. Body



RAJKOT METAL LAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : VK-0016

Customer Name : METAL MECH ENGINEERING.

Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared,
Jamnagar - 361004 (Gujarat, India)

ULR No. : TC521225000042794F

Report No. : MVSK-0016.1

Report Date : 16/11/2025

Date of Receipt : 16/11/2025

Type of Test : Chemical Analysis By Optical Emission Spectrometer.

Discipline & Group : Chemical & Metals & Alloys

Instrument Utilized : Optical Emission Spectrometer, Spectromaxx, LMX10

Calibration Date : 04/07/2025 & Due On 03/07/2026

**Customer's Reference : Nil

**Condition of Sample : Test Piece

**Material Specification : ASTM A276/A276M-24a Gr. 316L

**Identification of Sample : 32 MM Hex

Date of Testing : 16/11/2025

Test Method : ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

Elements	Results	Required Value
	Min	Max
% Carbon	: 0.018	0.030
% Silicon	: 0.513	1.000
% Manganese	: 1.510	2.000
% Phosphorus	: 0.031	0.045
% Sulphur	: 0.013	0.030
% Chromium	: 16.860	18.000
% Molybdenum	: 2.054	3.000
% Nickel	: 10.070	14.000
% Copper	: 0.360	
% Titanium	: 0.0103	
% Magnesium	: 0.010	
% Zirconium	: 0.005	
% Nitrogen	: 0.069	0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L


Remark : This material does not contain, by mass, more than 7.5% of Magnesium, Titanium and Zirconium.

*** END OF REPORT ***



Vishal

Tested By



Reviewed & Authorized By

Ankur (QM)

Terms & Conditions :

- The results relate only to the sample tested, Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. •** Information provided by Customer.