



TS-427
TS-436

P.O. NO. - 25100896
u n 25100974

313001m-04 N1004E
314006-04 DVS4



RAJKOT METLAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : CL-0627

Customer Name : METAL MECH ENGINEERING.

Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared,
Jamnagar - 361004 (Gujarat, India)

ULR No. : TC521226000005114F

Report No. : MCSL-0627.1

Report Date : 06/02/2026

Date of Receipt : 06/02/2026

Type of Test : Chemical Analysis By Optical Emission Spectrometer.
Discipline & Group : Chemical & Metals & Alloys
Instrument Utilized : Optical Emission Spectrometer, Spectromaxx, LMX10
Calibration Date : 04/07/2025 & Due On 03/07/2026
**Customer's Reference : Nil
**Condition of Sample : Test Piece
**Material Specification : ASTM A276/A276M-24a Gr. 316L
**Identification of Sample : Part Name: 50 mm Hex Bar
Date of Testing : 06/02/2026
Test Method : ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

Elements	Results	Required Value	
		Min	Max
% Carbon	: 0.011		0.030
% Silicon	: 0.335		1.000
% Manganese	: 1.380		2.000
% Phosphorus	: 0.040		0.045
% Sulphur	: 0.024		0.030
% Chromium	: 16.340	16.000	18.000
% Molybdenum	: 2.022	2.000	3.000
% Nickel	: 10.550	10.000	14.000
% Copper	: 0.325		
% Titanium	: 0.0084		
% Magnesium	: <0.001		
% Zirconium	: 0.005		
% Nitrogen	: 0.076		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

*** END OF REPORT ***



Mansi Trada

Tested By



Reviewed & Authorized By

Ankur (QM)

Terms & Conditions :

- The results relate only to the sample tested, Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.

