

TS-527
TS-528P.O.NO-26100340
P.O.NO-26100302RD3N20m
313001m-02-NHPPC
314006-02 BOSH

RAJKOT METLAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : PL-0911

Customer Name : METAL MECH ENGINEERING.

Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared,
Jamnagar - 361004 (Gujarat, India)

ULR No. : TC521226000031968F

Report No. : MPST-0911.1

Report Date : 23/08/2026

Date of Receipt : 23/08/2026

Type of Test : Chemical Analysis By Optical Emission Spectrometer.
Discipline & Group : Chemical & Metals & Alloys
Instrument Utilized : Optical Emission Spectrometer, Spectromaxx, LMX10
Calibration Date : 02/07/2026 & Due On 01/07/2027
**Customer's Reference : Nil
**Condition of Sample : Test Piece
**Material Specification : ASTM A276/A276M-24a Gr. 316L
**Identification of Sample : Part Name: 36 MM Hex
Date of Testing : 23/08/2026
Test Method : ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

Elements	Results	Required Value	
		Min	Max
% Carbon	: 0.024		0.030
% Silicon	: 0.390		1.000
% Manganese	: 1.340		2.000
% Phosphorus	: 0.041		0.045
% Sulphur	: 0.002		0.030
% Chromium	: 16.650	16.000	18.000
% Molybdenum	: 2.010	2.000	3.000
% Nickel	: 10.060	10.000	14.000
% Copper	: 0.510		
% Titanium	: 0.0020		
% Magnesium	: 0.002		
% Zirconium	: 0.006		
% Nitrogen	: 0.075		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

*** END OF REPORT ***

Mansi Trada
Tested ByReviewed & Authorized By
Ankur (QM)

Terms & Conditions :

- The results relate only to the sample tested, Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.