TS-428 P.O.NO-2510084 AR-32

TC-5212

RAJKOT LAB
RAJKOT METLAB SERVICES LLP

RAJKOT METLAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : CL-0625

Customer Name : METAL MECH ENGINEERING. **Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared, Jamnagar - 361004 (Gujarat, India)**	**ULR No. : TC521226000005112F** **Report No. : MCSL-0625.1** **Report Date : 06/02/2026** **Date of Receipt : 06/02/2026**

Type of Test	**: Chemical Analysis By Optical Emission Spectrometer.**
Discipline & Group	**: Chemical & Metals & Alloys**
Instrument Utilized	**: Optical Emission Spectrometer, Spectromaxx, LMX10**
Calibration Date	**: 04/07/2025 & Due On 03/07/2026**
****Customer's Reference**	**: Nil**
****Condition of Sample**	**: Test Piece**
****Material Specification**	**: ASTM A276/A276M-24a Gr. 316L**
****Identification of Sample**	**: Part Name: 42 mm Hex Bar**
Date of Testing	**: 06/02/2026**
Test Method	**: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)**

Elements		Results	Required Value Min	Required Value Max
% Carbon	:	0.016		0.030
% Silicon	:	0.364		1.000
% Manganese	:	1.580		2.000
% Phosphorus	:	0.033		0.045
% Sulphur	:	0.008		0.030
% Chromium	:	16.100	16.000	18.000
% Molybdenum	:	2.012	2.000	3.000
% Nickel	:	10.780	10.000	14.000
% Copper	:	0.433		
% Titanium	:	0.0095		
% Magnesium	:	<0.001		
% Zirconium	:	0.005		
% Nitrogen	:	0.059		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

*** END OF REPORT ***

Mansi Trada
Tested By

Reviewed & Authorized By
Ankur (QM)

Terms & Conditions :
• The results relate only to the sample tested , Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
• RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
• Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.

METALMECH ENGINEERING QA PASSED