



TS-422
TS-422
TS-432

P.O. No - 25100862



RD CM 2M RD 2P 2N RD 2N 2M

RAJKOT METLAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 9725213600

TEST REPORT

Lab ID : CL-0621

Customer Name : METAL MECH ENGINEERING. Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared, Jamnagar - 361004 (Gujarat, India)		ULR No. : TC521226000005108F Report No. : MCSL-0621.1 Report Date : 06/02/2026 Date of Receipt : 06/02/2026
Type of Test	: Chemical Analysis By Optical Emission Spectrometer.	
Discipline & Group	: Chemical & Metals & Alloys	
Instrument Utilized	: Optical Emission Spectrometer, Spectromaxx, LMX10	
Calibration Date	: 04/07/2025 & Due On 03/07/2026	
**Customer's Reference	: Nil	
**Condition of Sample	: Test Piece	
**Material Specification	: ASTM A276/A276M-24a Gr. 316L	
**Identification of Sample	: Part Name: 30 mm Hex Bar	
Date of Testing	: 06/02/2026	
Test Method	: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)	

Elements	Results	Required Value	
		Min	Max
% Carbon	: 0.011		0.030
% Silicon	: 0.437		1.000
% Manganese	: 1.610		2.000
% Phosphorus	: 0.036		0.045
% Sulphur	: 0.001		0.030
% Chromium	: 16.200	16.000	18.000
% Molybdenum	: 2.020	2.000	3.000
% Nickel	: 10.720	10.000	14.000
% Copper	: 0.592		
% Titanium	: 0.0088		
% Magnesium	: <0.001		
% Zirconium	: 0.006		
% Nitrogen	: 0.051		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

*** END OF REPORT ***



Mansi Trada
Tested By



Reviewed & Authorized By
Ankur (QM)

Terms & Conditions :

- The results relate only to the sample tested, Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.

