



TC-5212



RAJKOT METLAB SERVICES LLP

Lab ID : KL-0448

## TEST REPORT

Customer Name : METAL MECH ENGINEERING.

Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared,  
Jamnagar - 361004 (Gujarat, India)

ULR No. : TC521226000021246F

Report No. : MKSL-0448.1

Report Date : 05/06/2026

Date of Receipt : 05/06/2026

### Type of Test

: Chemical Analysis By Optical Emission Spectrometer.

### Discipline & Group

: Chemical & Metals & Alloys

### Instrument Utilized

: Optical Emission Spectrometer, Spectromaxx, LMX10

### Calibration Date

: 04/07/2025 & Due On 03/07/2026

### \*\*Customer's Reference

: Nil

### \*\*Condition of Sample

: Test Piece

### \*\*Material Specification

: ASTM A276/A276M-24a Gr. 316L

### \*\*Identification of Sample

: Part Name: 25 MM Hex

### Date of Testing

: 05/06/2026

### Test Method

: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

### Elements

#### Results

#### Required Value

|              | Min    | Max    |
|--------------|--------|--------|
| % Carbon     | 0.022  | 0.030  |
| % Silicon    | 0.397  | 1.000  |
| % Manganese  | 1.540  | 2.000  |
| % Phosphorus | 0.041  | 0.045  |
| % Sulphur    | 0.021  | 0.030  |
| % Chromium   | 16.690 | 18.000 |
| % Molybdenum | 2.007  | 3.000  |
| % Nickel     | 10.100 | 14.000 |
| % Copper     | 0.693  |        |
| % Titanium   | 0.0023 |        |
| % Magnesium  | <0.001 |        |
| % Zirconium  | 0.006  |        |
| % Nitrogen   | 0.060  | 0.100  |

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

\*\*\* END OF REPORT \*\*\*



Mansi Trada

Tested By



Reviewed & Authorized By

Ankur (QM)

### Terms & Conditions :

- The results relate only to the sample tested. Sample(s) drawn by party. \* Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. \*\* Information provided by Customer.

