


TS-508

P.O.NO-26100072

313002-04 m.Body
313003-04 Lab



RAJKOT METLAB SERVICES LLP

Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : KL-0451

Customer Name : METAL MECH ENGINEERING.

Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared,
Jamnagar - 361004 (Gujarat, India)

ULR No. : TC5212260000021249F

Report No. : MKSL-0451.1

Report Date : 05/06/2026

Date of Receipt : 05/06/2026

Type of Test

Discipline & Group : Chemical Analysis By Optical Emission Spectrometer.

Instrument Utilized : Chemical & Metals & Alloys

Calibration Date : Optical Emission Spectrometer, Spectromaxx, LMX10

**Customer's Reference : 04/07/2025 & Due On 03/07/2026

**Condition of Sample : Nil

**Material Specification : Test Piece

**Identification of Sample : ASTM A276/A276M-24a Gr. 316L

Date of Testing : Part Name: 55 MM Hex

Test Method : 05/06/2026

: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)

Elements

	Results	Required Value	
		Min	Max
% Carbon	: 0.018		0.030
% Silicon	: 0.388		1.000
% Manganese	: 1.580		2.000
% Phosphorus	: 0.033		0.045
% Sulphur	: 0.004		0.030
% Chromium	: 16.600	16.000	18.000
% Molybdenum	: 2.081	2.000	3.000
% Nickel	: 10.030	10.000	14.000
% Copper	: 0.435		
% Titanium	: 0.0023		
% Magnesium	: <0.001		
% Zirconium	: 0.006		
% Nitrogen	: 0.060		0.100

Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.

*** END OF REPORT ***



Mansi Trada
Tested By



Reviewed & Authorized By
Ankur (QM)

[Signature]

Terms & Conditions :

- The results relate only to the sample tested. Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
- RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made.
- Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.