

P.O. NO - 28100699
75-377

RAJKOT METLAB SERVICES LLP
Rajkot Lab Gate, NH27, Opp JCB Showroom,
Nr. Tulip Party Plot, B/h Perfect Maruti Showroom,
Vavdi, Rajkot, Gujarat 360004, India
testing@rajkotlab.com
www.rajkotlab.com +91 97252 13600

TEST REPORT

Lab ID : VK-0017

Customer Name : METAL MECH ENGINEERING. Address : Plot No. 4246, Road-E GIDC, Phase-III, Dared, Jamnagar - 361004 (Gujarat, India)		ULR No. : TC521225000042795F Report No. : MVSK-0017.1 Report Date : 16/11/2025 Date of Receipt : 16/11/2025	
Type of Test	: Chemical Analysis By Optical Emission Spectrometer.		
Discipline & Group	: Chemical & Metals & Alloys		
Instrument Utilized	: Optical Emission Spectrometer, Spectromaxx, LMX10		
Calibration Date	: 04/07/2025 & Due On 03/07/2026		
**Customer's Reference	: Nil		
**Condition of Sample	: Test Piece		
**Material Specification	: ASTM A276/A276M-24a Gr. 316L		
**Identification of Sample	: 36 MM Hex		
Date of Testing	: 16/11/2025		
Test Method	: ASTM E1086-22, IS 9879-98(RA2021), JIS G1253-2002(Amd 2013)		
Elements	Results	Required Value	
		Min	Max
% Carbon	: 0.019		0.030
% Silicon	: 0.393		1.000
% Manganese	: 1.370		2.000
% Phosphorus	: 0.034		0.045
% Sulphur	: 0.019		0.030
% Chromium	: 16.760	16.000	18.000
% Molybdenum	: 2.056	2.000	3.000
% Nickel	: 10.130	10.000	14.000
% Copper	: 0.448		
% Titanium	: 0.0093		
% Magnesium	: 0.010		
% Zirconium	: 0.004		
% Nitrogen	: 0.070		0.100
Statement of Conformity : Above results are Meeting with Chemical requirement of ASTM A276/A276M-24a Gr. 316L Specification.			
Remark : This material does not contain, by mass, more than 7.5% of Magnesium, Titanium and Zirconium.			
*** END OF REPORT ***			
 Vishal Tested By   Reviewed & Authorized By Ankur (QM)			
Terms & Conditions : • The results relate only to the sample tested, Sample(s) drawn by party. • Test Certificate shall not be re-produced except in full without the written approval of Laboratory. • RMS has made their best endeavors to provide accurate and reliable information. RMS is not responsible for any financial liability due to any act of omission or error made. • Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to RMS within this period. • ** Information provided by Customer.			