

P.O.NO - 25100320


31305-03 - cone



TC-16176

TS-307

Unitech Laboratories Services LLP
 16, Samrat Industrial Area, B/h. S. T. Workshop
 Gondal Road, Rajkot - 360 004. Gujarat, INDIA
M+91 84600 60450, 99742 01090, 79901 74169
E unitech_lab@yahoo.com



SINCE 2010

Unitech®

You can always trust on our accuracy.

T E S T R E P O R T

ULR - TC16176250080270F																												
Name of the Customer : METAL MECH ENGINEERING.	Lab No. : US/4464/0725																											
Plot No. 4246, Road E, GIDC Phase-III, Dared, Jamnagar(Guj.) INDIA	Date of Reporting : 31/07/2025 Date of Smp. Receipt : 31/07/2025																											
Group : Chemical Testing of Metals and Alloys Sub Group : Stainless Steel #Customer Reference No. : Letter Date-31/07/2025 Condition of Sample : Cut Piece Material Specification : ASTM A276/A276M-24a Gr. 316L(S31603) #Identification of Sample : Size : Ø 36.00 MM #Type of Test : Chemical Analysis Instrument Utilized : Optical Emission Spectrometer-Bruker- German make-Q4 TASMAN Date of Testing : 31/07/2025 Test Method : ASTM E1086-22, JIS G-1253-2002																												
<table border="1"> <thead> <tr> <th>ELEMENTS</th> <th>OBSERVATION</th> <th>REQUIRED VALUE</th> </tr> </thead> <tbody> <tr> <td>% CARBON</td> <td>0.020</td> <td>0.03 max</td> </tr> <tr> <td>% SILICON</td> <td>0.445</td> <td>1.00 max</td> </tr> <tr> <td>% MANGANESE</td> <td>1.644</td> <td>2.00 max</td> </tr> <tr> <td>% PHOSPHORUS</td> <td>0.043</td> <td>0.045 max</td> </tr> <tr> <td>% SULFUR</td> <td>0.011</td> <td>0.030 max</td> </tr> <tr> <td>% CHROMIUM</td> <td>16.703</td> <td>16.00-18.00</td> </tr> <tr> <td>% MOLYBDENUM</td> <td>2.042</td> <td>2.00-3.00</td> </tr> <tr> <td>% NICKEL</td> <td>10.097</td> <td>10.00-14.00</td> </tr> </tbody> </table>	ELEMENTS	OBSERVATION	REQUIRED VALUE	% CARBON	0.020	0.03 max	% SILICON	0.445	1.00 max	% MANGANESE	1.644	2.00 max	% PHOSPHORUS	0.043	0.045 max	% SULFUR	0.011	0.030 max	% CHROMIUM	16.703	16.00-18.00	% MOLYBDENUM	2.042	2.00-3.00	% NICKEL	10.097	10.00-14.00	
ELEMENTS	OBSERVATION	REQUIRED VALUE																										
% CARBON	0.020	0.03 max																										
% SILICON	0.445	1.00 max																										
% MANGANESE	1.644	2.00 max																										
% PHOSPHORUS	0.043	0.045 max																										
% SULFUR	0.011	0.030 max																										
% CHROMIUM	16.703	16.00-18.00																										
% MOLYBDENUM	2.042	2.00-3.00																										
% NICKEL	10.097	10.00-14.00																										
Conformity statement : The above result is conform to ASTM A276/A276M-24a Gr. 316L(S31603)																												

End of Report



(Signature)

Tested By :
 Jaimini Vadodariya
 (Technician)

(Signature)

Authorized signatory:
 Deepak Solanki
 (Quality Manager)

Note: (1) Sample(s) not drawn by ULS. The results relate only to the sample(s) tested.

(2) This certificate shall not be reproduced, except in full, without the written approval of ULS.

(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in writing or he can collect the same.

(4) While "ULS" has made their best endeavors to provide accurate and reliable information.

(5) The conformity statement is given bases of decision rule documented in Quality Manual Annexure-3. 'H' Information Given by Customer

